AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Decorated prehistoric pottery from Castello di Annone (Piedmont, Italy): archaeometric study and pilot comparison with coeval analogous finds

This is the author's manuscript

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/140237> since

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

This Accepted Author Manuscript (AAM) is copyrighted and published by Elsevier. It is posted here by agreement between Elsevier and the University of Turin. Changes resulting from the publishing process - such as editing, corrections, structural formatting, and other quality control mechanisms - may not be reflected in this version of the text. The definitive version of the text was subsequently published in JOURNAL OF ARCHAEOLOGICAL SCIENCE, 40, 2013, .

You may download, copy and otherwise use the AAM for non-commercial purposes provided that your license is limited by the following restrictions:

- (1) You may use this AAM for non-commercial purposes only under the terms of the CC-BY-NC-ND license.
- (2) The integrity of the work and identification of the author, copyright owner, and publisher must be preserved in any copy.
- (3) You must attribute this AAM in the following format: Creative Commons BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/deed.en>),

When citing, please refer to the published version.

Link to this full text:

<http://hdl.handle.net/2318/140237>

**Decorated Prehistoric Pottery from Castello di Annone (Piedmont, Italy):
Archaeometric Study and Pilot Comparison with Coeval Analogous Finds**

Roberto Giustetto^{1,2*}, Giulia Berruto³, Eliano Diana³, Emanuele Costa¹

¹Department of Earth Science, Università di Torino, via Valperga Caluso 35, 10125 Torino (Italy)

²NIS Centre of Excellence, via Quarello 11, 10135 Torino (Italy)

³Department of Chemistry, Università di Torino, via P. Giuria 7, 10125 Torino (Italy)

*Corresponding author: roberto.giustetto@unito.it – tel. +39-011-6705122 – fax +39-011-6705128

Abstract

Prehistoric pottery decorated with incisions or impressions filled with white and seldom coloured inlays is well documented in the archaeological literature, but the related in-depth archaeometric studies are sporadic. 43 decorated ceramic shards, dating from the Neolithic to the Bronze Age, and an Iron Age fibula from the archaeological site of Castello di Annone (Piedmont, North-Western Italy) were analyzed with FTIR, Raman and XRPD for characterization of the ornamental pigments forming these inlays. Few white components were used as fillers, namely talc and bone ash (hydroxyapatite – Bone White), often as a mixture and seldom accompanied by other pigments (i.e. kaolinite and calcite). Comparison with freshly-heated biogenic hydroxyapatite proved that ancient Bone White pigment was calcined at about 900°C. Such a process was kept separate from pottery firing as these white mixtures show absence of talc degradation by-products and sporadic presence of kaolinite, implying these ceramics were decorated only after firing in furnace. Actual presence of fluorapatite in bone ash could allow dating with the Fluorine Method, but lack of fluorine detection with SEM-EDS causes such an attempt to be impracticable so far. A pilot comparative study with a restricted but representative group (11) of coeval finds from other sites of Piedmont suggests that while recurrence of talc prevails in Castello di Annone from the Neolithic throughout the Bronze age, massive use of bone ash (Bone White) becomes widespread in the close Iron Age settlements, possibly consequent to a more efficient handling of its production technology.

Keywords: Ceramics; Inlay-filled incision; Talc; Hydroxyapatite; IR-spectroscopy; X-Ray powder diffraction.

34
35

36 1. **Introduction**

37

38 The practice and tradition in prehistory to painstakingly fill incisions and/or impressions on
39 pottery with inlays (more frequently white, seldom coloured) is well documented in the
40 archaeological literature. A huge number of related finds, covering all the chronological
41 intervals from the Neolithic to the Iron Age, were described from locations dispersed all over
42 the world. The recurring motif adorning such artefacts is characteristic of specific historical
43 periods and often helps the archaeologists in accurately dating these ceramics. Besides, it is
44 commonly reputed that the choice of the materials, colours and techniques used to manufacture
45 such decorations and inlays can be related to both aesthetical and technological reasons
46 (Campbell, 1989), being eventually inspired to specific forms of symbolism (De Hostos, 1919;
47 Plog, 1980; Topping, 1987; Tiné, 1988; Baird, 1991; Blasco, 1994; Martìn and Delibes, 1989;
48 Gibson and Woods, 1997; Gibson, 2002, 2006; Laing, 2003; Prieto-Martínez et al., 2003).
49 In spite of such a widespread diffusion, few papers have been focused so far on the
50 archaeometric characterization of the materials used by our ancestors to realize such
51 ornamental motifs. As far as Italian finds are concerned, samples of white inlays from the
52 Piedmont site of Casalnoceto (AL) were previously analyzed with XRPD techniques, which
53 revealed the presence of talc (Venturino Gambari 1998; Venturino Gambari 2004). A more
54 recent work (Giustetto, 2008) evidenced possible use of kaolinite in white inlays applied on
55 incised ceramic shards coming from Pecetto (TO). Use of bone ash (Bone White) was detected
56 on ceramic shards from Switzerland (Rychner-Faraggi & Wolf, 2001; Giustetto, pers. comm.)
57 and Spain (Odriozola and Hurtado-Pérez, 2007). Analogous scientific studies on artefacts
58 coming from different countries are similarly rather scarce (Noll et al., 1975; Hagstrum, 1985;

Jernigan, 1986; Swann et al., 2000; Mohammed-Ali and Khabir, 2003; Striova *et al.*, 2006; Bugoi et al., 2008; Katsaros et al., 2009; Curtis et al., 2010).

This paper is focused on the in-depth archaeometric characterization of decorated fragmental pottery from the prehistoric site of Castello di Annone (Piedmont, Italy; Fig. 1) and includes a detailed archaeological description of the stylistic shapes and decorating motifs recurring in all investigated periods. The exhaustive characterization of the materials used to realize these ornaments, which cover a chronological period from the Neolithic to the Iron Age, brought to significant extrapolations concerning the manufacturing process and the techniques adopted to produce such artefacts.

To achieve such a goal a multi-disciplinary, micro-destructive analytical approach was adopted in order to preserve, as much as possible, the integrity of the pottery remnants. In addition to identification purposes, efforts were dedicated towards the possible detection of binding agents or other vehicles used to fix these inlays on the underlying ceramic body.

The outcomes obtained from the Castello di Annone pottery were further compared with analogous data collected on a restricted but representative group of ceramic implements from other almost coeval archaeological sites (Chiomonte, Fossano and Castelletto sopra Ticino; Fig. 1), all located in Piedmont but differentiated from the cultural, technical and aesthetic points of view. Such a pilot study, although preliminary, allowed the individuation of specific chronological periods or geographic areas in which some pigments were preferentially used.

(INSERT FIGURE 1)

2. **Materials and methods**

2.1 *Materials and Archaeological Case Study*

A significant number of decorated ceramic shards and/or implements (55) were extracted from the remnants of each archaeological site and selected for analysis. The material forming these white inlays appears non-homogeneously distributed but evident in those areas where it still abounds. For analytical purposes, two specimens were collected from each shard by scraping the surface with a fine scalpel, labelled by a prefix attesting the provenance (CdA: Castello di Annone; Ch: Chiomonte; F: Fossano; CT: Castelletto Ticino) and accompanied by an odd (inlay) or even number (underlying ceramic body).
(INSERT FIGURE 2)

2.1.1 Decorated pottery from Castello di Annone

43 ceramic shards and a bronze fibula bearing decorative incisions or impressions filled with white inlays were selected among the thousands of fragmental pottery from the site of Castello di Annone. Attribution to a specific chronological period was based on the peculiar shapes and decorating motifs and brought to the following partition: Neolithic (29), Copper Age (10), Bronze Age (4), Iron Age (1 fibula).

Located on a hill district alongside the Tanaro river, this site saw several occupational phases dating from the middle Neolithic (4500 BC) to the middle Iron Age (VI - V century BC) until the post-medieval epoch. Continuity for the anthropic settlement was favoured by propitious environmental conditions, fit for human activities. The village position over the surrounding areas allowed control of the whole Tanaro Valley, favouring agriculture development in alluvial soils suitable for cereal growing even with the raw ancient techniques. The archaeological features of the analyzed ceramic shards are detailed hereafter for each of the investigated periods, together with the description of a bronze fibula dating to the Iron Age.

Middle to Late Neolithic (ca. 4600 - 4200 BC): a sprawling and enduring anthropic settlement gave rise to flourishing lithic and pottery industries. The former saw presence of flint, quartz and obsidian splintered stone implements, sandstone or gabbro grindstones and eclogite or Na-pyroxenite polished greenstone implements (mainly axes or chisels) (Giustetto et al., 2008), in the form of finished or semi-finished handmade articles (Venturino Gambari and Zamagni, 1996; Salzani, 2005).

Among the thousands of fragmental pottery dating back to the Neolithic village, 29 shards bearing incisions or impressions filled with white inlays were selected (Fig. 2.a). 88% of these ceramics belongs to the so-called phase II (meander-spiralic style) of the ‘Vasi a Bocca Quadrata’ (‘Square Mouth Vase’: VBQ hereafter) culture (27 specimens; see Supplementary Material, Table S1), which can be divided in two fractions: i) a finer one, with predominant square or round mouth bowls decorated with motifs showing homogeneous syntaxes (i.e. excised triangles); ii) an accompanying fraction, where round mouth shapes (bowls, vases, cinerary urns) bear notched rims and/or wall-dragging decorations. No VBQ culture – phase I remnant was found, although some fragments differ from the others due to adoption of peculiar manufacturing techniques and decorative motifs, sometimes accompanied by different impastos. This atypical material can be further divided in two groups (termed 2 and 3): i) group 2 ceramics show decorations which outline banded or stripped motifs, realized with the incision technique and showing traits leading back to the Varese Isolino VBQ facies; ii) group 3 ceramics can be referred to intervened contacts with the phase III of VBQ culture, occupying quite a restricted geographic area (eastern Lombardia, Veneto and Trentino). Finally, some ceramics shards are consistent with the plastic elements style due to presence of ashlar and elongated grips applied on sumptuously decorated VBQ shapes, apparently contradicting those features typical of other sites belonging to phase III (Salzani, 2005).

Arrival of people from the low and medium Rodano valley between 4400 and 4200 BC caused the VBQ traits to be contaminated by Western features. These materials form the residual 12% of the Castello di Annone ceramics (2 specimens: CdA33 and CdA81; see Supplementary Material, Table S1) divided in two groups: i) with traits leading back to the St. Uze style (deep shapes decorated with plastic elements); ii) with motifs typical of the ancient Chassey Culture (painted lattice-disposed triangles, bands filled by vertical lines, seldom with irregular geometric motifs). These implements show fine to medium-grained impastos and polished surfaces, with distinctive shapes (decorated rectilinear, convex-profile or brim-bordered bowls prevailing on globular or egg-shaped jars, neck-shaped vases or cups). Graffito decorations are characterized by canaliculated handles and single or multiple pierced grips, together with persistence of ribbon-shaped handles (Padovan, 2005).

Copper Age (ca. end of 3000-2000 BC): in the Eneolithic period a reduced human presence is apparently observed in the whole Piedmont region, probably because of a more enhanced mobility of the human groups. In Castello di Annone evidences about the knowledge of copper metallurgy were found, accompanied by new decorative typologies for ceramics, characterized by irregular and rough surfaces and by a composite syntax of ornaments in the form of plastic cordons. Influences from the Varese Isolino and from the French Culture of Chassey can be noticed throughout the whole III millennium BC, while decorative features typical of the bell-jar Culture appear only in the 2nd half.

Ten Eneolithic ceramic shards (bowl side fragments) were analyzed (Fig. 2.b; see Supplementary Material, Table S1), mainly characterized by metopal incised decorations filled with white to yellowish inlays.

Bronze Age (ca. end of 2000-1000 BC): a vast number of ceramic shards referred to all four chronological periods (Ancient, Medium, Late and Final) of such an Age (2nd

millennium BC) were found, consistently with an existing pile-dwelling and ‘terramaricole’ civilization. Between the end of the XVIII and the XVII Century, passing from the Ancient to the Medium Bronze Age, the more evident characteristic about the ceramics manufacture is the wide diffusion in the whole Italian peninsula of the axe-shaped handle superelevation which occurs in bowls. Such a feature (which appears in the Castello di Annone ceramics as well as in those coming from Mercurago and Chiomonte), though not directly related to any specific Culture, must be considered as an influence exerted by the Italian style also in the Cisalpine area. During the Late Bronze Age, fibulae in bronze and other metallic alloys begin to appear. Four ceramic shards (bowl sides), bearing parallel or zigzagged incised decorations filled with a white to yellowish inlay, were analyzed (Fig. 2.c; see Supplementary Material, Table S1).

Iron Age (ca. 1st Millennium BC): in addition to ceramic implements, several fusions in bronze can be found during the following Iron Age, such as fibulae, buckles, pendants and arrow tips. Some fibulae show different and peculiar features (i.e., snaked or Celtic bark wire) possibly used to relate these implements to specific cultures (i.e. the ‘Ligures’ people, for those fibulae found in the protostoric burial ground near Chiavari). As representative of this period, a bronze fibula (CdA67) bearing round-shaped incised decorations filled with a whitish inlay was analyzed (Fig. 2.d; see Supplementary Material, Table S1).

2.1.2 Decorated pottery from other coeval archaeological sites

A representative group of analogously decorated pottery implements from other archaeological sites of Piedmont [Chiomonte (Ch): one shard; Fossano (F): 4 implements; Castelletto sopra Ticino (CT): 6 implements] was also sampled and labeled

189 accordingly, in order to be analyzed for comparative purposes. Ceramics from
190 Chiomonte date back to the Neolithic age (between 6.000 and 3.500 BC), whereas
191 implements related to the other two sites date back to the Early to Middle Iron age
192 (VIII-VI century BC and 825-675 BC for Fossano and Castelletto sopra Ticino
193 respectively). A brief archaeological description of these ceramics is reported hereafter.
194 (INSERT FIGURE 3)

196 2.1.2.1 *Chiomonte/La Maddalena*

197
198 Located in the higher part of Susa Valley, this site lies at the base of a slope facing
199 South, disposing of water and soils suitable for cereals and legumes cultivation
200 (Padovan and Thirault, 2007). An archaeological excavation, hurriedly performed
201 during a motorway construction, brought to light different occupational phases
202 running from the Neolithic to the Middle Age.

203 An important enduring settlement attributed to a transalpine group of Chassey
204 Culture (Bertone et al., 1986) that dates back to the late Neolithic, has been related
205 to commercial exchanges of both flintstone and greenstone implements, together
206 with the development of high-altitude itinerant stock-rising. Ceramics from this
207 period show convex bottom vases, bearing single, double or multiple grips, pierced
208 and located close to the border and along the body, with fine to medium-grained
209 impasto. Recurrent shapes are frustum of cone bowls and ovoid or globular vases
210 with short, cylindrical neck and brimmed dishes, incised by graffito or impressed
211 decorations with white or coloured inlays (red, brown or black; Padovan and
212 Thirault, 2007; Bertone and Fozzati, 2002). A single ceramic shard from
213 Chiomonte (Ch1) was investigated, dating back to the Late Neolithic (ca. 3700 BC)

and bringing a scratch decoration filled with a red inlay (Fig. 3.a, see Supplementary Material, Table S2).

2.1.2.2 *Fossano*

This site is located on a plateau near the Stura di Demonte river, in a position suitable for anthropic settlement thanks to the presence of water resources, soils for cultivation/breeding and visual control on the surrounding landscape. Recent archaeological surveys discovered traces of a continuous occupation from the Neolithic to the Iron Age. In the Bronze Age, a cultural and economical development favoured the rise of commercial relationships with other transalpine areas and Golasecca, causing social differentiation evidenced by appearance of typical Ligurian crematory rites (Gambari, 2004). Use of river navigation as commercial paths allowed these Ligurian groups to control the access to the coast and alpine passes. The influence exerted by Etruscan groups is testified by prestige objects found in Ligurian territories from VII century BC, when Fossano became a startling example of demographical crowding.

The related ceramic shapes (VIII-VI century BC) show short-rimmed cups, deep-tanked bowls, big frustum of cone-necked vases decorated by banded incisions, ovoid vases with protruded rim and digitally impressed cord between rim and shoulder. Decorations are infrequent and consist of incised bunches of short lines/grooves and zigzagged motifs, sometimes filled with a white inlay (Venturino Gambari et al., 1996). Both of these motifs can be found on the four white-decorated analyzed finds (F1, F3, F5, F7; Fig. 3.b, see Supplementary Material, Table S2),

2.1.2.3 Castelletto sopra Ticino

This site, together with Varallo Pombia, saw the development in the IX century BC of the so-called Golasecca Culture in an area covering the actual borderlines of Piedmont, Lombardy and Canton Ticino, where also previous cultures had arose (i.e. the Canegrate Culture in the XIII century BC, equivalent of transalpine cultures, and the Cisalpine Culture, defined as Protogolasecca, in the final Bronze Age - XII-X century BC). The Golasecca Culture developed during the Iron Age in an area surrounding the commercial lines directed North-South (Ticino-Verbano e Agogna-Cusio-Toce systems; Gambari, 1988) and gradually became the *trait d'union* between the Mediterranean Sea and Continental Europe. In the VII-VI century BC the richness of these communities favoured the demographical growth of Castelletto Ticino, Sesto Calende, Golasecca and Como (Gambari and Cerri, 2009), which acquired proto-urbane dimension hosting most pre-roman necropolis of the North-West of Italy. Prestigious objects were found both in Golasecca and in Celtic transalpine areas, testifying the well developed commercial system existing among Etruscans, Celts and Greeks (De Marinis, 1991; Kruta, 2003, 2004).

The Golasecca culture covers three chronological periods (I, II and III), each characterized by peculiar ceramic decorations. All six analyzed implements (handmade ovoid or spheroid bi-conic cinerary urns with scarcely depurated impastos and incised decorating motifs filled by white inlays; Fig. 3.c) belong to the first, more ancient period, which can be further articulated in Golasecca I A (between IX and VIII century BC), I B (end of VIII and beginning of VII century BC) and I C (half of VII to beginning of VI century BC). A sharper attribution can

be made by keeping into account the evolution of the decorative motifs. Three cinerary urns (CT7, CT9 and CT11; Fig. 3.c, see Supplementary Material, Table S2) belong to the I A sub-period and bear in the upper half a repetitive ‘thin rope’ decorating motif, showing two stripes of reversed triangles incised by oblique parallel impressions (‘wolf-tooth’ decoration). These decorations are filled by a white inlay and divided by two or more gridded or zigzagged thin stripes (De Marinis, 1982). In the Golasecca I B sub-period, the ‘thin rope’ decorated bi-conic urns have been substituted by incisions showing ‘wolf-tooth’ decorations divided by a single stripe with network motifs (CT1, CT3 and CT5; Fig. 3.c, see Supplementary Material, Table S2). The following Golasecca I C and II periods bring to predominance of typical globular or ovoid urns bearing ‘*stralucido*’ decorations, characterized by larger and more complicated ‘wolf tooth’ motifs which tend to disappear in the III period.

2.1.3 Synthetic talc/hydroxyapatite mixtures

Freshly synthesized white mixtures of known wt% composition were prepared by grinding talc and hydroxyapatite. Talc powders were obtained by crushing of a natural specimen coming from the ‘Nuova Fontane’ mining concession, near Perrero, Prali and Salza di Pinerolo (Piedmont, Italy). Biogenic hydroxyapatite was obtained by thigh bovine bones according to the method proposed by Herliansyah et al. (2009). After cleaning and boiling three times (30 min, each time changing water), the bones were sun-dried for three days, cut with a hacksaw and calcined in a box furnace at 900° for 2 hours (5°C/min heating ramp) to remove organic matrix and avoid soot formation. The calcined bone fragments were cooled at room temperature and ground in an agate

mortar. The degree of purity for both talc and hydroxyapatite was checked by XRPD, which showed absence of accessory mineral phases.

2.2 Analytical methods

A multi-disciplinary, micro-destructive analytical approach – comprehending FT-IR, Raman, X-ray diffraction and SEM-EDS – was adopted to achieve an exhaustive archaeometric characterization of all colorizing agents forming these inlays. Such an evidence is often hardly reached by using a single technique, due to the intrinsic limits which inevitably affect each method. X-ray diffraction allows a sharp mineralogical analysis of the studied specimen, but is strongly biased by the high intensity of those reflections related to heavy-scattering materials (such as quartz, feldspars and micas, quite abundant in the ceramic body) which may cover signals related to the white pigments. Though less affected by such an inconvenient, an exclusive characterization by means of vibrational spectroscopies (FTIR and Raman) may be troublesome, due to dubious attribution of the related absorption bands and consequent sharp phase identification. An undisputable identification needs therefore to be supported by a cross-checked convergence of data collected with different methods. In addition to pigment identification, vibrational spectroscopies were also used to possibly identify those binding agents (presumably organic) used to fix the colouring agents on the underlying ceramic body. IR absorption spectra were collected on a FT-IR Bruker Vertex 70, equipped with an ATR attachment with a resolution of 2 cm^{-1} , collecting 32 scans for each spectrum. FT-Raman spectra were collected on a Renishaw in Via Raman Microscope with a laser emitting at 785 nm. Photons scattered by the sample were dispersed by a 1200 lines/mm grating monochromator and simultaneously collected on a CCD camera; the collection

318 optic was set at 50X objective. The spectra collection setup of 75 acquisitions, each taking
319 50 s, was adopted.

320 X-ray powder diffraction (XRPD) data were collected on hand-ground specimens in an
321 agate mortar using an automated PW3050/60 PANalytical X'Pert-PRO diffractometer,
322 with θ - θ setup and an RTMS (real Time Multiple Strip) detector using monochromatized
323 Cu-K α radiation. The use of capillary has been prevented from the scarcity of the
324 samples; for this reason diffraction data were collected on a zero-background, Si-
325 monocrystal flat sample holder. Preferred orientation effects were attenuated by
326 suspending the crushed powders in a non-volatile inert solution (amyl acetate + 5%
327 collodion), thus maximizing the statistic disposition of the crystallites.

328 Quantitative analyses, restricted to the mutual talc and hydroxyapatite weight% amounts
329 forming the ancient white pigment mixtures, were extrapolated by comparing the
330 intensities of the experimental diffraction data with those collected under the same
331 conditions (powders dispersed in amyl acetate + 5% collodion on a zero-background
332 sample holder) on purposely prepared mixtures of known wt% composition (see
333 Supplementary Material, Fig. S1). Multiple calibration curves were independently
334 computed by calculating the ratio between the integrated intensities of several couples of
335 non-overlapping talc and hydroxyapatite reflections [i.e. between the (002), (004), (006)
336 and (0010) peaks of talc and the more intense (211) peak of hydroxyapatite] in each of the
337 synthesized control mixtures (see Supplementary Material, Fig. S2). These curves were
338 applied in reverse on the experimental data collected on the ancient specimens, thus
339 obtaining an estimate of the mutual wt% talc-hydroxyapatite amounts for each couple of
340 reflections (generalized Reference Intensity Ratio – RIR method). All computed estimates
341 were further averaged so to possibly smooth the residual preferred orientation biasing the
342 (00 l) peaks of talc (only ones visible in the experimental data). The Diffrac Plus (2005)
343 evaluation package was used for both qualitative and quantitative mineralogical analyses.

Scanning Electron Microscopy was performed using a SEM Stereoscan 360, Cambridge Instrument, coupled with an EDS Link Pentafet Oxford instrument equipped with a ‘thin window’ detector, that allows qualitative/quantitative chemical analyses of light elements (down to Boron). Working parameters were: acceleration voltage 15 kV, working distance 25 mm, probe current 1 nA and spectra acquisition time varying from 60 to 300 s. Standardization was performed using a pure Co specimen. Chemical data collected on unpolished and carbon coated fragments of the white inlays scraped from the ancient ceramics were processed with the Inca 200 Microanalysis Suite Software, version 4.08.

3. **Results**

Despite the scant mass of each scraped specimen (few mg), the adopted analytical approach allowed in most cases an exhaustive characterization of all white pigments used for the manufacture of these inlays, together with other polluting phases possibly related to the underlying ceramic body (whose presence is justified by the objective difficulty in sampling the scarce and extremely thin superficial white layer). Presence of contaminating materials can also be related, in specific cases, to impurities of the pigment mixture. A complete list of all materials detected in the analyzed Castello di Annone inlays, together with a concise archaeological description of each ceramic shard, is given in Table S1 (see Supplementary Material).

The pilot comparative study conducted by matching the Castello di Annone outcomes with those of analogous pottery from other anthropic settlements in Piedmont, although suffering from a restricted statistic, sketched an extremely appealing picture about the possible recurrence-predominance of specific materials in particular areas or periods. The complete list of ceramic implements coming from other sites of Piedmont (Chiomonte, Fossano and

Castelletto sopra Ticino) and analyzed for comparative purposes, comprehensive of all above mentioned data, is listed in Table S2 (see Supplementary Material).

3.1 Castello di Annone

Analytical data collected on 43 ceramic shards and one bronze fibula from Castello di Annone are commented hereafter for each of the adopted techniques.

3.1.1 Vibrational spectroscopies

FTIR evidences suggest that at least two different materials were mainly used as white fillers to produce these inlays. The recurring presence, in several spectra, of the $\delta(\text{OH})$ absorption band at 669 cm^{-1} leads to possible presence of talc ($\text{Mg}_3\text{Si}_4\text{O}_{10}(\text{OH})_2$) (Farmer 1974, Wilkins 1967). Traces of the talc signature were unequivocally detected in 17 out of the 44 analyzed archaeological finds (for example CdA1, CdA7, CdA11, CdA23, CdA37, CdA39, CdA41 and CdA49 – see Supplementary Material, Table S1; Fig. 4). Other samples show presence of a different kind of hydroxyls [bands at 3572 cm^{-1} - $\nu(\text{OH})$ and 630 cm^{-1} - $\delta(\text{OH})$], coupled with bands related to presence of CO_3^{2-} (signals at 1460 , 1419 and 873 cm^{-1} ; Fowler, 1974) and PO_4^{3-} groups (1040 , 1093 and 962 cm^{-1} ; Babot and Apella, 2003). A broad band at 1640 cm^{-1} is related to $\delta(\text{H}_2\text{O})$, whose stretching counterpart forms a broad feature between 3250 cm^{-1} and 3500 cm^{-1} . All these evidences point to possible presence of a phosphate/carbonate phase such as hydroxyapatite [$\text{Ca}_5(\text{PO}_4)_3(\text{OH})$] and carbonate-hydroxyapatite [$\text{Ca}_{10}(\text{PO}_4)_5\text{CO}_3(\text{OH})$], mineral components of bone. This suggests possible use of Bone White, an ancient synthetic pigment obtained by calcination of animal bones, teeth and antlers. Unequivocal

detection of hydroxyapatite spectral signature was detected in 5 out of the 44 analyzed specimens (i.e CdA3, CdA5, CdA17, CdA25, CdA53; see Supplementary Material, Table S1; Fig. 4).

Raman spectra unfortunately evidenced strong fluorescence in all analyzed specimens, which basically prevented an easy interpretation of the collected data. Presence of Bone White is however further supported by the typical phosphate band, systematically emerging from the convolute background at about 961 cm^{-1} (not shown; Silva and Sombra, 2004) in those specimens marked by recurrence of the typical hydroxyapatite IR absorption bands.

In some specimens FTIR absorption bands related to both talc and hydroxyapatite were observed (i.e. CdA51, CdA65; see Supplementary Material, Table S1), implying that a mixture of these two materials was possibly used to realize these white inlays. An unambiguous attribution of each signal to a specific colouring agent, however, is not easy because bands related to the main component tend to mask those of the subordinate material, which appear only as weak shoulders (i.e. CdA9; CdA23; CdA85; see Supplementary Material, Table S1).

Sporadic IR evidences (bands at 1436 , 1088 and 874 cm^{-1}) about presence of calcite, possibly as the result of secondary, post-burial deposition processes (rather than an additional white agent) were also recorded twice (i.e. CdA27, CdA51; see Supplementary Material, Table S1).

In some cases (i.e. CdA13, CdA19 and CdA31) spectroscopic data collected on the white fillers specimen strongly resemble those of the corresponding ceramic body (CdA14, CdA20 and CdA32 respectively), suggesting a contamination during sampling. Such a limitation, dictated by the scarcity of the residual layer of inlay, generally did not prevent an accurate characterization of the white components (with some due exceptions, i.e. CdA19, CdA75, CdA87; see Supplementary Material, Table S1).

In addition to white pigments and ceramic components, other weak bands were often observed probably related to presence of proteins (i.e CdA7, CdA11 and CdA21). Though unequivocal identification could not be achieved, presence of these signals could possibly be related to residual traces of binding agents apt to favour adhesion of the inlay to the substrate. In some cases traces of a consolidant resin (paraloid) were also detected, consequence of an intervened restoration (i.e. CdA19). FTIR data collected on the decorated bronze fibula (CdA67) evidenced presence of a multi-component white mixture, including bone ash (hydroxyapatite) and calcite. (INSERT FIGURE 4)

3.1.2 X-Ray Powder Diffraction

The enhanced sensibility granted by XRPD towards detection of the bulk composition allowed a more exhaustive characterization of all mineral phases forming the studied decorating motifs, together with the description of all contaminating phases related to the underlying ceramic body and/or pigment impurities. Adoption of essentially two different white components for the manufacture of these ornaments is basically confirmed by XRPD. On the basis of their mineralogical composition, all investigated specimens can be approximately divided in three main groups: i) exclusively talc-constituted inlays (15 out of the 44 total samples: for example CdA1, CdA7, CdA23 and CdA37 – Fig. 5.a); ii) presence of talc and hydroxy-/carbonate-hydroxyapatite (bone ash) mixtures (18 specimens), which can be the sole components (14 samples, such as CdA9, CdA11, CdA29 and CdA85 – Fig. 5.b) or combined to additional white agents (4 cases, such as CdA13 with kaolinite or CdA51 with calcite), with variable quantities in different specimens; iii) exclusive presence of pristine Bone White (3 specimens, i.e. CdA3, CdA5 and CdA17 – Fig. 5.c). An exception

to such a rule is offered by CdA27, which showed an atypical calcite + kaolinite composition. For 7 specimens an unequivocal characterization could not be achieved, due to insufficient sampling or heavy contaminations from the ceramic body.

A mixture of two white components, namely talc and bone ash (calcined hydroxyapatite), is therefore likely to have been used in most cases. The mutual amounts of talc and hydroxyapatite in such mixtures were extrapolated, whenever possible, by comparing the intensities of the related diffraction peaks with those of control mixtures of known composition. The related results, expressed as absolute talc and hydroxyapatite wt%, are reported in Table 1. Despite the relatively high standard deviations [computed by averaging the compositional estimates obtained on different couples of reflections, in an attempt to smooth the residual preferred orientation inevitably affecting the (00 l) talc reflections], it is worth noting that throughout all the investigated chronological periods (from the Neolithic to the Bronze Age) the amount of talc usually exceeds or approximately equals that of hydroxyapatite (bone ash), with few exceptions (i.e. CdA13, CdA15 and CdA25).

(INSERT TABLE 1)

Among those inlays containing only pristine talc, it has to be pointed out that although this composition is unequivocal in unpolluted samples (such as CdA1, CdA23 and CdA39), it is objectively difficult to assess whether small amounts of bone ashes are present when strong contamination occurs. The diffraction signatures of high scattering materials from the ceramic body, in fact, tend to mask those signals related to low scattering hydroxyapatite, possibly thwarting its accurate characterization (i.e. CdA43 and CdA69).

Subordinate amounts of contaminating components were observed, in addition to the white pigments, in almost all investigated specimens. Presence of chlorite [(Mg,Al)₆(Si,Al)₄O₁₀(OH)₈], often coupled to talc in natural outcrops, was sporadically

recorded (i.e. CdA7) and related to an impurity of the pigment itself. Peaks related to quartz, micas (biotite and muscovite) and feldspars (orthoclase and plagioclase), detected in most specimens, can conversely be justified by intervened contaminations from the ceramic body during sampling, an hypothesis confirmed by the diffraction data collected on the bulk of the ceramic shards (specimens labelled 'CdA' and followed by an even number). As mentioned above, strong contaminations could occasionally prevent an exhaustive characterization of all decorating agents (for example in CdA19, CdA55 and CdA75).

Diffraction data collected on the white inlay scraped from the Iron Age bronze fibula (CdA67) evidenced contextual presence of predominant talc, abundant calcite (CaCO_3) and subordinate hydroxyapatite, together with the detection of hydrocerussite $[(\text{PbCO}_3)_2\text{Pb}(\text{OH})_2]$ and negligible quantities of contaminant phases (such as quartz and feldspars). Possible traces of hydrocerussite were also observed in the CdA83 specimen (see Supplementary Material, Table S1).

(INSERT FIGURE 5)

3.2 Comparison with decorated pottery from other archaeological sites

A brief but exhaustive analytical report concerning the restricted group of prehistoric decorated ceramic shards and implements coming from the three additional sites of Chiomonte, Fossano and Castelletto sopra Ticino, studied for comparative purposes, is exposed hereafter.

3.2.1 *Chiomonte/La Maddalena*

The FTIR pattern of the unique Late Neolithic (ca. 3700 BC) ceramic shard from Chiomonte (Ch1), decorated by incisions filled with a reddish inlay (Fig. 3.a), shows a strong absorption band at 1082 cm^{-1} together with minor features appearing at 1166, 798, 778 e 694 cm^{-1} , possibly related to quartz. The broad band peaking at 3400 cm^{-1} can be related to $\nu(\text{OH})$, suggesting possible presence of a hydroxylated mineral such as hydroxyapatite or kaolinite. Minor features appear at 1032 (Si-O-Si), 1009 (Si-O-Al), 938 and $914\text{ (Al-O-H)}\text{ cm}^{-1}$ (Fig. 6). Though no direct IR evidence was found, detection of quartz and other minerals may suggest presence of red ochre (hematite, Fe_2O_3) as the possible colouring agent (Bikiaris *et al.* 1999). Such a hint is confirmed by the appearance of weak reflections related to hematite in the XRPD pattern (not shown). Traces of hydroxyapatite and subordinate talc were also detected, but no kaolinite was found. As suggested by FTIR, massive presence of quartz together with feasible traces of a spinel-like phase [$\text{Mg}(\text{Al,Fe})\text{O}_4$; $d = 2.031\text{ \AA}$] were observed.

(INSERT FIGURE 6)

3.2.2 Fossano

The four white-decorated finds (F1, F3, F5, F7; Fig. 3.b) show FTIR and Raman patterns quite similar. In all cases, vibrational modes related to hydroxyls (3572 and 630 cm^{-1}), phosphate (1093 , 1040 and 962 cm^{-1}) and carbonate groups (1460 and 875 cm^{-1}) lead to presence of hydroxy-/carbonate-hydroxyapatite phases, suggesting pristine Bone White as the sole pigment forming these inlays (Fig. 7.a). This assumption is basically confirmed by XRPD, which however shows that variable amounts of talc are also present in all specimens in addition to bone ash (hydroxyapatite; Fig. 7.b). The mutual talc-bone ash amounts, inferred from XRPD data, show that the talc quantities are sensibly lower than those observed for Castello di Annone, only occasionally reaching worth mentioning

values (i.e. F7: $\cong$ 20%; Table 2). The observed compositional monotony is consistent with the excellent purity of the samples; minor traces of quartz and orthoclase, residues of the ceramic body, can only be observed in addition to white pigments.

(INSERT TABLE 2)

(INSERT FIGURE 7)

3.2.3 *Castelletto sopra Ticino*

The FT-IR and Raman spectral features of all six analyzed decorated pottery implements show absorption maxima related to hydroxyls (3572 and 630 cm^{-1}), phosphate (1093, 1040 and 962 cm^{-1}) and carbonate groups (1460 and 875 cm^{-1}), leading to presence of hydroxy-/carbonate-hydroxyapatite phases (Bone White pigment). Some specimens show traces of a Paraloid contamination, possibly applied during the conservation work, as certified by a weak feature at 1732 cm^{-1} (Fig. 8.a). Massive presence of both hydroxy-/carbonate-hydroxyapatite is unequivocally confirmed by XRPD, though in all samples subordinated amounts of talc are also detected. The mutual talc/hydroxyapatite amounts in these mixtures, inferred by XRPD (Table 2), show that bone ash is always predominant; talc is very scarce, only occasionally reaching 15 wt% (i.e. CT1 and CT7; Fig. 8.b). The essential purity of the analyzed specimens is corroborated by the scarce presence of contaminant phases (quartz, feldspars and micas) from the ceramic body.

(INSERT FIGURE 8)

4. **Discussion**

The analytical survey performed on the Castello di Annone fragmental pottery shows that the white fillers used to manufacture these inlays can be essentially traced to a restricted variety of natural and/or synthetic pigments, mainly represented by talc and bone ash (Bone White). The former, in particular, is the most frequently used, appearing as the exclusive colouring agent in 34% of the investigated specimens. An even more relevant fraction (41%), however, shows presence of talc and hydroxyapatite mixtures, mostly with no further addition (32%) and seldom with the sporadic contribution of other colouring agents (9%) such as kaolinite, calcite (presumably of secondary origin) and/or hydrocerussite. Generally these mixtures are formed by approximately equal weighed quantities of talc and bone ash (50% of the investigated specimens), but frequently (33%) talc is more abundant (Table 1). Pristine Bone White inlays (7%) are also observed (Figure 9.a and 9.b).

(INSERT FIGURE 9)

The recurrent use of talc/bone ash mixtures is basically confirmed by data collected on decorated ceramics from other archaeological sites of Piedmont (namely Fossano and Castelletto Ticino; Table 2), although in this case sheer predominance of hydroxyapatite on talc is observed (Figure 9.b).

Talc is a frail phyllosilicate mineral formed by alteration of Mg-bearing silicate rocks in low-degree metamorphic conditions, whose crushing gives a white powder often used as a pigment or extender in prehistory (Swann et al., 2000; Hradil et al., 2003; Chairkina and Kosinskaia, 2009; Pesonen and Leskinen, 2009). Talc outcrops are quite common in Piedmont and surrounding areas located near the actual towns of Ala (TO), Bibiana (TO), Borzoli (GE), Castel Delfino (CN), Chamonix (France), Col de Tende (France), Lanzo (TO), Masone (GE), Monte Rosa (VB), Montjovet (AO), Prali (TO), Traversella (TO), Viù (TO) and Voltaggio (AL) (Barelli, 1835). Another even more suitable source for talc, however, is represented by steatite (or soapstone), a talc-schist metamorphic rock often associated with the ophiolitic rocks typical of the low Piedmont region. Steatite is quite common in the neighbourhoods of the

investigated Castello di Annone site and its direct crushing produces a fine, fairly whitish powder (depending on the wt% of talc) directly useable as a pigment.

Bone White is a chemically inert and heat resistant synthetic pigment obtained by calcination at high temperature of animal bones and/or teeth, whose ashes contain a mixture of two similar phosphates, hydroxyapatite and carbonate-hydroxyapatite. In fresh bone tissue, hydroxyapatite accounts for about 40% of the total weight, the remaining 60% being related to H₂O and organic constituents (mainly collagen). When heated, bone loses around 25% of its mass due to loss of H₂O and organic matter combustion; this process does not affect the Ca/P ratio of biogenic hydroxyapatite, which varies between 1.83 and 2.51. Non-biogenic (mineral) hydroxyapatite, conversely, shows an average Ca/P ratio < 1.8 (Shiegl et al., 2003; Zaichicka and Tzaphlidou, 2002). Use of synthetic Bone White as the main constituent of similar inlays filling incisions on prehistoric pottery is known from literature (Roberts et al., 2007; Odriozola and Martínez-Blanes, 2007; Odriozola and Hurtado Pérez, 2007; Curtis et al., 2010; Parkinson et al., 2010), even in the Far East (Li et al., 2009). In all analyzed specimens, the biogenic origin of this pigment is experimentally supported by appearance of FTIR absorption maxima at 1460, 1419 (CO₃²⁻ substitution of either the OH⁻ or -PO₄³⁻ groups: Fowler, 1974; Smith, 1999) and 873 cm⁻¹ [ν (CO₃); Dauphin, 1993; Farmer, 1974] (See Fig. 4; CdA5). These bands, in fact, are typical of fossil bones but absent (or weak) in mineral hydroxyapatite, whose natural sources in Piedmont and surrounding areas are scarce. In addition, detection of the 630 cm⁻¹ band (OH librational mode) may suggest that bone calcination occurred at high temperature (Odriozola and Hurtado Perez, 2007). This process is known to cause *T*-dependent transformations in biogenic hydroxyapatite, which significantly vary its crystalline degree. In fresh bone tissue (pattern 1 in Fig. 10.a) broad diffraction peaks are observed for hydroxyapatite, a situation which is not significantly affected by natural ageing (pattern 2 in Fig. 10.a). Severe heating (i.e. calcination; Rogers and Daniels, 2002), on the other hand, causes appearance of progressively narrower reflections (i.e. calcined bovine thigh bone,

pattern 3 in Fig. 10.a), symptomatic of an increased crystallization analogous to that observed in the ancient inlays made of pristine Bone White (pattern 4 in Fig. 10.a).

(INSERT FIGURE 10)

While XRPD data show that talc and calcined biogenic hydroxyapatite mixtures were used in most cases, FT-IR/Raman techniques seldom evidence contextual presence of both these components in the analyzed inlays.

The mutual talc/bone ash quantities in these mixtures tend to significantly vary in the different investigated sites, leading to important archaeometric extrapolations. Although more or less significant differences can be observed even within the same context, generally in the more ancient Castello di Annone site use of talc appears to be predominant: such a pigment can be exclusive (34% of the analyzed specimens) or mixed to minor or equal hydroxyapatite amounts (40%) (Figure 9.a). Due exceptions are represented by pure Bone White inlays (i.e. CdA3 and CdA5) or mixtures where bone ashes prevail upon talc (i.e. CdA13 and CdA25; Table 1). In the more recent Iron Age locations (Fossano and Castelletto sopra Ticino; Table 2), conversely, hydroxyapatite becomes significantly more abundant than talc, occasionally pertaining an almost exclusive role (Figure 9.b).

The adopted approach makes it impossible to determine whether bone ash and talc were mixed and applied simultaneously or rather be the result of distinct and sequential applications. If the latter hypothesis is true, multiple coats may have been spread by various hands in different ages, possibly due to colour ‘refreshment’ or ‘vintage’ restoration. A careful, in-depth stratigraphic study of these inlays – involving both optical microscopy and SEM-EDS – could possibly shed light on this aspect, although the macro-destructivity of this approach could severely spoil these precious prehistoric relics. Despite the absence of such information, however, it is unquestionable that in Castello di Annone use of talc – alone or mixed to bone ash – was widely adopted throughout all the investigated periods (Neolithic, Copper and

Bronze Age), whereas in the more recent Iron Age sites (Fossano and Castelletto sopra Ticino) an almost exclusive use of hydroxyapatite prevailed.

Massive use of talc/bone ash mixtures brings to other fundamental extrapolations concerning the technology used to manufacture these white inlays. An analytical method was proposed in literature to infer the burning temperature of bone remains from XRPD and FTIR data (Pleshko et al., 1991; Piga et al., 2008) based on the crystal size increase and structural changes triggered by heating of biogenic hydroxyapatite (Bonucci and Graziani, 1975; Shipman et al., 1984). A correlation exists between the Full Width at Half Maximum (FWHM) of selected diffraction peaks and the temperature reached during calcination (Bartsiokas and Middleton, 1992; Person et al., 1995). In crude bone, the (211) and (112) reflections ($2\theta \cong 31.8^\circ$ and 32.2° using $\text{CuK}\alpha$, respectively) are overlapped and virtually indistinguishable while the (300) peak ($2\theta \cong 32.9^\circ$) appears as a shoulder (Surovell and Stiner, 2001). By gradually heating, the (211) and (112) peaks start to split (700-750°C) until complete separation (850-900°C) whereas the (300) reflection grows in intensity. This sequence is due to progressive transformation with the temperature rise of hydroxyapatite to β -tricalcium phosphate (Grupe and Hummel, 1991; Nielsen-Marsh, 2000; Roberts et al., 2002). All analyzed specimens containing bone ashes (pristine Bone White or talc/hydroxyapatite mixtures), both from Castello di Annone and the other investigated sites, show sharp and distinct diffraction peaks: the computed FWHM of ancient bone ash (211), (112) and (300) reflections (see, for example, CdA5 and CT1 in Fig. 10.b) corresponds to that of fresh biogenic hydroxyapatite calcined at 900°C (OH-apt in Fig. 10.b). Besides, these data are in excellent agreement with those presented by Odriozola and Martínez-Blanes (2007; Fig. 10.c), further confirming that calcination for preparation of ancient bone ash indeed occurred at 900°C. These values are consistent with the presumed firing temperatures of these ceramics, qualified as low-fired productions (temperature varying between 750 and 900°C) comparable to coeval French and Swiss findings (Covertini, 1996; Morzadec, 1995; Salanova, 2000). While studying Neolithic ceramics from the Middle

Guadiana river (Badajoz, Spain), Odriozola and Hurtado Pérez (2007) assumed that similar ornaments were applied (with or without a binder) as crude bone powder, made into a paste, directly on the uncooked forged implements before firing in furnace: formation of bone ash would therefore be a byproduct of the ceramics firing. Though similar conclusions could be claimed for the pristine Bone White inlays studied here (i.e. CdA3 and CdA5), the recurrent detection of two-components mixtures (talc + bone ash) in variable ratios leads to an alternative interpretation. The thermal decomposition of talc is known to begin at 800°C (Wesolowski, M., 1984; De Souza Santos & Yada, 1988; Bose & Ganguly, 1994), with consequent formation of byproducts such as enstatite ($\text{Mg}_2\text{Si}_2\text{O}_6$), tridimite (SiO_2) and (if higher temperature is reached) cristobalite (SiO_2). If talc had been applied on the unfired ceramics together with crude bone powder prior to firing, the extent of the temperature ($\geq 900^\circ\text{C}$, as inferred from hydroxyapatite calcination) would also have triggered formation of talc derivatives during sintering in furnace. No trace of enstatite and tridimite, however, was ever detected by XRPD in any of the analyzed specimens, implying that these talc-containing inlays (alone or mixed to bone ash) were applied only after firing. Analogous considerations were recently suggested also by Iordanidis and Garcia-Guinea (2011) studying ancient potsherds (XVI to III century BC) from Northern Greece.

Firing of the ceramic implements ($750 < T < 900^\circ\text{C}$) for the current study must therefore be considered a process distinct from bone calcination ($T \geq 900^\circ\text{C}$), aimed exclusively to preparation of bone ashes: such a material was applied – possibly together with talc – only on the already fired pottery. This assumption is also empirically supported by the fact that the material grinding of fresh bones to prepare crude bone powder is a very tough task (the Authors personally experienced this while preparing freshly-synthesized Bone White pigment for comparative purposes; see § 2.2), but it becomes considerably easier once the bone is calcined. One can guess it was quite inconvenient for our ancestors to keep on crushing crude bones for the resulting powders (made into a paste) to be burned on the uncooked implements, after

680 realizing that the same results could be obtained with a considerably minor effort just by
681 keeping the two processes (pottery firing and bone calcination) separated and applying bone
682 ashes on the already fired ceramics.

683 A third natural pigment seldom used to produce these white inlays is kaolinite [$\text{Al}_2\text{Si}_2\text{O}_5(\text{OH})_4$],
684 a soft earthy phyllosicate produced by the chemical weathering of Al-silicates such as
685 feldspars. Possible use of kaolinite as a pigment or extender on prehistoric pottery, though
686 infrequent, is not unknown (Sziki et al., 2003; Hradil et al., 2003; Katsaros et al., 2009). In
687 ceramics from Piedmont, presence of kaolinite can be exclusive (Giustetto, 2008) or more
688 frequently mixed in subordinate quantities together with talc and bone ash (i.e. CdA13) or
689 calcite (CdA27). The role of kaolinite as a basic ingredient of the ceramic *impasto* is unrelated
690 to its use as a white pigment, because this mineral undergoes a complete phase transformation
691 during heating. Therefore sporadic detection of kaolinite further supports the above mentioned
692 assumption according to which such inlays were realized for aesthetic purposes only after
693 ceramics firing: application prior to firing would in fact cause such a phase to disappear.
694 Presence of calcite was also episodically observed (i.e CdA27 and CdA51). Use of this
695 carbonate phase as a Neolithic pigment, possibly associated to other colorizing agents, was
696 seldom reported (Mioč et al., 2004) and its incidental detection would apparently further
697 support the perspective of these ornaments being applied after ceramics firing (at $T \geq 800^\circ\text{C}$ de-
698 carbonation would cause disappearance of calcite-based pigments applied prior to firing). Its
699 sporadic recurrence, however, suggests that presence of calcite is probably related to post-
700 burial, secondary depositional processes (Constantinescu et al., 2007; Bugoi et al., 2008) rather
701 than purpose addition by prehistoric artists.

702 Though a fascinating perspective, infrequent detection of hydrocerussite (in addition to talc,
703 hydroxyapatite and/or calcite; Fig. 9.b) is unlikely to be related to use of Lead White. This
704 pigment, in fact, was first produced in ancient Greece as early as 400 BC or even before
705 (Rossotti, 1983), but its use has never been reported so far in Northern Italy in prehistory.

Detection of hydrocerussite on the Iron Age fibula ornament (CdA67) can be possibly related to corrosion of the bronze surface, due to exposure to degrading/bleaching agents (i.e. rain, groundwaters, soil components, etc.), with consequent formation of Pb corrosion byproducts such as lead carbonates (Selwyn et al., 1996; Balassone et al., 2009). Usually high CO₂ contents favor formation of hydrocerussite (Turgoose, 1985) whereas cerussite forms at low pH (Graedel, 1994). Presence of hydrocerussite in the CdA83 specimen, on the other hand, is dubious.

The unique red inlay found on the ceramic shard from Chiomonte (Ch1) shows presence of red ochre (hematite; Fe₂O₃) together with traces of talc and bone ash. A mixture of several components was therefore used to realize such an ornament, which is consistent with previous studies (Judson, 1959; Mioč et al., 2004; Constantinescu et al., 2007; Bugoi et al., 2008; Iordanidis and Garcia-Guinea, 2011). The scarce purity of the red ochre (contamination from Si, Al and Ca-bearing minerals: Bikiaris *et al.* 1999) is known to prevent sometimes the identification with conventional methods. The detection of a spinel-like mineral, besides, certifies possible Fe³⁺ stabilization due to incorporation in a stable hosting phase (Bondioli et al., 1998; Garcìa et al., 2003), thus explaining the low intensity of hematite XRD reflections.

Possible sources for red ochre in Piedmont and surrounding areas are Almesè (TO), Apt Ochre Basin (Provence, France), Baio (TO), Brosso (TO), Carouge (France), Germagnano (TO), La Thuile (AO), Maggiore (NO), Orta (NO) ('lands of the Vercelli and Novara high plains'), Quart (AO), Schieranco (VB), St. Julien (France), Vico (CN), Villa del Bosco (BI) and Villanova di Mondovì (CN) ('Monregalese land') (Barelli 1835; Scarsella and Natale 1989).

An accurate study of the variably coloured ceramic inlays from Chiomonte (red, brown, black: Bertone and Fozzati 2002) could hopefully help to shed light on the relationships which in Neolithic occurred between these inhabitants and those of transalpine and cisalpine areas.

In some white inlays from Castello di Annone weak IR-active vibrational modes related to proteic material were observed, possibly related to the addition of a binder or vehicle apt to

ensure pigment adhesion to the ceramic body. No certain attribution (i.e. animal fat, resin or egg, in addition to water; Chalmin et al., 2003; Barnett et al., 2006; Williamson, 2000), however, could be attempted. Traces of Paraloid were also observed on some Castelletto Ticino specimens, diagnostic of a recent consolidation process.

In those ornaments marked by an exclusive/predominant use of bone ashes, a careful analysis of XRPD data suggests possible presence of a further phosphate in addition to hydroxyapatite/carbonate-hydroxyapatite, namely fluorapatite $[\text{Ca}_5(\text{PO}_4)_3\text{F}]$ or francolite $[(\text{Ca},\text{Mg},\text{Sr},\text{Na})_{10}(\text{PO}_4,\text{SO}_4,\text{CO}_3)_6\text{F}_{2-3}]$, a fluorine rich phosphate or phosphate-carbonate phase respectively (i.e. Castello di Annone and Fossano, Figures 5.c and 7.b respectively, magnifications). It is known from literature that hydroxyapatite can gradually transform into fluorapatite (Hagen, 1973; Wei et al., 2003) due to selective OH^-/F^- vicariance, a process which affects the diagenesis of bone remains submersed in sea waters (Nemliher et al., 2003) or interred in soils permeated by F^- -rich aqueous solutions (Wier et al., 1972; Reiche, 2006; Stathopoulou et al., 2008). The OH^-/F^- substitution rate strictly depends from the geo-chemistry of the interring soil and rock substratum and is influenced by F^- concentration on local basis. This substitution plays a fundamental role in the dating of buried bone remains with the so called Fluorine Dating Method (Carnot, 1893; Middleton, 1845; Cook and Ezra-Cohn, 1959; McConnel, 1962; Johnsson, 1997; Goffer, 2007; Gaschen et al., 2008; Goodrum and Olson, 2009).

The observed potential splitting of the hydroxyapatite reflections at high 2θ values in the XRPD patterns, however, is also possibly biased by the non-elimination of the $\text{Cu-K}\alpha_2$ wavelength, thus causing detection/quantification of any F^- -substituted phosphate phase to be unreliable. In order to possibly detect actual presence of fluorapatite in these white inlays – and evaluate the feasible setting of an alternative dating method for these implements – pristine bone ash grains were scraped from the CdA3 and CdA5 specimens and analyzed with SEM-EDS. The obtained results, despite their semi-quantitative reliability (being collected on

unpolished specimens), show that the averaged chemical composition of these samples (see Supplementary Material, Table S3) is consistent with an almost pure hydroxyapatite; no fluorine was detected. All measured weight% Ca/P ratios (see Supplementary Material, Table S4) fall in the range between 2.12 and 2.31 (average: 2.21), further confirming the biogenic origin of this pigment (Shiegl et al., 2003). These evidences disprove any measurable evidence about actual presence of fluorapatite in bone ashes, unless more sensitive approaches are adopted (i.e. PIGE or PIGME; Quattropiani et al., 1999). Moreover, the absence of an appreciable fluorapatite content in these Bone White inlays is consistent with the geochemistry of the fluorine-poor Piedmont subsoil, which does not favour subterranean circulation of F-rich groundwaters.

5. **Conclusions**

A detailed archaeometric study was performed, aimed towards the characterization of white inlays filling incisions and/or impressions on prehistoric pottery coming from the archaeological site of Castello di Annone (Piedmont, Italy), dating from the Neolithic to the Iron age.

The collected evidences show that a restricted number of white pigments was used, namely natural talc and synthetic Bone White, with the sporadic addition of other minor components (i.e. kaolinite). Talc, whose recurrence is predominant in almost all analyzed specimens, could be found as pristine mineral or rather derived from direct crushing of steatite (soapstone rock). As a pigment, it could be used alone or (more frequently) mixed with subordinate or equal amounts of bone ash.

Significant archaeometric considerations can be extrapolated from a pilot study which compares the outcomes from Castello di Annone with those collected on analogously decorated

pottery coming from other almost coeval sites of Piedmont (Chiomonte, Fossano and Castelletto sopra Ticino). In spite of its limited statistics, this approach shows that in the more ancient Castello di Annone settlement use of talc (black columns in Fig. 9.b) apparently prevails, though frequently coupled to subordinate or equal quantities of bone ash (which episodically becomes exclusive: Bone White). Use of calcined biogenic hydroxyapatite (white columns in Fig. 9.b), on the other hand, appears to be predominant in the more recent Iron Age sites (Fossano and Castelletto sopra Ticino). It is convenient to suppose that in Castello di Annone the adopted decorating techniques underwent no significant development from the Neolithic to the Bronze Age. The procedure leading to preparation of synthetic Bone White, though already experimented, was probably yet to be adequately mastered. Lack of this technological skill possibly caused diffusion of talc to prevail, for which mere crushing and addition to a binder are required. In the close Fossano and Castelletto sopra Ticino settlements, on the other hand, skilled craftsmen possibly managed, during the Iron Age, to set up a convenient procedure for the production of Bone White, thus realizing the sheer advantages granted by such a pigment in terms of artistic yield and gradually supplanting use of talc. The performed analyses could not establish whether contextual presence of talc and bone ash in mixture could result from a single application or rather multiple coatings of different pigments in separate moments, aimed to 'refresh' or 'restore' faded ornaments. The latter hypothesis, if founded, may explain the episodic presence of significant quantities of calcined biogenic hydroxyapatite on the more ancient Neolithic artefacts. Absence of talc degradation by-products, however, suggests that these white inlays were applied only after firing of the ceramics in furnace, a process distinct and independent from calcination aimed to bone ash synthesis ($T \geq 900^{\circ}\text{C}$).

Lack of an appreciable fluorapatite/hydroxyapatite substitution in pure Bone White-manufactured ornaments causes the Fluorine Dating Method to be inapplicable. Analysis of analogous coeval potteries interred in different geographic contexts, with soils permeated by

fluorine-rich groundwaters (similar white inlays were recently described in Syria by Fornacelli and Memmi, 2012), might cause such an attempt to be worth trying.

The adopted analytical approach seldom detected traces of a protein binder used to favour adhesion of the pigments to the ceramics, but no sharp attribution could be attempted and an alternative protocol should therefore be pursued. Together with such a goal, future perspectives are directed towards extending the archaeometric survey to other coeval anthropic settlements, in order to enlarge the statistical basis and further support the proposed outcomes.

Acknowledgements

The authors wish to thank Marica Venturino Gambari of the Soprintendenza per i Beni Archeologici del Piemonte and Filippo Maria Gambari, Soprintendente per i Beni Archeologici della Liguria e dell'Emilia Romagna, for kindly providing the materials and their invaluable support.

We also thank Stefania Padovan, Tommaso Poli, Angelo Carlone, Fabio Gernetti and Filippo Rubat-Borel for their precious help and advices in the archaeological description of the studied materials.

We respectfully thank the reviewers of this paper (anonymous) because with their precious advices and suggestions significantly helped to improve both the archaeological and scientific quality of the manuscript.

Special thanks go to Francesca Silenzi and Susanna Valfré for their contribution in collecting and commenting XRPD data.

References

- Babot, M.P., Apella, M.C., 2003. Maize and bone: residues of grinding in North-Western Argentina. *Archaeometry* 45, 121-132.
- Baird, D., 1991. Independent variables? A flexible classification of Late Neolithic and Chalcolithic pottery. In: Barlow J.A., Bolger D.L., Kling B. (Eds.), *Cypriot ceramics, reading the prehistoric record.*, Philadelphia.
- Barelli, V., 1835. *Cenni di Statistica Mineralogica degli Stati di S.M. Il Re di Sardegna, ovvero Catalogo Ragionato della raccolta formata presso l'Azienda Generale dell'Interno.* Tipografia di Giuseppe Fodratti, Torino.
- Barnett, J.R., Miller, S., Pearce, E., 2006. Colour and art: a brief history of pigments. *Opt. Laser Technol.* 38, 445-453.
- Bartsiokas, A., Middleton, A.P., 1992. Characterization and dating of recent and fossil bone by X-ray diffraction. *Journal of Archaeological Science* 19, 63-72.
- Benedetti, E., D'alessio, A., Zini, M.F., Bramanti, E., Tirelli, N., Vergatini, P., Moggi, G., 2000. Characterization of acrylic resins and fluoroelastomer blends as potential materials in stone protection. *Polymer International* 49, 888-892.
- Bertone, A., Carrara, F., Fedele, F., Fozzati, L., Perotto, A., 1986. *Archeologia preistorica dell'alta Valle di Susa: Chiomonte-La Maddalena.* In: Tipolito Melli snc, (Ed.), Segusium. Susa.
- Bertone, A., Fozzati, L. 2002. *Seimila anni di storia sulle Alpi occidentali.* La Maddalena di Chiomonte, Torino.
- Bikiaris, D., Daniilia, S., Sotiropoulou, S., Katsimbiri, O., Pavlidou, E., Moutsatsou, A.P., Chrysoulakis, Y., 1999. Ochre-differentiation through micro-Raman and micro-FTIR spectroscopies: application on wall paintings at Meteora and Mount Athos, Greece. *Spectrochimica Acta Part A*, 56, 3-18.
- Blasco, C., 1994. El horizonte campaniforme de la region de Madrid en el centenario de Ciempozuelos. *Universidad Autónoma de Madrid, Madrid.*
- Bondioli, F., Ferrari, A.M., Leonelli, C., Manfredini, T., 1998. Syntheses of Fe₂O₃/silica red inorganic inclusion pigments for ceramic applications. *Mater. Res. Bull.* 33, 723-729.
- Bonucci, E., Graziani, G., 1975. Comparative thermogravimetric X-ray diffraction and electron microscope investigations of burnt bones from recent, ancient and prehistoric age. *Atti dell'Accademia Nazionale dei Lincei, Rendiconti, Classe di Scienze Fisiche, Matematiche e Naturali* 59, 517-532.
- Bose, K., Ganguly, J., 1994. Thermogravimetric study of the dehydration kinetics of talc. *American Mineralogist* 79, 692-699.
- Bugoi, R., Constantinescu, B., Pantos, E., Popovici, D., 2008. Investigation of Neolithic ceramic pigments using synchrotron radiation X-ray diffraction. *Powder Diffraction* 23, 195-199.
- Campbell, P.J., 1989. The geometry of decoration on prehistoric pueblo pottery from starkweather ruin. *Computer & Mathematics with Applications* 17, 731-749.
- Carnot, A., 1893. *Recherches sur la composition générale et la teneur en fluor des os modernes et des os fossils de différent âges.* Annales de Mines, Memoires, Paris 9(3), 155-195.
- Chairkina, N.M., Kosinskaia, L.L., 2009. Early hunter-gatherer ceramics in the Urals and Western Siberia. In: Jordan P. and Zvelebil M. (Eds.), *Ceramics before farming, the dispersal of pottery among prehistoric Eurasian hunter-gatherers.* Left Coast Press, Walnut Creek, CA, 209-235.
- Chalmin, E., Menu, M., Vignaud, C., 2003. Analysis of rock art painting and technology of Paleolithic painters. *Meas. Sci. Technol.* 14, 1590-1597.
- Constantinescu, B., Bugoi, R., Pantos, E., Popovici, D., 2007. Phase and chemical composition analysis of pigments used in Cucuteni Neolithic painted ceramics. *Documenta Praehistorica* 34, 281-288.

899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960

Cook, S.F., Ezra-Cohn, H.C., 1959. An evaluation of the fluorine dating method. *Southwestern Journal of Anthropology* 15(3), 276-290.

Covertini, F., 1996. Production et signification de la céramique campaniforme à la fin du 3ème millénaire av.J.C. dans le Sud et le Centre Ouest de la France et en Suisse occidentale. *BAR International Series* 656, Oxford.

Curtis, N., Popovic, L., Wilkin, N., 2010. The moon, the bonfire and the beaker? Analyzing white inlay from beaker pottery in Aberdeenshire. *Past, the newsletter of the prehistoric society* 65, 1-3.

Dauphin, Y., 1993. Potential of the Infrared Fourier Transform (DRIFT) method in paleontological studies of bone. *Applied Spectroscopy* 47, 52-55.

De Hostos, A., 1919. Prehistoric Porto Rican ceramics. *American Anthropologist* 21, 376-399.

De Marinis, R.C., 1982. La ceramica della prima tomba di guerriero di Sesto Calende e nuove osservazioni sulla cronologia del Golasecca I. *Rivista di Archeologia dell'antica provincia e Diocesi di Como* 163, 5-48.

De Marinis, R.C., 1991. I Celti golasecchiani. *I Celti, Catalogo della Mostra di Palazzo Grassi, Milano*, 93-102.

Derrick, M.R., Stulik, D., Landry, J.M., 1999. *Infrared Spectroscopy in Conservation Science*. The Getty Conservation Institute, Los Angeles.

De Souza Santos, H., Yada, K., 1988. Thermal transformation of talc as studied by electron-optical methods. *Clays and Clay Minerals* 36(4), 289-297.

Diffra Plus Evaluation Package, 2005. Copyright © SOCABIM 1996-2005.

Edmunds, M., Smedley, P., 2005. Fluoride in mineral waters. In: *Essentials of medical geology: impacts of the natural environment on public health*, Ed. Elsevier Academic Press, London.

Farmer, V.C., 1974. *The infrared spectra of minerals*, Mineralogical Society Monograph 4, London.

Fornacelli, C, Memmi, I., 2012. Studio archeometrico di un repertorio di ceramiche provenienti dal sito archeologico di Tell Barri (Siria). *Riunione Annuale GABeC, Roma* 21 settembre 2012.

Fowler, B.O., 1974. Infrared studies of apatites. *Inorganic Chemistry* 13, 194-207.

Gambari, F.M., 1988. Gli insediamenti e la dinamica del popolamento nell'età del Bronzo e nell'età del Ferro. In: *Venturino Gambari M., Mercado L. (Eds.), Archeologia in Piemonte, la preistoria (I)*, Torino.

Gambari, F.M., 2004. L'etnogenesi dei Liguri cisalpini tra l'età del Bronzo finale e la prima età del Ferro. *Ligures celeberrimi. La Liguria interna nella seconda età del Ferro, Atti del convegno, Mondovì, 26-28 aprile 2002* (Venturino Gambari, M., Gandolfi, D.), Bordighera 2004, 11-28.

Gambari, F.M., Cerri, R., 2009. *Guida a L'alba della città. Le prime necropoli del centro protourbano di Castelletto Ticino*, Interlinea edizioni, Novara.

Garcia, A., Llusar, M., Sorli, S., Calbo, J., Tena, M.A., Monròs, G., 2003. Effect of the surfactant and precipitant on the synthesis of pink coral by a microemulsion method. *Journal of the European Ceramic Society* 23, 1829-1838.

Gaschen, A.A.-M, Döbeli, M., Markwitz, A., Barry, B., Ulrich-Bochsler, S., Krähenbühl, U., 2008. Restrictions on fluorine depth profiling for exposure age dating in archaeological bones. *Journal of Archaeological Science* 35, 535-552.

Gibson, A.M., Woods, A., 1997. In: *Prehistoric pottery for the archaeologist*. Ed. Leicester University press, London.

Gibson, A.M., 2002. In: *Prehistoric pottery in Britain & Ireland*. Ed.: Stroud & Charleston (SC),Tempus Publishing Ltd.

Gibson, A.M., 2006. In: *Prehistoric pottery: some recent research*. Ed.: Oxford Archaeopress.

Giustetto, R., 2008. Analisi dei componenti su frammenti ceramici. In: *Taurini sul confine*, Ed. Celid, Torino.

961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022

Goffer, Z., 2007. The fluoridation of bone. In: *Archaeological Chemistry – 2nd Edition*. Ed. Wiley & Sons, New Jersey.

Goodrum, M.R., Olson, C., 2009. The quest for an absolute chronology in human prehistory: anthropologists, chemists and the fluorine dating method in palaeoanthropology. *The British Journal for the History of Science* 42, 95-114.

Graedel, T.E., 1994. Chemical mechanisms for the atmospheric corrosion of lead. *J. Electrochemical Society* 141, 922-927.

Grupe, G., Hummel, S., 1991. Trace element studies on experimentally cremated bone. I. Alteration of chemical composition at high temperatures. *Journal of Archaeological Science* 18, 177-186.

Hagen, A.R., 1973. Studies on fluorapatite: 1. Chemical characterization and exchange properties. *Calcified Tissue International* 13, 259-270.

Hagstrum, M.B., 1985. Measuring prehistoric ceramic craft specialization: a test case in the American Southwest. *Journal of Field Archaeology* 12, 65-75.

Herliansyah, M.K., Hamdi, M., Ide-Ektessabi, A., Wildan, M.W., Toque, J.A., 2009. The influence of sintering temperature on the properties of compacted bovine hydroxyapatite. *Materials Science and Engineering C* 29, 1674-1680.

Hradil, D., Grygar, T., Hradilová, J., Bezdička, P., 2003. Clay and iron oxide pigments in the history of painting. *Applied Clay Science* 22, 223-236.

Iordanidis, A., Garcia-Guinea, J., 2011. A preliminary investigation of black, brown and red coloured potsherds from ancient upper Macedonia, Northern Greece. *Mediterranean Archaeology and Archaeometry* 11, 85-97.

Jernigan, E.W., 1986. A non-hierarchical approach to ceramic decoration analysis: a southwestern example. *American Antiquity* 51(1), 3-20.

Johnsson, K., 1997. Chemical dating of bones based on diagenetic changes in bone apatite. *Journal of Archaeological Science* 24, 431-437.

Judson, S., 1959. Palaeolithic paint. *Science* 130, 708.

Katsaros, T., Liritzis, I., Laskaris, N., 2009. Is white pigment on Appelle's palette a TiO₂-rich kaolin? New analytical results on the case of Melian-earth. *Mediterranean Archaeology and Archaeometry* 9, 29-35.

Koutsopoulos, S., 1991. Synthesis and characterization of hydroxyapatite crystals: a review on the analytical methods. *Journal of Biomedical Research* 62, 600-612.

Kruta, V., 2003. *La grande storia dei Celti. La nascita, l'affermazione, la decadenza*. Ed. Newton & Compton, Roma.

Kruta, V., 2004. *I Celti e il Mediterraneo*. Jaca Book/WIDE, Milano.

Laing, L., 2003. In: *Pottery in Britain 4000 BC to 1900 AD: a guide to identifying potsherds*. Ed.: Greg Payne, Greenlight publishing.

Li, T., Xie, Y., Yang, Y., Wang, C., Fang, X., Shi, J., He, Q., 2009. Pigment identification and decoration analysis of a 5th century Chinese lacquer painting screen: a micro-Raman and FTIR study. *Journal of Raman spectroscopy* 40, 1911-1918.

Martín, R., Delibes, G., 1989. La cultura del vaso campaniforme en las campinas meridionales del Duero: el enterramiento de Fuente-Olmedo. *Junta de Castilla y León, Valladolid*.

McConnel, D., 1962. Dating of fossil bones by the Fluorine Method: fluorine analysis by indirect methods is not a reliable means of determining age. *Science* 136, 241-244.

Middleton, J., 1844. On fluorine in bones: its sources and its application to the determination of the geological age of fossil bones. *Proceedings, Geological Society of London* 4, 431-433.

- Mioč, U.B., Colomban, P., Sagon, G., Stojanovic, M., Roric, A., 2004. Ochre decor and cinnabar residues in Neolithic pottery from Vinča, Serbia. *Journal of Raman Spectroscopy* 32, 843-846.
- Mohammed-Ali, A.S., Khabir, A.M., 2003. The wavy line and the dotted wavy line pottery in the prehistory of the central Nile and the Sahara-Sahel belt. *African Archaeological Review* 20, 25-58.
- Morzadec, H., 1995. *Péto-archaeologie des céramiques armoricaines du Néolithique à la fin de l'Age du Fer*. Travaux du laboratoire d'anthropologie de Rennes, Université de Rennes, Rennes.
- Nemliher, J.G., Baturin, G.N., Kallaste, T.E., Murdmaa, I.O., 2004. Transformation of hydroxyapatite of bone phosphate from the ocean bottom during fossilization. *Lithology and Mineral Resources* 39, 468-479.
- Nielsen-Marsh, C.M., 2000. Patterns of diagenesis in bone I: the effects of site environments. *Journal of Archaeological Science* 27, 1139-1150.
- Noll, W., Holm, R., Born, L., 1975. Painting of ancient ceramics. *Angewandte Chemie* 14, 602-613.
- Odriozola C.P., Hurtado Pérez V.M., 2007. The manufacturing process of 3rd millennium BC bone based incrustated pottery decoration from the Middle Guadiana river basin (Badajoz, Spain). *Journal of Archaeological Science* 34(11), 1794-1803.
- Odriozola, C.P., Martínez-Blanes, J.M., 2007. Estimate of firing temperatures through bone-based chalcolithic decorated pottery. *Journal of Thermal Analysis and Calorimetry* 87, 135-141.
- Padovan, S., 2005. Castello di Annone (scavi 1994-1995). I materiali di tradizione occidentale. In: *Preistoria dell'Italia Settentrionale: Studi in ricordo di Bernardino Bagolini*, Atti del Convegno, Edizioni del Museo Friulano di Storia Naturale, Udine.
- Padovan, S., Thirault, E., 2007. Chiomonte e Sollières. Pionieri delle Alpi dal Neolitico alle invasioni galliche. *Pionniers des Alpes du Néolithique aux invasions gauloises*, Ed. Nautilus, Torino.
- Parkinson, W.A., Peacock, E., Palmer, R.A., Xia, Y., Carlock, B., Gyucha, A., Yerkes, R.W., Galaty, M.L., 2010. Elemental analysis of ceramic incrustation indicates long-term cultural continuity in the prehistoric Carpathian basin. *Archaeology Ethnology & Anthropology of Eurasia* 38/2, 64-70.
- Person, A., Bocherens, H., Saliège, J.F., Paris, F., Zeitoun, V., Gérard, M., 1995. Early diagenetic evolution of bone phosphate : an X-ray diffractometry analysis. *Journal of Archaeological Science* 22, 211-221.
- Pesonen, P., Leskinen, S., 2009. Pottery of the Stone Age hunter-gatherers in Finland. In: Jordan P. and Zvelebil M. (Eds.), *Ceramics before farming, the dispersal of pottery among prehistoric Eurasian hunter-gatherers*. Left Coast Press, Walnut Creek, CA.
- Piga, G., Malgosa, A., Thompson, T.J.U., Enzo, S., 2008. A new calibration of the XRD technique for the study of archaeological burned human remains. *Journal of Archaeological Science* 35, 2171-2178.
- Pleshko, N., Boskey, A., Mendelsohn, R., 1991. Novel infrared spectroscopic method for the determination of crystallinity of hydroxyapatite minerals. *Biophysical Journal, Biophysical Society* 60, 786-793.
- Plog, S., 1980. In: *Stylistic variation in prehistoric ceramics – Design analysis in the American Southwest*. Ed. Cambridge University Press, Cambridge.
- Prieto-Martínez, M.P., Cobas-Fernández, I., Criado-Boado, F., 2003. Patterns of spatial regularity in late prehistoric material culture styles of the NW Iberian peninsula. In: Gibson A. (Ed.), *Prehistoric pottery, people, pattern and purpose*, Oxford.
- Quattropiani, L., Charlet, L., de Lumley, H., Menu, M., 1999. Early Palaeolithic bone diagenesis in the Arago cave at Tautavel, France. *Mineralogical Magazine*, 63(6), 801-812.
- Reiche, I., 2006. Chapter 8: fluorine and its relevance for archaeological studies. In: *Advances in Fluorine Science*, 2, 253-283.

- Roberts, S.J., Smith, C.I., Millard, A., Collins, M.J., 2002. The taphonomy of cooked bone: characterizing boiling and its physic-chemical effects. *Archaeometry* 44, 485-494.
- Roberts, S., Sofaer, J., Kiss, V., 2007. Characterization and textural analysis of Middle Bronze Age Transdanubian inlaid wares of the encrusted pottery culture, Hungary: a preliminary study. *Journal of Archaeological Science*, 35, 322-330.
- Rogers, K.D., Daniels, P., 2002. An X-ray diffraction study of the effects of heat treatment on bone mineral microstructure. *Biomaterials* 23, 2577-2585.
- Rossotti, H., 1983. In: *Colour: Why the World Isn't Grey*. Ed.: Princeton, NJ: Princeton University Press.
- Rychner-Faraggi, A.M., Wolf, S., 2001. Cendre d'os et céramiques hallstattiennes à Onnens (Vaud) – Le Motti. *Annuaire de la Société Suisse de Préhistoire et d'Archéologie* 84, 171-176.
- Salanova, L., 2000. La question du campaniforme en France et dans les îles anglo-normandes. Production et rôles d'un standard céramique. CTHS: Société préhistorique française, Paris.
- Salzani, P., 2005. Castello di Annone (scavi 1994-1995). I materiali della Cultura dei Vasi a Bocca Quadrata. *Preistoria dell'Italia Settentrionale: Studi in ricordo di Bernardino Bagolini, Atti del Convegno, Edizioni del Museo Friulano di Storia Naturale, Udine*, 501-508.
- Scarsella, P., Natale, P., 1989. Terre coloranti naturali e tinte murali a base di terre. *Stamperia Artistica Nazionale, Torino*.
- Shiegl, S., Goldberg, P., Preftzschner, H.A., Conard, N.J., 2003. Palaeolithic burnt bone horizons from the Swabian Jura: distinguishing between *in situ* fireplaces and dumping areas. *Geoarchaeology* 18, 541-565.
- Selwyn, L.S., Binnie, N.E., Poitras, J., Laver, M.E., Downham, D.A., 1996. Outdoor bronze statues: analysis of metal and surface samples. *Studies in Conservation* 41, 205-228.
- Shipman, P., Foster, G., Schoeninger, M., 1984. Burnt bones and teeth: an experimental study of color, morphology, crystal structure and shrinkage. *Journal of Archaeological Science* 11, 307-325.
- Silva, C.C., Sombra, A.S.B., 2004. Raman spectroscopy measurements of hydroxyapatite obtained by mechanical alloying. *Journal of Physics and Chemistry of Solids* 65, 1031-1033.
- Smith, B., 1999. *Infrared spectral interpretation: a systematic approach*. CRC Press, Boca Ratón, 171-172.
- Smith, R., Rehman, I., 1995. Fourier transform Raman spectroscopic studies of human bone. *Journal of Material Science: Materials in Medicine* 5, 775-778.
- Stathopoulou, E.T., Psycharis, V., Chryssikos, G.D., Gionis, V., Theodorou, G., 2008. Bone diagenesis: new data from infrared spectroscopy and X-ray diffraction. *Palaeogeography, Palaeoclimatology, Palaeoecology* 266, 168-174.
- Striova, J., Lofrumento, C., Zoppi, A., Castellucci, E.M., 2006. Prehistoric Anasazi ceramics studied by micro-Raman spectroscopy. *Journal of Raman Spectroscopy* 37, 1139-1145.
- Surovell, T.A., Stiner, M.C., 2001. Standardizing infra-red measures of bone mineral cristallinity: an experimental approach. *Journal of Archaeological Science* 28, 633-642.
- Swann, C.P., Ferrence, S., Betancourt, P.P., 2000. Analysis of Minoan white pigments used on pottery from Palaikastro. *Nucl. Instr. And Meth. In Phys. Res. - sec. B: Beam Interactions with Materials and Atoms* 161-163, 714-717.
- Sziki, G.A., Birò, K.T., Uzonyi, I., Dobos, E., Kiss, A.Z., 2003. Investigation of incrustated pottery found in the territory of Hungary by micro-PIXE method. *Nuclear Instruments and Methods in Physics Research B* 210, 478-482.
- Tiné, S., 1988. Il Neolitico tra Liguria e Piemonte. In: Gambari M., Mercado L. (Eds.), *Archeologia in Piemonte, la Preistoria*, I, Torino.
- Topping, P.G., 1987. Typology and chronology in the later prehistoric pottery assemblages of the Western Isles. *Proc. Soc. Antiq. Scotland* 117, 67-84.

- Herliansyah, M.K., Hamdi, M., Ide-Ektessabi, A., Wildan, M.W., Tocque, J.A., 2009. The influence of sintering temperature on the properties of compacted bovine hydroxyapatite. *Materials Science and Engineering C* 29, 1674-1680.
- Turgoose, S., 1985. The corrosion of lead and tin: before and after excavation. In: Miles G. and Pollard S. (Eds.), *Lead and Tin: Studies in Conservation and Technology*. UK, Institute for Conservation, London.
- Venturino Gambari, M., 1998. Il Neolitico e l'Eneolitico in Piemonte, *Atti della XXXII Riunione Scientifica. Preistoria e Protostoria del Piemonte*, Istituto Italiano di Preistoria e Protostoria, Firenze, 33-64.
- Venturino Gambari, M., Micheletto, E., Davite, C., 1996. Fossano, centro storico. Insediamenti preistorici e fasi dell'abitato medievale. *Quaderni della Soprintendenza Archeologica del Piemonte* 14, 235-237.
- Venturino Gambari, M., Zamagni, B., 1996. Castello di Annone. In: Omega (Ed.), *Le vie della pietra verde*, Torino.
- Venturino Gambari, M., 2004. Dalla pietra al metallo. Il Neolitico e l'Età del Rame nelle valli Curone, Grue e Ossona. In: Omega (Ed.), *Alla conquista dell'Appennino. Le prime comunità delle valli Curone, Grue e Ossona*, Torino.
- Wei, M., Evans, J.H., Bostrom, T., Grøndal, L., 2003. Synthesis and characterization of hydroxyapatite, fluoride-substituted hydroxyapatite and fluorapatite. *Journal of Materials Science: Materials in Medicine* 14, 311-320.
- Wesolowski, M., 1984. Thermal decomposition of talc: a review. *Thermochimica Acta* 78, 395-421.
- Wilkins, R.W.T., Ito, J., 1967. Infrared spectra of some synthetic talcs. *American mineralogist* 52, 1649-1661.
- Wier, D.R., Chien, S.H., Black, C.A., 1972. Transformation of hydroxyapatite to fluorapatite. *Soil Scientific Society of America Proceedings* 36(2), 285-288.
- Williamson, B.S., 2000. Direct testing of rock painting pigments for traces of haemoglobin at Rose Cottage Cave, South Africa. *Journal of Archaeological Science* 27, 755-762.
- Zaichicka, V., Tzaphlidou, M., 2002. Determination of calcium, phosphorus, and the calcium/phosphorus ratio in cortical bone from the human femoral neck by neutron activation analysis. *Applied Radiation and Isotopes* 5, 781-786.

1203 **Table Captions**

1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254

- Table 1: Quantitative amounts (expressed as wt%) of talc and hydroxyapatite in the decorating white mixtures found on the Castello di Annone specimens, as inferred by XRPD analyses.
- Table 2: Quantitative amounts (expressed as wt%) of talc and hydroxyapatite in the decorating white mixtures found on the Fossano and Castelletto sopra Ticino specimens, as inferred by XRPD analyses.

Figure Captions

Figure 1. Schematic map of Northern Italy (upper left corner) and physical map of Piedmont bearing indication of the Castello di Annone (AT) prehistoric settlement and the other coeval archaeological sites investigated for comparative purposes [1: Chiomonte (TO); 2: Fossano (CN); 3: Castelletto sopra Ticino (NO)].

Figure 2. Ceramic shards bearing incisions or impressions filled with white inlays from the archaeological site of Castello di Annone (AT), dating to the Neolithic (a), Copper (b) and Bronze age (c). Fragment of a bronze fibula decorated with a white inlay from the same site, dating to the Iron age (d). (Dimensional scale: cm)

Figure 3. Ceramic shards and implements bearing incisions or impressions filled with white or coloured inlays from the archaeological sites of Chiomonte (red-decorated shard) (a), Fossano (b) and Castelletto sopra Ticino (c). (Dimensional scale: cm)

Figure 4. FT-IR spectra of samples CdA11 (talc) and CdA5 (Bone White).

Figure 5. XRPD patterns of exclusively talc-based (dashed lines: CdA1, CdA7, CdA23, CdA37) (a), both talc and hydroxyapatite-based (dashed and dotted lines respectively: CdA9, CdA11, CdA23, CdA85) (b) and exclusively hydroxyapatite-based (dotted lines: CdA3 and CdA5) (c) white inlay specimens from Castello di Annone. Magnification in the (c) upper right corner shows the possible presence of diffraction peaks related to fluorapatite.

Figure 6. FT-IR spectrum of sample Ch1.

Figure 7. FT-IR spectrum of sample F1 (analogous to F3, F5 and F7) (a); XRPD patterns of hydroxyapatite-based (dotted lines) white inlay specimens (F1, F3, F5 and F7) from Fossano; magnification (upper right corner) shows the possible presence of diffraction peaks related to fluorapatite (b).

Figure 8. FT-IR spectrum of sample CT3 (analogous to CT1, CT5, CT7, CT9 and CT11) (a); XRPD patterns of predominant hydroxyapatite (dotted lines) and subordinate talc-based (dashed lines) samples (CT1 and CT7) (b).

Figure 9. Compositional % distribution of the white inlays applied on the 44 analyzed specimens from Castello di Annone; for each fraction, the number of specimens and related % are reported respectively (a). Summarizing histogram concerning the approximate composition of white pigment mixtures (expressed as talc and hydroxyapatite %) for each specimen in the investigated archaeological sites. Sporadic presence of other white components (i.e. calcite, kaolinite and hydrocerussite) is also indicated. Within the same epoch, specimens were ordered from higher to lower talc content. While in Castello di Annone use of talc prevails in all investigated chronological periods, in the more recent Fossano and Castelletto Ticino settlements such a situation is drastically reversed in favour of bone ash (b).

Figure 10. a) Comparison in the 8-70° 2θ region of XRPD patterns collected on fresh pork rib (1), XVI century human rib (2), biogenic hydroxyapatite calcined at 900°C (3) and Iron Age Bone White pigment (F1) from Fossano (4). Calcination causes the diffraction peaks of hydroxyapatite to dramatically reduce their full width at half maximum (FWHM),

consequent to an increase in the cristallinity degree. b) Comparison in the 30-35° 2θ region of the (211), (112) and (300) diffraction peaks of Bone White-based filler inlays (CdA5 and CT1) with the same reflections related to biogenic hydroxyapatite calcined at 900°C (OH-apt), showing similar FWHM and cristallinity degree. c) Consistency of the experimentally collected data with those presented by Odriozola and Martínez-Blanes (2007), typical of biogenic hydroxyapatite heated at 900°C.

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

1375

Figure 7

1376
1377
1378

Figure 8

Figure 9

Figure 10

1405 **Supplementary Material**
1406
1407

1408 Table S1: Chronologic list of all analyzed white inlay specimens from Castello di Annone,
1409 complete with both archaeological and archaeometric descriptions (question marks imply
1410 uncertain attributions).
1411

1412 Table S2: Chronologic list of all analyzed white inlay specimens from other coeval sites of
1413 Piedmont (Chiomonte, Fossano and Castelletto sopra Ticino), complete with both
1414 archaeological and archaeometric descriptions (question marks imply uncertain
1415 attributions).
1416

1417 Table S3: EDS chemical analyses (expressed as weight% of oxides) on individual analytical spots
1418 collected on the CdA3 and CdA 5 Bone White specimens; last column lists the averaged
1419 values.
1420

1421 Table S4: Weight% of Ca and P and related ratio resulting from EDS analyses on the CdA3 and
1422 CdA5 Bone White specimens.
1423
1424
1425

1426

1427 In order to quantify the mutual talc/hydroxyapatite amounts in the studied white inlays on ancient
1428 potteries, control mixtures with measured weight% composition of both phases (from talc 100% –
1429 hydroxyapatite 0% to talc 0% – hydroxyapatite 100%, with a 10% sequential step) were prepared
1430 and analyzed with an automated PW3050/60 PANalytical X’Pert-PRO diffractometer, with θ - θ
1431 setup and an RTMS (real Time Multiple Strip) detector using monochromatized Cu-K α radiation
1432 (Fig. S1). Preferred orientation effects affecting the (00 l) reflections of talc were possibly smoothed
1433 by using a zero-background, Si-monocrystal flat sample holder and suspending the crystallites in a
1434 non-volatile inert solution (amyl acetate + 5% collodion), thus maximizing their statistic
1435 disposition.

Figure S1. XRPD patterns of synthesized control mixtures with composition ranging from talc 0% - hydroxyapatite 100% (low) to talc 100% - hydroxyapatite 0% (high), each separated by a 10% increase/decrease sequential step. Magnifications indicate the intensity variation trend for all talc [(002); (004); (006); (0010)] and hydroxyapatite (211) reflections considered for the construction of calibration curves.

Feasible calibration curves were obtained by computing, in each of the synthesized control mixtures, the intensity ratios for several couples of independent talc/hydroxyapatite reflections [i.e. between the (002), (004), (006) and (0010) reflections of talc – only ones visible in the ancient white inlays XRD data – and the more intense (211) reflection of hydroxyapatite; Fig. S2). Such curves were then applied in reverse on the ancient inlays XRD data so to obtain reliable quantitative estimates of the mutual talc and hydroxyapatite weight % related to each specimen (generalized Reference Intensity Ratio – RIR method). To further minimize bias related to talc preferred orientation, the compositional values were averaged on all four obtained estimates (related to each couple of talc/hydroxyapatite reflections).

Figure S2. Calibration curves obtained by computing, for each control mixture, the intensity ratios and the related interpolation lines between the (002) reflection of talc and the (211) reflection of hydroxyapatite (a); talc (004) and (211) hydroxyapatite (b); talc (006) and (211) hydroxyapatite (c); talc (0010) and (211) hydroxyapatite (d). (logarithmic scale on Y axis).