



UNIVERSITÀ DEGLI STUDI DI TORINO

AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Does cyclic stress and accelerated ageing influence the wear behavior of highly crosslinked polyethylene?

This is the author's manuscript							
Original Citation:							
Availability:							
This version is available http://hdl.handle.net/2318/1557713 since 2016-11-10T17:18:44Z							
Published version:							
DOI:10.1016/j.jmbbm.2016.02.029							
Terms of use:							
Open Access							
Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.							

(Article begins on next page)



UNIVERSITÀ DEGLI STUDI DI TORINO

This is an author version of the contribution:

S. Affatato, J. S. De Mattia, P. Bracco, E. Pavoni, P. Taddei. Does cyclic stress and accelerated ageing influence the wear behavior of highly crosslinked polyethylene?, Journal of the Mechanical Behavior of Biomedical Materials, Volume 59, June 2016, Pages 418-429

> *The definitive version is available at:* http://dx.doi.org/10.1016/j.jmbbm.2016.02.029

DOES CYCLIC STRESS AND ACCELERATED AGEING INFLUENCE THE WEAR BEHAVIOR

OF HIGHLY CROSSLINKED POLYETHYLENE?

Saverio Affatato¹, Jonathan Salvatore De Mattia¹, Pierangiola Bracco², Eleonora Pavoni³, Paola

Taddei³

¹ Laboratorio di Tecnologia Medica, Istituto Ortopedico Rizzoli, Bologna-Italy

² IFM Chemistry Department and NIS-Centre of Excellence, University of Turin Via Giuria 7, 10125
Turin, Italy

³ Dipartimento di Scienze Biomediche e Neuromotorie, Università di Bologna, Via Belmeloro 8/2,

40126, Bologna, Italy

Running title: Accelerated ageing of different PEs

Journal: Journal of The Mechanical Behavior of Biomedical Materials

Corresponding author:

Saverio Affatato Laboratorio di Tecnologia Medica - Istituto Ortopedico Rizzoli Via di Barbiano, 1/10 40136 BOLOGNA, ITALY tel: +39-051-6366864 fax: +39-051-6366863 e-mail: affatato@tecno.ior.it

ccepte

ABSTRACT

First-generation (irradiated and remelted or annealed) and second-generation (irradiated and vitamin E blended or doped) highly crosslinked polyethylenes were introduced in the last decade to solve the problems of wear and osteolysis.

In this study, the influence of the Vitamin-E addition on crosslinked polyethylene (XLPE_VE) was evaluated by comparing the in vitro wear behavior of crosslinked polyethylene (XLPE) versus Vitamin-E blended polyethylene XLPE and conventional ultra-high molecular weight polyethylene (STD_PE) acetabular cups, after accelerated ageing according to ASTM F2003–02 (70.0 \pm 0.1°C, pure oxygen at 5 bar for 14 days). The test was performed using a hip joint simulator run for two millions cycles, under bovine calf serum as lubricant.

Mass loss was found to decrease along the series XLPE_VE > STD_PE > XLPE, although no statistically significant differences were found between the mass losses of the three sets of cups. Micro-Raman spectroscopy was used to investigate at a molecular level the morphology changes induced by wear. The spectroscopic analyses showed that the accelerated ageing determined different wear mechanisms and molecular rearrangements during testing with regards to the changes in both the chain orientation and the distribution of the all-trans sequences within the orthorhombic, amorphous and third phases. The results of the present study showed that the addition of vitamin E was not effective to improve the gravimetric wear of PE after accelerated ageing. However, from a molecular point of view, the XLPE_VE acetabular cups tested after accelerated ageing appeared definitely less damaged than the STD_PE ones and comparable to XLPE samples.

Keywords: Accelerated ageing; Vitamin E; Crosslinked PE; Hip simulator; Raman spectroscopy.

1. INTRODUCTION

It is well established that the oxidative degradation of ultra-high molecular weight polyethylene (UHMWPE) decreases its mechanical properties and represents one of the main causes of its failure [1–3]. Efforts were faithful to improve UHMWPE and to extend the lifetime of orthopaedic implants [4]. Currently, highly crosslinked polyethylene (XLPE) used in total hip arthroplasty (THA), is clinically accepted as the material for acetabular liners articulated with metallic or ceramic femoral heads [1,5]. Annealed or remelted XLPE substantially reduces the residual free radicals, but also crystallinity and mechanical properties of the polymer [1,6,7]. Other strategies were approached to reduce or retard oxidation by adding suitable additives capable of interrupting the oxidation cycle, by decreasing the reactivity of the radical species; thus, stabilizers are compounds added to the polymer in order to slow the oxidation processes and to preserve its chemical, physical and mechanical properties, i.e. to prolong its lifetime [8,9]. Vitamin E seems to be the ideal candidate, being already employed as a natural antioxidant in the physiological processes of the human body [10].

The evolution of in vivo oxidation is complex, depending not only on the type of UHMWPE material, but also on the duration of implantation and the local availability of oxygen in body fluids and/or tissues [11]. To this regard, it is important not only to characterize the actual orthopaedic components from a tribological point of view, but also to expose these components to an accelerated ageing in order to compare their behavior with that observed following long-term exposure to natural ageing during shelf storage and/or in vivo exposure in human patients [11]. Hopefully, a procedure of accelerated ageing should simultaneously reproduce the chemical changes in materials, as well as the depth profiles of these changes, including oxidation [12].

Protocols and standards for accelerated ageing of UHMWPE usually involve heating for 21 days at 80 °C in air or heating for 14 days at 70 °C under 5 bar oxygen [12–15]. However, there are no ageing protocols that have been adequately validated to replicate real-time shelf and in vivo ageing of XLPE or conventional UHMWPE [16,17].

The present study was aimed at investigating the effects of the accelerated ageing on the wear behavior of vitamin E-stabilized XLPE acetabular cups in comparison to standard UHMWPE and remelted XLPE acetabular cups. To this purpose, in a first test, the wear behavior of the three sets of samples was investigated against CoCrMo femoral heads in a hip joint simulator for five million cycles [18]. After the test, the cups underwent an accelerated ageing treatment according to ASTM F2003-02 and subsequently were newly tested in the hip joint simulator for another two million cycles. The wear behavior of the three sets of acetabular cups was evaluated by gravimetric measurements. To gain more insights into the role of vitamin E in the wear mechanism of the aged acetabular cups, the samples were analysed by micro-Raman spectroscopy before the second test (i.e. after accelerated ageing) and after it. This technique proved suitable to investigate at a molecular level the morphology changes (i.e. in crystallinity, phases distribution and chain orientation) induced by wear. Micro-Raman spectroscopy was chosen due to its non destructive character, in view of continuing the tests under more severe conditions (i.e. in presence of third-body wear particles).

2. Materials and methods

The wear behavior of three different batches of polyethylene acetabular cups (28-mm inner × 44-mm outer dimensions; four specimens for each batch) coupled with 28-mm cobalt-chromiummolybdenum (CoCrMo) femoral heads was investigated using a hip joint simulator; three specimens of each test were tested, the fourth was used as control check (see below). All the components (acetabular cups and femoral heads) were produced through the same manufacturing procedures and supplied by the same manufacturer as finished-products. Standard UHMWPE acetabular cups (hereinafter called STD_PE) were machined from polymer bars made of GUR 1020 (Orthoplastics Ltd, Lancashire, UK). Crosslinked acetabular cups (hereinafter called XLPE) were obtained from a cylindrical bar, firstly electron beam-irradiated to 70 kGy, then thermally treated at 135°C, in order to remove free radicals formed during irradiation. After these treatments, the cups were machined to their final shape. Similarly, Vitamin E-containing XLPE acetabular cups (hereinafter called XLPE_VE) were machined from a Vitamin E-blended UHMWPE bar (0.1% w/w; Orthoplastics Ltd, Lancashire,

UK), after electron beam irradiation to 70 kGy followed by a thermal treatment at 160°C under nitrogen for 12 hours. All the cups were then subjected to Ethylene Oxide Sterilization (EtO). Further details are available in previous reports [18]. Following a standardized procedure, three control check acetabular cups (one for each type of material used) were stored (non-loaded) in bovine calf serum to compensate for weight changes due to fluid absorption. All polyethylene acetabular cups were presoaked for four weeks prior the wear tests [18,19].

2.1 Accelerated aging

In the first wear test the specimens were run for five million cycles [18]. Then, all the acetabular cups (worn specimens and soak controls) underwent an accelerated ageing treatment, which was performed in a stainless steel pressure vessel, under 503 ± 7 kPa of oxygen pressure at 70.0 ± 0.1 °C for 14 days, according to ASTM F2003-02. After accelerated ageing, the cups were newly mounted on the hip joint simulator and were run for two million cycles against the CoCrMo femoral heads (second wear test).

2.2 Wear test details

Wear test was performed using a 12-station hip joint simulator (IORSynthe, Bologna, Italy). Each channel has the ability to run an independent load profile under closed-loop control up to 2Hz. In this test, for each station an axial load up to 2600 N was applied, as recommended by the ISO 14242-3 international guideline, according to the rotation test frequency. Flexion/Extension and Adduction/Abduction translations are programmed using a 23° biaxial rocking motion common to all channels. Typically, in an in vivo situation, the surgeon fixes the acetabular cup with an abduction of about 45° and this scenario is reproduced in vitro by considering an inclination of 23° with respect to a horizontal plane as observed in a previous study [20]. The acetabular cup orientation was set in upside-down (inverted anatomical) position with the aim of reproducing worst-case scenarios, i.e. the

entrapment of polyethylene wear debris, generated during the test, at the interface head-cup. The lubricant used was 25% (v/v) new born calf serum balanced with distilled water, with 0.2% sodium azide in order to retard bacterial growth and 20 mM EDTA (ethylenediaminetetracetic acid) to minimize precipitation of calcium phosphates. The mass loss of the cups was determined every 0.4 million cycles using a microbalance (Sartorius Cubis MSE 225, Goettingën, Germany) with a sensitivity of 0.01 mg and an uncertainty of 0.01 mg. Each mass measurement was repeated three times and the average mass was used for calculations.

Wear trend was determined from the mass loss of each acetabular cup, corrected by acetabular soak control; the wear rates, calculated from the steady-state slopes of the mass loss versus number of cycles lines, were obtained using least squares linear regression. The mass loss data were analysed using a non-parametric Kruskall-Wallis (K-W) test. Statistical significance was set at P < 0.05.

2.3 Roughness measurements

The surface roughness of all the CoCrMo femoral heads was measured at the beginning and at the end of the second test using contact profilometer Hommel Tester T8000 (Hommel Werke, Koeln, Germany). Scanning operations were performed on ten point for each femoral head: one point on the pole and three random points on three different planes identified according to a previously standardized protocol [21]. Sampling lengths were taken using a cut-off of 0.08 mm. Three parameters (Ra, Rt, and Rsk), in agreement with a previous study [21], were taken into consideration to qualify the variation of surface roughness during the test.

2.4 Micro-Raman analyses

The PE components were analysed by micro-Raman spectroscopy before (i.e. after ageing) and after the second wear test. Micro-Raman spectra were obtained using a Jasco NRS-2000C instrument with a microscope of $50 \times$ magnification. All the spectra were recorded in back-scattering conditions with 5 cm⁻¹ spectral resolution using the 532 nm Green Diode Pumped Solid State (DPSS) Laser Driver (RgBLase LLC, USA) with a power of ca. 20 mW. A 160 K cooled digital CCD (Spec-

10: 100B, Roper Scientific Inc.) was used as detector. A confocal pinhole with an aperture diameter of 200 µm was placed in the optical circuit to obtain signals from a limited in-depth region. All the Raman measurements were made in a fully non-destructive way, without any sample manipulation.

The worn components were analysed near the center of the articulating surface, which appeared the most damaged area according to previously reported data [22,23]; twelve spectra at least were recorded. At a first approximation, PE can be considered a composite of three different phases [24]: a crystalline phase, a melt-like amorphous one and an anisotropic disordered phase (i.e. a "third phase" with a prevailing trans conformation of the chains, which have lost their lateral order). The crystalline phase contains chains folded into highly oriented lamellae, with the crystals being primarily orthorhombic in structure, although monoclinic structures may coexist in particular stress conditions [25,26]. To evaluate the effects of wear testing on the PE structure, several spectroscopic markers were calculated according to the literature [24,27]; the bands used to this purpose are shown in Figure 1 together with their assignments [24,28].

The fraction of orthorhombic (α_o), amorphous (α_a) and intermediate anisotropic disordered (α_b) phases were calculated from the relative intensities of selected Raman bands, according to Strobl and Hagedorn [24]:

$$\alpha_{o} = \frac{A_{1414}}{0.46 \times A_{1295+1305}}$$
(1)
$$\alpha_{a} = \frac{A_{1080}}{0.79 \times A_{1295+1305}}$$
(2)

$$\alpha_{\rm b} = 1 - (\alpha_{\rm o} + \alpha_{\rm a}) \tag{3}$$

where A_{1414} and A_{1080} are the areas of the Raman bands at 1414 and 1080 cm⁻¹, respectively; $A_{1295+1305}$ is the area of the internal conventional (i.e. independent of chain conformation) band group. The A_{1080} band area was determined after a curve fitting analysis of the 1040-1109 cm⁻¹ range by

means of a commercial software (Opus 5.0 from Bruker Optik GmbH, Germany). Curve fitting was performed on the original spectra after baseline correction, using the Levenberg-Marquardt algorithm. The Raman components were described as linear combinations of Gaussian and Lorentzian functions. According to a method proposed by Lagaron et al. [27], the fraction of all-trans sequences was evaluated through the following ratio:

all - trans =
$$\frac{A_{1130}}{0.80 \times A_{1295+1305}}$$
 (4)

where A_{1130} is the area of the Raman band at about 1130 cm⁻¹, which has been associated with all-trans C-C bonds located both in the crystalline and amorphous phases. The fraction of all-trans sequences in an orthorhombic environment (namely ortho-trans) was calculated as:

ortho - trans =
$$\frac{1.78 \times A_{1414}}{A_{1130}}$$

(5)

The area of the above mentioned bands was determined by means of a commercial software (Spectra Analysis, Jasco Corporation, Japan). The occurrence of orientation upon wear tests was assessed by evaluating the A_{1130}/A_{1060} area ratio. The 1060 cm⁻¹ band area was calculated by the curve fitting analysis of the 1040-1109 cm⁻¹ range by means of a commercial software (OPUS 6.0 from Bruker Optik GmbH, Germany). Curve fitting was performed on the original spectra after baseline correction, using the Levenberg-Marquardt algorithm. The Raman bands were described as linear combination of Gaussian and Lorentzian functions.

3. Results

All the prosthetic acetabular cups completed the planned two Mc. As shown in Figure 2, mass loss constantly increased during the whole test and the XLPE_VE acetabular cups wore more than the XLPE ones. In particular, mass loss was found to decrease along the series XLPE_VE > STD_PE >

XLPE, although the results of the Post hoc test (Table 1) did not disclose any significant difference between the three sets of cups at any number of cycles.

The surface analysis of the metallic heads showed a general worsening of the three roughness parameters in comparison with the values measured at the end of the first test and before it [18] (Table 2). In particular, upon the second test, an appreciable increase of Ra is observed for the heads that articulated against both XLPE and XLPE_VE cups. Moreover, a significant increase of Rt was observed for all the sets of specimens. Upon the second test, the surface of the heads that articulated against STD_PE and XLPE cups became less negatively skewed, while an opposite behavior happened for those coupled with XLPE_VE samples, indicating the generation of diminishing peaks. This roughness trend is emphasized in Figure 3, which shows the topography of the three most worn samples obtained in particularly scratched areas.

Figure 4 reports the average values of α_o , α_a and α_b , calculated from the micro-Raman spectra recorded on the aged cups before and after testing. As can be easily seen from Figure 4, the α_o orthorhombic content underwent a general decrease upon testing, while a parallel increase in the α_b third phase content occurred; less noticeable changes occurred in the α_a amorphous content. The most significant changes in α_o and α_b were observed for the STD_PE acetabular cups, although were detected also for XLPE_VE 2 and XLPE_1.

The changes in the fraction of all-trans sequences (all-trans content) reflected these trends: the most significant decreases were revealed in the STD_PE acetabular cups (Figure 5), followed by the XLPE_VE samples; actually, these specimens underwent the highest weight losses. The ortho-trans content and the A_{1130}/A_{1030} ratio had different trends in the three sets of acetabular cups (Figure 5). Upon testing, the fraction of all-trans sequences in an orthorhombic environment (i.e. ortho-trans) overall increased in the STD_PE samples (and this change was significant in STD_PE 3), remained nearly constant in XLPE_VE, while generally decreased in XLPE (and this change was significant in XLPE 1). The A_{1130}/A_{1030} ratio, sensitive to changes in orientation, decreased in the STD_PE samples,

while increased in the XLPE and XLPE_VE acetabular cups, in agreement with a trend previously observed [4].

4. Discussion

Although the long-term survival of hip prostheses is affected by multiple factors, a UHMWPE hip component articulating against a metallic or ceramic counterface remains the most commonly used bearing biomaterial in total joint arthroplasty [29,30]. Unfortunately, the limitless material does not exist and PE fails during hip implantation. The main concern about the failure of THA has been the biological response to particulate PE debris generated by conventional metal on polyethylene bearing surfaces leading to osteolysis and aseptic loosening of the prosthesis [31]. The wear particles generated by metal on UHMWPE articulation cause a chronic inflammatory response to foreign body, which is mediated by macrophages with release of lytic enzymes, bone resorbing mediators and proinflammatory cytokines [31]. The problem of wear debris induced osteolysis may be overcome with the use of new generation metal-on-metal or ceramic-on-ceramic prostheses [32]. However, for metalon-metal prostheses, the prospects of increasing the osteolysis- free life of the implant are good, but additional biological problems associated with the nanometer size and reactivity of the wear particles in vivo are emerging [33-35]. For the ceramic-on-ceramic prostheses, initial prospects were encouraging with a significantly decreased risk of osteolysis, aseptic loosening, dislocation and thus revision [36]. Currently, standard UHMWPE has been improved through crosslinking for enhanced wear resistance and, more recently, also with the addition of antioxidants (i.e. vitamin E) to address oxidation [6]. The latter process is a complex sequence of various cascade reactions, which is not fully predictable in the long-term [12]. Efforts have been performed in the scientific community to approach ageing methodologies able to simulate the in vivo ageing of UHMWPE and to reproduce the chemical changes occurring in PE due to oxidation. Although none of the existing protocols can fully reproduce the in vivo environment and service conditions of the implants, thereby limiting the clinical

significance of this as of any other in vitro study, accelerated ageing according to ASTM F2003-02, has demonstrated satisfactory results in differentiating the oxidation stability of different UHMWPE configurations [2], which in turn is known to influence the wear performance.

With this in mind, we asked if the wear behavior of XLPE VE was influenced by accelerated ageing to a different extent with respect to STD_PE and XLPE. To this purpose, the wear performance of the three sets of PE acetabular cups coupled with CoCrMo femoral heads was evaluated for two million cycles, using a 12-station hip simulator, after accelerated ageing. The results of this investigation clearly showed a different wear behavior with respect to our previous work [18]. In that study, a decreasing wear was measured along the series STD PE > XLPE VE > XLPE. We have already shown [18] that lipids absorption significantly affects the absolute gravimetric wear measurement, even if it did not influence the overall trend, in that case. We have therefore assumed that the same applies to the present study. We have not measured the actual lipid absorption here, since we chose to perform only non-destructive analyses, in order to preserve the cups for a further, highly demanding test. After accelerated ageing, all the polyethylene acetabular cups showed a different wear performance with respect to the previous test [18]. In fact, in the present study, the XLPE VE acetabular cups wore more than the STD PE ones and even more than the XLPE samples, although no statistically significant differences were observed between the three sets of PE cups using the K-S statistical test. The lower wear rate observed for XLPE was not unexpected, since radiation crosslinking of PE results in a substantially higher wear resistance as compared to uncrosslinked PE [26,37,38]. The addition of vitamin E has been found to protect PE from oxidative degradation resulting in improved mechanical and wear properties [39,40]; on the contrary, Bladen et al. have reported that the wear rates of UHMWPE with or without vitamin E were not significantly different [41] and also in our previous test XLPE_VE did not exhibit a lower wear rate than XLPE [18]. These apparent discrepancies must be explained in relation to the different methods utilized to incorporate vitamin E as well as to the differences in the PE processing conditions. With regards to vitamin E incorporation, this antioxidant may be added before irradiation (during moulding or extrusion) or by diffusion after irradiation. Both methods have some drawbacks. In the former, the crosslinking

efficiency is decreased due to the ability of vitamin E to scavenge free radicals during irradiation [42] even if it is difficult to control the concentration and the distribution of the antioxidant. In the present study, vitamin E was incorporated into PE before irradiation; actually, XLPE_VE displayed a lower crosslink density than XLPE [18]. Therefore, the higher wear rate measured for XLPE_VE compared to XLPE may be ascribed to the lower crosslinking extent of the former.

In association with a bad wear performance, a worsening of the surface roughness of the CoCrMo femoral heads was observed. An "ideal surface finish" should have low Ra and Rt values and a negative Rsk value [43,44]. The presence of depressions or holes (rather than scratches) with smooth (rather than sharp) edges seems to improve the lubrication and wettability properties. Smoother surfaces (Rsk < 0) are less detrimental than surfaces with a positive Rsk. In this test, an overall increase of Ra and Rt values was observed. Counterface roughness has been indicated as an important variable controlling the contribution of each wear process [45]. A significant change in the morphological features of the bearing surfaces, as happened in this case, could strongly affect the lubricating phenomena (boundary, mixed, hydrodynamic, squeeze) [46] and modify the fluid dynamic behaviour of the synovial fluid [47] favouring a fluid film rupture and causing localized contacts of the prostheses surfaces.

To gain insights into this subject at a molecular level, micro-Raman analyses were carried out. From a general point of view, spectroscopic investigations confirmed a bad wear behavior for the three sets of cups, definitely worst than that observed in a previous test comparing unaged STD_PE, XLPE_VE and XLPE [4]; the XLPE and XLPE_VE acetabular cups appeared to overall exhibit slightly lower differences in the evaluated spectral markers than the STD_PE samples. The spectroscopic analyses showed that upon ageing a different wear mechanism occurred: for the STD_PE, the α_0 content decreased and the α_b content increased (Figure 4), while these parameters were found to have an opposite trend by testing unaged samples [4]. Moreover, the orthorhombic and third-phase contents were found to significantly change also in some crosslinked samples (XLPE_VE 2 and XLPE 1), while remained constant in our previous test on unaged samples [4], confirming the worse wear behavior after accelerated ageing. It must be stressed that, as observed for unaged

samples, also after accelerated ageing the three sets of acetabular cups underwent different structural rearrangements upon wear. Actually, the ortho-trans content overall increased in the STD_PE samples, remained nearly constant in XLPE_VE, while generally decreased in XLPE (Figure 5). These trends revealed a different rearrangement of the polymeric chains in the three sets of samples upon wear, with different changes in the distribution of the all-trans sequences within the orthorhombic, amorphous and third phases. The A_{1130}/A_{1060} ratio, sensitive to changes in orientation, decreased in the STD_PE samples, while increased in the XLPE and XLPE_VE acetabular cups, in agreement with a trend previously observed for unaged samples [4]. At this purpose, it must be recalled that the bands at 1130 and 1060 cm⁻¹ have different vibrational symmetries; if the molecules are oriented in a preferred direction, the 1130 cm⁻¹ band has been reported to become stronger with respect to the 1060 cm⁻¹ band [48].

According to some studies, a decrease in crystallinity may represent a worsening of the mechanical properties; actually, Simis et al. [49] have reported that a decrease in crystallinity results in decreases in elastic modulus, yield strength and micro-hardness. Karuppiah et al. [50] have found that an increase in crystallinity results in a lower friction force, lower wear depth and width as well as increases in hardness and scratch resistance at a microscale and nanoscale. Figure 6 allows to gain more insights into the effects of accelerated ageing on the wear behavior of the acetabular cups at the molecular level; the reported graphs show that a correlation exists between the difference % observed upon the test in the α_0 , α_a , α_b and all-trans contents and the value of these spectral markers measured before the test (i.e. after ageing). In other words, the acetabular cups that showed after ageing the highest α_0 and all-trans values and the lowest α_a and α_b values underwent upon the test the most significant decrease in the orthorhombic and all-trans contents (Figure 6A and 6D) and the highest increase in the amorphous and third phases contents (Figure 6B and 6C), i.e. were the most affected by the wear testing. These trends are not unexpected. Actually, it is well recognised that the mechanical properties and wear performance of PE depend on the distribution of crystalline and non-crystalline phases as well as molecular orientation, besides molecular weight and degree of crosslinking. The trends of Figure 6 are in agreement with the findings by Takahashi et al. [51], who have related a

lower content of the amorphous phase to a higher resistance to creep deformation, but to a lower capacity of shape recovery after removal of the applied load.

This study was approached to acquire further knowledge about the effects that the accelerated ageing protocol could elicit on the wear performance of these different polyethylenes. Further researches are needed to optimize this approach with the addition of third-body debris, in order to study the tribological behavior under more severe simulator conditions, as reported in a previous study by Zietz et al. [52]. Actually, third-body wear resistance of XLPE has not been extensively investigated yet and it has been supposed that this material, due to its micromorphology, could be less resistant than STD_PE to such wear [53].

CONCLUSIONS

All the acetabular cups studied in this work maintained an increased weight loss during the whole test. Lower weight losses (although not statistically significant) were exhibited by the XLPE acetabular cups, which have the potential for reduced wear and decreased osteolysis. The roughness of the CoCrMo femoral heads seemed to increase indiscriminately for all the analyzed configurations, not showing a predominant pattern correlated to weight loss.

crife

The acetabular cups studied in this work showed a bad wear behavior, both at gravimetric and molecular levels. The micro-Raman analyses showed that accelerated ageing determined a worsening of the wear resistance, since the evaluated spectroscopic markers underwent more significant changes than for unaged acetabular cups [4]. The three sets of samples showed different wear mechanisms during testing with regards to the changes of both the molecular orientation and the distribution of the all-trans sequences within the orthorhombic, amorphous and third phases.

The results of the present study showed that the addition of vitamin E was not effective in improving the gravimetric wear behaviour of PE after accelerated ageing, differently from as reported by other authors [54,40]. However, from a molecular point of view, the XLPE_VE acetabular cups tested after accelerated ageing appeared definitely less damaged than the STD_PE ones and comparable to XLPE

samples. Further studies are in progress to assess the influence of vitamin E on the wear behaviour of

PE under more severe conditions (i.e. in presence of third-body wear particles).

Acknowledgements

The authors wish to thank Tomaso Villa (Politecnico di Milano, Dept. of Structural Engineering, Milano-Italy) for his help to providing the components. This work was partially supported by the Italian Program of Donation for Research "5 per mille", year 2011.

Accepted manuscrip

References

- [1] Brach del Prever EM, Bistolfi A, Bracco P, Costa L. UHMWPE for arthroplasty: past or future? J Orthop Traumatol 2009;10:1–8.
- [2] Bracco P, Oral E. Vitamin E-stabilized UHMWPE for total joint implants: A review. Clin. Orthop. Relat. Res., vol. 469, 2011, p. 2286–93.
- [3] James SP, Oldinski R (Kurkowski), Zhang M, Schwartz H. UHMWPE Biomaterials Handbook. 2009.
- [4] Affatato S, Freccero N, Taddei P. The biomaterials challenge: A comparison of polyethylene wear using a hip joint simulator. J Mech Behav Biomed Mater 2016;53:40–8.
- [5] Kurtz S, Medel FJ, Manley M. (iii) Wear in highly crosslinked polyethylenes. Curr Orthop 2008;22:392–9.
- [6] Banche G, Bracco P, Allizond V, Bistolfi A, Boffano M, Cimino A, et al. Do Crosslinking and Vitamin E Stabilization Influence Microbial Adhesions on UHMWPE-based Biomaterials? Clin Orthop Relat Res 2014;473:974–86.
- [7] Kurtz SM, Hozack WJ, Purtill JJ, Marcolongo M, Kraay MJ, Goldberg VM, et al. 2006 Otto Aufranc Award Paper: significance of in vivo degradation for polyethylene in total hip arthroplasty. Clin Orthop Relat Res 2006;453:47–57.
- [8] Zweifel H. Stabilization of Polymeric Materials | Springer 1998.
- [9] Kurtz SM, Muratoglu OK, Evans M, Edidin AA. Advances in the processing, sterilization, and crosslinking of ultra-high molecular weight polyethylene for total joint arthroplasty. Biomaterials 1999;20:1659–88.
- [10] Bracco P, Brunella V, Zanetti M, Luda MP, Costa L. Stabilisation of ultra-high molecular weight polyethylene with Vitamin E. Polym Degrad Stab 2007;92:2155–62.
- [11] Kurtz SM, Siskey RL, Dumbleton J. Accelerated aqueous aging simulation of in vivo oxidation for gamma-sterilized UHMWPE. J Biomed Mater Res Part B Appl Biomater 2009;90:368–72.
- [12] Rocha M, Mansur A, Mansur H. Characterization and Accelerated Ageing of UHMWPE Used in Orthopedic Prosthesis by Peroxide. Materials (Basel) 2009;2:562–76.
- [13] Toohey KS, Blanchet TA, Heckelman DD. Effect of accelerated aging conditions on resultant depthdependent oxidation and wear resistance of UHMWPE joint replacement bearing materials. Wear 2003;255:1076–84.
- [14] Lu S, Buchanan FJ, Orr JF. Analysis of variables influencing the accelerated ageing behaviour of ultrahigh molecular weight polyethylene (UHMWPE). Polym Test 2002;21:623–31.
- [15] McKellop H, Shen FW, Lu B, Campbell P, Salovey R. Effect of sterilization method and other modifications on the wear resistance of acetabular cups made of ultra-high molecular weight polyethylene. A hip-simulator study. J Bone Jt Surg Am 2000;82-A:1708–25.
- [16] Willie BM, Bloebaum RD, Ashrafi S, Dearden C, Steffensen T, Hofmann AA. Oxidative degradation in highly cross-linked and conventional polyethylene after 2 years of real-time shelf aging. Biomaterials 2006;27:2275–84.
- [17] Wolf C, Macho C, Lederer K. Accelerated ageing experiments with crosslinked and conventional ultrahigh molecular weight polyethylene (UHMW-PE) stabilised with alpha-tocopherol for total joint arthroplasty. J Mater Sci Mater Med 2006;17:1333–40.
- [18] Affatato S, Bracco P, Costa L, Villa T, Quaglini V, Toni A. In vitro wear performance of standard, crosslinked, and vitamin-E-blended UHMWPE. J Biomed Mater Res A 2012;100:554–60.
- [19] Taddei P, Affatato S, Fagnano C, Toni A. Oxidation in ultrahigh molecular weight polyethylene and cross-linked polyethylene acetabular cups tested against roughened femoral heads in a hip joint simulator. Biomacromolecules 2006;7:1912–20.
- [20] Taddei P, Affatato S, Fagnano C, Toni A. Photoluminescence investigations on alumina ceramic bearing couples tested under different angles of inclination in a hip joint simulator. J Mater Sci 2006;41:399–407.

- [21] Affatato S, Bersaglia G, Junqiang Y, Traina F, Toni A, Viceconti M. The predictive Power of Surface Profile Parameters on the Amount of Wear Measured In Vitro on Metal-On-Polyethylene Artificial Hip Joints. Proc Inst Mech Eng Part H J Eng Med 2006;220:457–64.
- [22] Bertoluzza A, Fagnano C, Rossi M, Tinti A, Cacciari GL. Micro-Raman spectroscopy for the crystallinity characterization of UHMWPE hip cups run on joint simulators. J Mol Struct 2000;521:89– 95.
- [23] Affatato S, Bersaglia G, Emiliani D, Foltran I, Taddei P, Reggiani M, et al. The performance of gammaand EtO-sterilised UHMWPE acetabular cups tested under severe simulator conditions. Part 2: wear particle characteristics with isolation protocols. Biomaterials 2003;24:4045–55.
- [24] Strobl GR, Hagedorn W. Raman spectroscopic method for determining the crystallinity of polyethylene. J Polym Sci Polym Phys Ed 1978;16:1181–93.
- [25] Taddei P, Affatato S, Rocchi M, Fagnano C, Viceconti M. The effects of irradiation and EtO-treatment on ultrahigh molecular weight polyethylene acetabular cups following accelerated aging: Degradation of mechanical properties and morphology changes during hip simulator tests. J Mol Struct 2008;875:254– 63.
- [26] Taddei P, Di Foggia M, Affatato S. Raman characterization of conventional and cross-linked polyethylene in acetabular cups run on a hip joint simulator. J Raman Spectrosc 2011;42:1344–52.
- [27] Lagaron JM, Dixon NM, Reed W, Pastor JM, Kip BJ. Morphological characterisation of the crystalline structure of cold-drawn HDPE used as a model material for the environmental stress cracking (ESC) phenomenon. Polymer (Guildf) 1999;40:2569–86.
- [28] Citra M, Chase D, Ikeda R, Gardner K. MOLECULAR-ORIENTATION OF HIGH-DENSITY POLYETHYLENE FIBERS CHARACTERIZED BY POLARIZED RAMAN-SPECTROSCOPY. Macromolecules 1995;28:4007–12.
- [29] Sobieraj MC, Rimnac CM. Ultra high molecular weight polyethylene: mechanics, morphology, and clinical behavior. J Mech Behav Biomed Mater 2009;2:433–43.
- [30] MDDI. Developing PEEK Polymer as a Bearing Material for Implants | MDDI Medical Device and Diagnostic Industry News Products and Suppliers n.d.
- [31] Kumar N, Arora GNC, Datta B. Bearing surfaces in hip replacement Evolution and likely future. Med Journal, Armed Forces India 2014;70:371–6.
- [32] Ingham E, Fisher J. Biological reactions to wear debris in total joint replacement. Proceed Inst Mech Eng Part H J Eng Med 2000;214:21–37.
- [33] Long WT. The clinical performance of metal-on-metal as an articulation surface in total hip replacement. Iowa Orthop J 2005;25:10–6.
- [34] Kwon Y-M, Ostlere SJ, McLardy-Smith P, Athanasou NA, Gill HS, Murray DW. "Asymptomatic" pseudotumors after metal-on-metal hip resurfacing arthroplasty: prevalence and metal ion study. J Arthroplasty 2011;26:511–8.
- [35] Haddad FS, Thakrar RR, Hart AJ, Skinner JA, Nargol AVF, Nolan JF, et al. Metal-on-metal bearings: the evidence so far. J Bone Joint Surg Br 2011;93:572–9.
- [36] Hu D, Tie K, Yang X, Tan Y, Alaidaros M, Chen L. Comparison of ceramic-on-ceramic to metal-onpolyethylene bearing surfaces in total hip arthroplasty: a meta-analysis of randomized controlled trials. J Orthop Surg Res 2015;10:22.
- [37] Kurtz SM, Gawel HA, Patel JD. History and systematic review of wear and osteolysis outcomes for first-generation highly crosslinked polyethylene. Clin Orthop Relat Res 2011;469:2262–77.
- [38] Affatato S, Bersaglia G, Rocchi M, Taddei P, Fagnano C, Toni A. Wear behaviour of cross-linked polyethylene assessed in vitro under severe conditions. Biomaterials 2005;26:3259–67.
- [39] Grupp TM, Holderied M, Mulliez MA, Streller R, Jäger M, Blömer W, et al. Biotribology of a vitamin E-stabilized polyethylene for hip arthroplasty Influence of artificial ageing and third-body particles on wear. Acta Biomater 2014;10:3068–78.
- [40] Oral E, Muratoglu OK. Vitamin E diffused, highly crosslinked UHMWPE: a review. Int Orthop

2011;35:215-23.

- [41] Bladen CL, Teramura S, Russell SL, Fujiwara K, Fisher J, Ingham E, et al. Analysis of wear, wear particles, and reduced inflammatory potential of vitamin E ultrahigh-molecular-weight polyethylene for use in total joint replacement. J Biomed Mater Res B Appl Biomater 2013;101:458–66.
- [42] Oral E, Godleski Beckos C, Malhi AS, Muratoglu OK. The effects of high dose irradiation on the crosslinking of vitamin E-blended ultrahigh molecular weight polyethylene. Biomaterials 2008;29:3557–60.
- [43] Davidson JA, Poggie RA, Mishra AK. Abrasive wear of ceramic, metal, and UHMWPE bearing surfaces from third-body bone, PMMA bone cement, and titanium debris. Biomed Mater Eng 1994;4:213–29.
- [44] Raimondi MT, Pietrabissa R. The in-vivo wear performance of prosthetic femoral headswith titanium nitride coating. Biomaterials 2000;21:907–13.
- [45] Hailey JL, Ingham E, Stone M, Wroblewski BM, Fisher J. Ultra-high molecular weight polyethylene wear debris generated in vivo and in laboratory tests; the influence of counterface roughness. Proc Inst Mech Eng H 1996;210:3–10.
- [46] Ma L, Rainforth WM. A study of Biolox? delta subject to water lubricated reciprocating wear. Tribol. Int., vol. 43, 2010, p. 1872–81.
- [47] Ruggiero A, Gòmez E, D'Amato R. Approximate analytical model for the squeeze-film lubrication of the human ankle joint with synovial fluid filtrated by articular cartilage. Tribol Lett 2011;41:337–43.
- [48] Pigeon M, Prud'homme RE, Pezolet M. Characterization of molecular-orientation in polyethyleen by Raman-spectroscopy. Macromol 1991;24:5687–94.
- [49] Simis KS, Bistolfi A, Bellare A, Pruitt LA. The combined effects of crosslinking and high crystallinity on the microstructural and mechanical properties of ultra high molecular weight polyethylene. Biomaterials 2006;27:1688–94.
- [50] Kanaga Karuppiah KS, Bruck AL, Sundararajan S, Wang J, Lin Z, Xu Z-H, et al. Friction and wear behavior of ultra-high molecular weight polyethylene as a function of polymer crystallinity. Acta Biomater 2008;4:1401–10.
- [51] Takahashi Y, Masaoka T, Pezzotti G, Shishido T, Tateiwa T, Kubo K, et al. Highly Cross-Linked Polyethylene in Total Hip and Knee Replacement: Spatial Distribution of Molecular Orientation and Shape Recovery Behavior. Biomed Res Int 2014;2014.
- [52] Zietz C, Fabry C, Reinders J, Dammer R, Kretzer JP, Bader R, et al. Wear testing of total hip replacements under severe conditions. Expert Rev Med Devices 2015;12:393–410.
- [53] Brach Del Prever EM, Bistolfi A, Bracco P, Costa L. UHMWPE for arthroplasty: past or future? J Orthop Traumatol 2009;10:1–8.
- [54] Fu J, Doshi BN, Oral E, Muratoglu OK. High temperature melted, radiation cross-linked, vitamin E stabilized oxidation resistant UHMWPE with low wear and high impact strength. Polymer (Guildf) 2013;54:199–209.

Table 1 - Cumulative mass loss (mean \pm standard deviation) for the three sets of PE acetabular cups tested. The p-values were obtained using a Kruskall-Wallis non-parametric test.

Table 2 - Mean roughness (± Standard Deviation) for the femoral heads coupled with the three sets of cups.

Figure 1 – Average micro-Raman spectrum of PE (STD_PE before the test, i.e. after accelerated ageing), in the CH₂ bending (δ), CH₂ twisting (τ) and C-C stretching (v; s = symmetric; a = anti-symmetric) regions; the assignments to the amorphous (A) and crystalline (C) phases have been given according to the literature.

Figure 2 – Wear behavior and Regression coefficient for the different polyethylenes tested.

Figure 3 – Surface topography (a) and Abbott-Firestone curve (b) of the CoCrMo femoral heads coupled with the most worn PE specimens of each set.

Figure 4 – Values (average \pm standard deviation) of α_0 , α_a and α_b contents as obtained from the spectra recorded before the test (i.e. after accelerated ageing) and after it on the STD_PE, XLPE_PE and XLPE acetabular cups.

Figure 5 – Values (average \pm standard deviation) of all-trans and ortho-trans contents, and A_{1130}/A_{1060} ratios as obtained from the spectra recorded before the test (i.e. after accelerated ageing) and after it on the STD_PE, XLPE_PE and XLPE acetabular cups.

Figure 6 – Trend of the difference % observed upon the test in the α_0 , α_a , α_b and all-trans contents of the analysed acetabular cups as a function of the value of these spectral markers measured before the test (i.e. after ageing).

19



















Table 1 - Cumulative mass loss (mean ± standard deviation) for the three sets of PE acetabular cups tested. The pvalues were obtained using a Kruskall-Wallis non-parametric test.

	Mean	K-W test (p-value)		
Cycles	XLPE	STD_PE	XLPE_VE	
[Mc]				
0.4	3.3 ±1.7	15.7 ±2.5	21.4 ±9.7	0.061
0.8	7.2 ± 3.2	34.8 ±6.9	42.5 ±16.3	0.066
1.2	8.6 ±5.4	56.6 ±10.0	59.7 ±18.3	0.068
1.6	15.4 ±6.6	81.9 ±9.21	83.3 ±20.7	0.066
2	20.8 ± 6.8	97.4 ±7.2	105.7 ±21.7	0.061

Table 2 - Mean roughness (± Standard Deviation) for the CoCrMo femoral heads coupled with the three sets of cups.

Before wear tests [18]			After the first wear test [at five million cycles] [18]		After the second wear test [at seven million cycles]			Difference % (second test – first test)				
	STD_PE	XLPE	XLPE_VE	STD_PE	XLPE	XLPE_VE	STD_PE	XLPE	XLPE_VE	STD_PE	XLPE	XLPE_VE
Ra	0.01 ± 0.01	0.01 ± 0.01	0.01 ± 0.01	0.04 ± 0.01	0.01 ± 0.01	0.02 ± 0.01	0.04 ± 0.02	0.03 ± 0.01	0.04 ± 0.02	0	66.7	50.0
Rt	0.05 ± 0.01	0.05 ± 0.01	0.05 ± 0.01	0.11 ±0.09	0.11 ± 0.03	0.13 ± 0.03	0.41 ± 0.07	0.38 ± 0.17	0.37 ± 0.05	73.2	71.1	64.9
Rsk	0.053 ± 0.07	0.037 ± 0.05	0.001 ± 0.03	-0.56± 0.08	-0.64±0.60	-0.20±0.15	-0.35±0.96	-0.36 ± 0.49	-0.46 ± 0.29	-60.0	-77.2	56.5