

AperTO - Archivio Istituzionale Open Access dell'Università di Torino

The role of hybrid chitosan membranes on scarring process following lumbar surgery: post-laminectomy experimental model

This is the author's manuscript

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/1506193> since 2016-06-15T11:57:30Z

Published version:

DOI:10.1179/1743132814Y.0000000414

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)



UNIVERSITÀ DEGLI STUDI DI TORINO

This is an author version of the contribution published on:

Questa è la versione dell'autore dell'opera:

*Neurol Res. 2015 Jan;37(1):23-9. doi: 10.1179/1743132814Y.0000000414. Epub
2014 Jun 25.*

The definitive version is available at:

La versione definitiva è disponibile alla URL:

*[http://www.tandfonline.com/doi/full/10.1179/1743132814Y.0000000414#.V2Enaf
mLTIU](http://www.tandfonline.com/doi/full/10.1179/1743132814Y.0000000414#.V2EnafmLTIU)*

The role of hybrid chitosan membranes on scarring process following lumbar surgery: post-laminectomy experimental model

Miguel Carvalho¹, Luís M. Costa², José E. Pereira², Yuki Shirotsaki³, Satoshi Hayakawa⁴, José D. Santos⁵, Stefano Geuna⁶, Federica Fregnan⁶, António M. Cabrita⁷, Ana C. Maurício^{8,9}, Artur S. Varejão^{2,9}

¹Neurosurgery Department, Coimbra Hospital and University Center (CHUC), Coimbra, Portugal, ²Department of Veterinary Sciences, University of Trás-os-Montes e Alto Douro, Vila Real, Portugal, ³Frontier Research Academy for Young Researchers, Kyushu Institute of Technology, Kitakyushu, Japan, ⁴Graduate School of Natural Science and Technology, Okayama University, Okayama Japan, ⁵CEMUC, Departamento de Engenharia Metalúrgica e Materiais, Faculdade de Engenharia, Universidade do Porto, Porto, Portugal, ⁶Department of Clinical and Biological Sciences, University of Turin, Italy, ⁷Experimental Pathology Department, Faculty of Medicine of the University of Coimbra, Coimbra, Portugal, ⁸Departamento de Clínicas Veterinárias, Instituto de Ciências Biológicas de Abel Salazar (ICBAS), Universidade do Porto (UP), Porto, Portugal, ⁹Centro de Estudos de Ciência Animal (CECA), Instituto de Ciências e Tecnologias Agrárias e Agro-Alimentares (ICETA), Porto, Portugal

Objectives

Post-operative scarring process on lumbar surgery is object of several studies mainly because of the epidural fibrosis formation. Hybrid chitosan have shown promising effect on fibrosis prevention. The aim of this study was to determine the influence of chitosan-silane membrane on the lumbar surgery scarring process. These membranes have improved mechanical strength which makes them suitable to maintain a predefined shape. Methods: A two level lumbar laminectomy was performed in 14 New Zealand male rabbits. Laminectomy sites were randomly selected for biomaterial or control. Chitosan membranes were prepared and care was taken in order to make it adapted to the bone defect dimensions covering the totality of the defect including the bone margins. Histological analysis was performed by haematoxylin/eosin and by Masson's trichrome staining four weeks after laminectomy. Results: Microscope observations revealed the presence of a well-organized regenerating tissue, integrated in the surrounding vertebral bone tissue with a regular and all-site interface on the chitosan sites, in clear contrast with the presence of a disorganized regenerating tissue with aspects consistent with the persistence of a chronic inflammatory condition, on control sites. Discussion: The results of this study clearly demonstrated that hybrid chitosan had an organizing effect on post-operative scarring process. The presence of the hybrid chitosan membrane resulted on a wellorganized tissue integrated in the surrounding vertebral bone tissue with signs of regenerative bone tissue in continuity with native bone. This can be a major feature on the dynamics of epidural fibrosis formation.

Keywords: Chitosan-silane, Epidural fibrosis, Hybrid chitosan, Laminectomy, Lumbar surgery

Introduction

Since the clarification of the sciatic pain pathophysiology, nearly a century ago, and its relationship to lumbar disk herniation, several surgical approaches were proposed and currently it is the most common indication for neurosurgical procedure in the US and there is evidence that the surgical treatment has advantage over conservative treatment.^{1–3} The surgical technique involves a posterior approach and an extradural disk removal.

Several authors have described different surgical techniques and a large majority describe gestures for protection against post-operative scarring.^{2,4–7} The prevention of post-operative perineural fibrosis has been object of increasing interest as this condition has been pointed out as one of the main causes of failed

back surgery syndrome.^{8–10} Ross et al.'s prospective, randomized, controlled, blind and multicentric trial, revealed a significant association between post-operative epidural fibrosis and recurrent radicular pain.¹¹ Chitin is a co-polymer of N-acetyl-glucosamine and of N-glucosamine. When the number of N-acetyl-glucosamine units is superior to 50% it is called chitin and when the number of N-glucosamine units is superior that biopolymer is then called chitosan. Of these two biopolymers, chitosan has been more used on research due to its chemical properties. Chitin and chitosan are obtained from shellfish such as crabs and shrimps. It could be possible, on a near future, chitin or chitosan production through biotechnology techniques, especially if it is for medical applications.¹² Advantageous physicochemical properties can be achieved by the cross-linking between chitosan, gamaglycidoxypropyltrimethoxysilane (GPTMS) and a siloxane network forming hybrid chitosan membranes.^{13–17}

Materials and Methods

Animals For this in vivo study it was used 14 New Zealand male rabbits (Charles River, Barcelona, Spain). The animals' average weight was 3 kg. Each animal was submitted to a two level lumbar laminectomy (L1 and L3). For each animal, one laminectomy site was randomly selected for biomaterial application and the other laminectomy site acted as control. The animals were kept in the Veterinary Medical Teaching Hospital of the University of Trás-os-Montes e Alto Douro, and were fed with a standard rabbit regimen. All rabbits underwent a complete pre-operative neurological evaluation by a veterinary clinician to ensure complete neurological integrity. After surgery, all animals were kept under close surveillance for infection or neurological deterioration screening. All procedures were performed with the approval of the Veterinary Authorities of Portugal in accordance with the European Communities Council Directive of 24 November 1986 (86/609/EEC).
Hybrid chitosan membranes preparation Hybrid chitosan membranes were prepared by a previous described method.¹⁴ Chitosan (high molecular weight, Sigma, St. Louis, MO, USA) was dissolved in a 0.25M acetic acid solution to attain a concentration of 2% (w/v). The precursor sols were obtained by adding GPTMS (Sigma) to the chitosan solution. After stirring at room temperature for 1 hour, the resultant chitosan–siloxane solutions were poured into polystyrene containers and frozen at 220uC. The frozen sols were subsequently transferred to a freeze-dryer and then, they were lyophilized for 12 hours to complete dryness. The obtained porous hybrid xerogels were soaked in a 0.25M sodium hydroxide solution to neutralize the remaining acetic acid, and then washed with distilled water, and lyophilized again in the freeze-dryer. Before the implantation procedure the membranes were sterilized with ethylene oxide gas and kept at room temperature for 1 week.
Surgical procedure Animals were anesthetized intravenously with ketamine (30 mg/kg) and medetomidine (0.1 mg/kg).

Then, lateral spine radiographs were performed in order to identify the number of lumbar vertebrae and, thus, localize the segments to operate. A midline incision exposed the spinal column at the L1–L3 level, and the paravertebral muscles were dissected bilaterally to visualize the transverse apophyses. The segments to surgically approach were identified intraoperatively by direct palpation. On each segment, the dorso-lumbar fascia was divided and a bilateral paravertebral muscles sub-periosteal dissection was performed. On this stage, the paravertebral muscles were retracted and it was then performed the bilateral laminectomy at L1 and L3 with a drill exposing the dura-mater. The laminectomy defects were measured to be approximately 1065 mm. In order to diminish the influence of any levelspecific variations the biomaterial implantation was placed on L1 laminectomy site (seven animals) or on L3 laminectomy site (seven animals) and the defect was left empty in the remaining site. Care was taken in order to produce a chitosan membrane adapted to the bone defect dimensions in a way that it covered the totality of the defect and also the bone of the margins (Fig. 1). A thorough haemostasis was performed in order to reduce the potential postoperative haematoma. Dorso-lumbar fascia was closed with simple stitches of resorbable

suture and the cutaneous layer was closed with intra-dermic continuous resorbable suture. The operative wound was cleaned with an iodopovidone solution. During the surgical procedure the animal's temperature, blood pressure and electrocardiogram were continuing monitored. An ophthalmic gel (Lacryvisc, Alcon, Lisbon, Portugal) was applied to prevent drying of the eyes. Postoperatively the animals were housed in individual cages and allowed normal activity. They were weighed daily for the first 7 days post-surgery and then weighed weekly. Post-operative care included injections of sulfadiazine and trimethoprim twice a day for up to 1 week. The animals were euthanized 4 weeks after laminectomy and the specimens were prepared for histological analysis.

Histological analysis

The vertebral L1–S1 segment was removed en bloc during the animals necropsy and was fixed on 10% formaldehyde. Decalcification of the entire vertebral segment was achieved using the Morse solution. In brief, decalcification was obtained using sodium citrate/formic acid until chemical testing for the presence of calcium runs negative; the samples were placed in 10 times their volume of the decalcifying solution and the solution was replaced daily. Chemical testing for the presence of calcium was carried out by adding 1 cc of ammonium hydroxide to 5 cc of the decalcifying solution plus 0.1 cc of a saturated ammonium oxalate solution. When calcium is still present in the solution, it precipitates, otherwise decalcification is complete (usually it takes around three weeks). The columns were then cut in 1 cm-long segments transversely to their axis. Each column was then rehydrated with phosphate buffer solution and cryoprotected with three passages in increasing solutions of sucrose (7.5% for 1 hour, 15% for 1 hour, 30% over-night) in 0.1M phosphate buffer solution. Thereafter, specimens are maintained in a 1:1 solution of sucrose 30% and optimal cutting temperature medium for 30 min and then embedded in 100% optimal cutting temperature medium. Specimens must then be stored at -80°C . Sections were then cut by means of a Leica CM1850 Cryostat in a thickness range of 20–30 μm , placed on silane-coated microscope slides to improve slice adhesion, and stored at -20°C . Before staining, sections were taken out of freezer to room temperature and as soon as they were acclimatized, they were further processed either by haematoxylin and eosin (the most commonly used stain for light microscopy observation in histology and histopathology) or by Masson's trichrome staining (that, in comparison to haematoxylin and eosin staining, it highlights also connective tissue). For haematoxylin and eosin staining, the slides were immersed in 0.1% haematoxylin (we use the product from Ciba, Basle, Switzerland) for 10 minutes, washed in tap water for 15 minutes, then immersed in 0.1% eosin (we use the product from Ciba, Basle, Switzerland) for 5 minutes and washed in distilled water. The sections were finally dehydrated in ethanol and mounted in DPX (Fluka, Buchs, Switzerland). For Masson's trichrome staining, we used a Masson trichrome with aniline blue kit (Bio-Optica, Milano, Italy): six drops of Weigert's iron haematoxylin

(solution A) and six drops of Weigert's iron haematoxylin (solution B) were combined together and used to stain slides for 10 minutes. Without washing, the slides were then drained and incubated with 10 drops of alcoholic picric acid solution for 4 minutes. After washing in distilled water, sections were stained with 10 drops of Ponceau acid fuchsin for 4 minutes and washed again in distilled water. Further on, 10 drops of phosphomolybdic acid solution were added to the section for 10 minutes. Without washing, the slides were drained and 10 drops of aniline blue are added to the section for 5 minutes. Finally, after washing in distilled water, dehydrating rapidly in ethanol and clearing in xylol/Bioclear (Bio-Optica, Milano, Italy), the slides were mounted in DPX (Fluka, Buchs, Switzerland). Sections were then analysed and photographed using a DM4000B microscope equipped with a DFC320 digital camera and an IM50 image manager system (Leica Microsystems, Wetzlar, Germany).

Results Results of the histological analysis of rabbit columns at the site of laminectomy are illustrated in Figs. 2–5. Extensive microscope observations, at different magnifications, showed, in the animals that did not receive chitosan application, the presence of a disorganized regenerating tissue (Fig. 2A, asterisk) mingled with islets of bone tissue (Fig. 2A, arrows). At higher magnification (Fig. 2B), the regenerating tissue appeared to be rich in various-sized and roundshaped cells (including many lymphocytes) that indicate the persistence of a chronic inflammatory condition. With respect to the bone tissue organization at the border of the lesion site, lamellae did not show osteonic organization and were oriented without clear orientation (Fig. 3A). Higher magnification observation (Fig. 3B) showed that the interface between the regenerating tissue and the bone tissue (Fig. 3B, arrow) has a limited extension without a clear orientation. Often, bone and regenerating tissue were completely detached and separated by large empty lacunae (Fig. 3A, asterisk). Histological analysis of rabbit columns at the site of laminectomy in the animals that received chitosan application are illustrated in Figs. 4 and 5. At lower magnification (Fig. 4), the presence of a well-organized regenerating tissue, integrated in the surrounding vertebral bone tissue through an interface (Fig. 4, arrows) that, contrary to what was observed in the control group, was regular and extended from the side to the other side of the lamina. The location of islets of bone tissue inside regenerating tissue (Fig. 5, arrows) and the small extension of regenerative tissue in comparison to controls suggest that bone regeneration has progressed significantly filling the lamina defect. Yet the presence of signs of osteonic reorganization (Fig. 4, asterisk) can be detected inside the regenerating tissue. However, since regenerated bone tissue can hardly be distinguished from native bone tissue, the amount of regenerated bone cannot be quantified.

Discussion

The epidural fibrosis formation is the result of postoperative haematoma invasion by thick fibrotic tissue, starting on the periosteum fibrous layer and fibroblast migration from the deep layer of the paravertebral muscles. This process can progress to the vertebral canal and create adherences to the duramater and nerve roots and inflammation is considered to play an important and early role in this process.^{18–20} Fibroblasts have multiple functions important to wound repair, such as collagen synthesis, extracellular matrix reorganization, and wound contraction resulting in mature scar formation. It has been shown that chitosan can inhibit fibroblast growth.^{21,22} Chang et al. in a study for reduction of peritoneal adhesions concluded that a chitosan barrier can inhibit tissue adhesion by inhibiting proliferation and triggering apoptosis.²² For this study it was used an animal laminectomy model using New Zealand rabbits. The bone anatomy of these animals is favourable for a lumbar laminectomy model as the dorsal laminae are long which makes the surgical procedure brief and straightforward, therefore reducing post-operative complications. One of the major complications of this procedure in rabbits is post-operative neurological deterioration which is more common with laminectomies on lower levels. This fact determined the choice of the laminectomy level for this work. Thus, in this study two different levels of lumbar laminectomy were performed, on L1 and L3. At these levels, on the vertebral canal, there is the lower portion of the spinal cord. Therefore, on this particular aspect, this model does not mimic the human lumbar laminectomy conditions. For these concerns, some authors have suggested lumbar laminectomy models in the region of the cauda equina (suggesting different animals, such as the ovine model) which would allow biomechanical testing on nerve roots.^{23,24} However, on the present work, the focus of the study was the histological characterization of the differences of post-operative fibrosis on a manipulated site (in the presence of the biomaterial) and on a control site. Therefore, the results are still valid and applicable to the biomaterial effects on post-operative epidural fibrosis. Another pitfall of the present study is that a simple laminectomy was performed but not a discectomy. Therefore, the effect that the experimental material might have on scar formation at discectomy site and on annular ligament healing could not be assessed.

The main reason for not performing the discectomy was the extreme difficulty to expose the nerve root and annulus fibrosus without neurologic injury in a rabbit model. Chitosan matrices have been shown to have low mechanical strength under physiological conditions and to be unable to maintain a predefined shape for transplantation. The improvement of their mechanical properties can be achieved by modifying chitosan with a silane agent. The GPTMS is one of the silanecoupling agents, which has epoxy and methoxysilane groups. The epoxy group reacts with the amino groups of chitosan molecules while the methoxysilane groups are hydrolyzed and form silanol groups. The silanol groups are subjected to the construction of a siloxane network due to the condensation. Thus, the mechanical strength of chitosan can be improved by the cross-linking between chitosan, GPTMS and siloxane network.¹⁴ This hybrid chitosan membrane was used on the present work and was found to be very convenient to surgically manipulate in order to cover the entire bone defect. A synergistic effect of a more favourable porous microstructure and physicochemical properties (more wettable and higher water uptake level) of chitosan hybrids, and the presence of silica ions may be responsible for the good results in promoting posttraumatic nerve regeneration. In fact, chitosan hybrids were successful in improving sciatic nerve regeneration after axotomy.^{15,16} Other published studies revealed chitosan ability to promote cell membranes fusion after damage as chitosan is able to form large phospholipid aggregates and preferentially targets damaged tissues.^{25,26} On the other hand, in biocompatibility studies, hybrid chitosan membranes elicited a mild inflammatory response that decreased gradually, in clear contrast with the exuberant pyogranulomatous inflammatory reaction developed by non-hybrid chitosan membranes.¹⁶ One important aspect of the present study results was the finding that the hybrid chitosan membrane was consistently and totally degraded by the fourth week after the surgical procedure. This is an important feature as the barrier-effect for this biomaterial is important only in the early stages of the scarring process. Zhou et al. stressed this aspect on their work on reduction of post-surgical adhesion formation after cardiac surgery by application of N,O-carboxymethyl chitosan. Those authors described that the chitosan film used was effective on reducing post-surgical adhesion formation maintaining its structural integrity for five days and degrading by the seventh postoperative day.²⁷ The results of this study clearly demonstrated that chitosan had an organizing effect on post-operative scarring process. The presence of the chitosan membrane resulted on a well-organized tissue integrated in the surrounding vertebral bone tissue. It was also observed signs of regenerative bone tissue in continuity with native bone which, by the present technique cannot be distinguished from each other. In fact, the four-week duration of this study allows only the important conclusion of improved vertebral regeneration on a post-laminectomy model. This can be a major feature on the dynamics of epidural fibrosis formation. Sandoval-Sánchez et al.²⁸ achieved similar results using bilayer chitosan scaffolding as a dural substitute on experimental models. Chuang et al.,²⁹ using a combination of poly-lactic acid gel and autologous micromorselized bone observed significant lamina bone regeneration. However, it is still unknown if the regenerated vertebral lamina can be expected to confer stability to the spinal column and prevent peridural adhesion as a long-term outcome. Further research on ligament structure will confirm whether a newly generated vertebral lamina can provide an

attached bed for soft tissue growth and enable ligament regeneration. Nonetheless, these studies are aiming tissue regeneration after surgical aggression which is significantly different from other current studies that purely aim inhibition of fibrosis such as the use of Mitomycin C.^{20,30} Those studies, chasing the same goal, use an entirely different approach and their results cannot be compared with results from studies using regenerative approaches. Whereas a quantitative analysis of the type or tissue repair was not possible due to its polymorph complexity, extensive microscopy observation carried out in the present study allowed to demonstrate that the morphology of tissue repair was rather consistent, in each of the two experimental groups, and rather differentiated between them. It can thus be concluded that hybrid

chitosan application after laminectomy improves vertebral regeneration by accelerating formation of a new and well organized cover tissue at the site of bone removal and by accelerating its quick differentiation into a newly formed and well organized bone tissue that integrates rapidly with the native bone filling the defect and recreating a vertebral structure which is close to the normal pre-lesion one. Unlike previous studies focused on inhibition of the scarring process in order to prevent epidural adhesions, the present work using this chitosan membrane, has showed that the scarring process can be directed to improving tissue regeneration suggesting a reduction on epidural fibrosis.

Disclaimer Statements

Contributors All authors contributed extensively to the work presented in this paper and discussed the results and implications and commented on the manuscript at all stages. Miguel Carvalho and Artur S. Vareja~o: designed the experiment. Miguel Carvalho, Luís M. Costa and José E. Pereira: performed the neurosurgeries. Yuki Shirotsaki, Satoshi Hayakawa, José D. Santos and Ana C. Maurício: developed the Hybrid chitosan membranes. Stefano Geuna, Federica Fregnan and António M. Cabrita: carried out the histological analysis. Artur S. Vareja~o: supervised the project.

Funding Project TRIBONE, No. 11458, co-financed by the European Community FEDER fund through ON2 – O Novo Norte – North Portugal Regional Operational Program 2007–2013 and from the program COMPETE – Programa Operacional Factores de Competitividade, project Pest-OE/AGR/UI0211/ 2011, and from project QREN I&DT Cluster in Development of Products for Regenerative Medicine and Cell Therapies – Biomat & Cell QREN 2008/1372.

Conflicts of interest None.

Ethics approval All procedures were performed with the approval of the Veterinary Authorities of Portugal in accordance with the European Communities Council Directive of 24 November 1986 (86/609/ EEC).

Acknowledgements The authors would like to acknowledge the financial support from Project TRIBONE, No. 11458, cofinanced by the European Community FEDER fund through ON2 – O Novo Norte – North Portugal Regional Operational Program 2007–2013 and from the program COMPETE – Programa Operacional Factores de Competitividade, project Pest-OE/AGR/ UI0211/2011, and from project QREN I&DT Cluster in Development of Products for Regenerative Medicine and Cell Therapies – Biomat & Cell QREN 2008/1372.

References

- 1 Koebbe CJ, Maroon JC, Abla A, El-Kadi H, Bost J. Lumbar microdiscectomy: a historical perspective and current technical considerations. *Neurosurg Focus*. 2002;13:E3.
- 2 Wenger M, Mariani L, Kalbarczyk A, Gro~ger U. Long-term outcome of 104 patients after lumbar sequestrectomy according to Williams. *Neurosurgery*. 2001;49:329–34; discussion 334–5.
- 3 Weinstein JN, Lurie JD, Tosteson TD, Tosteson AN, Blood EA, Abdu WA, et al. Surgical versus nonoperative treatment for lumbar disc herniation: four-year results for the Spine Patient Outcomes Research Trial (SPORT). *Spine (Phila Pa 1976)*. 2008;33:2789–800.
- 4 Rosner MK, Campbell VA. Treatment of disk disease of the lumbar spine. In: Winn HR, editor. *Youmans neurological surgery*. 6th ed. Philadelphia, PA: Elsevier Saunders Eds.; 2011. p. 2919–22.

- 5 Ehni BL, Benzel EC, Biscup RS. Lumbar discectomy. In: Benzel EC, editor. Spine surgery – techniques, complication avoidance, and management. 2nd ed. Philadelphia, PA: Elsevier Saunders Eds.; 2005. p. 601–18.
- 6 Javedan S, Sonntag VK. Lumbar disc herniation: microsurgical approach. *Neurosurgery*. 2003;52:160–2; discussion 162–4.
- 7 Ozer AF, Oktenoglu T, Sasani M, Bozkus H, Canbulat N, Karaarslan E, et al. Preserving the ligamentum flavum in lumbar discectomy: a new technique that prevents scar tissue formation in the first 6 months postsurgery. *Neurosurgery*. 2006;59(1 Suppl 1):ONS126–33; discussion ONS126–33.
- 8 Schofferman J, Reynolds J, Herzog R, Covington E, Dreyfuss P, O’Neill C. Failed back surgery: etiology and diagnostic evaluation. *Spine J*. 2003;3:400–3.
- 9 North RB, Campbell JN, James CS, Conover-Walker MK, Wang H, Piantadosi S, et al. Failed back surgery syndrome: 5year follow-up in 102 patients undergoing repeated operation. *Neurosurgery*. 1991;28:685–91.
- 10 Waguespack A, Schofferman J, Slosar P, Reynolds J. Etiology of long-termfailuresoflumbarspinesurgery. *PainMed*. 2002;3:18–22.
- 11 Ross JS, Robertson JT, Frederickson RC, Petrie JL, Obuchowski N, Modic MT, et al. Association between peridural scar and recurrent radicular pain after lumbar discectomy: magnetic resonance evaluation. ADCON-L European Study Group. *Neurosurgery*. 1996;38:855–61; discussion 861–3.
- 12 Dash M, Chiellini F, Ottenbrite RM, Chiellini E. Chitosan – A versatile semi-synthetic polymer in biomedical application. *Prog Polym Sci*. 2011;36:981–1014.
- 13 Shiroasaki Y, Tsuru K, Hayakawa S, Osaka A, Lopes MA, Santos JD, et al. Physical, chemical and in vitro biological profile of chitosan hybrid membrane as a function of organosiloxane concentration. *Acta Biomater*. 2009;5:346–55.
- 14 Shiroasaki Y, Okayama T, Tsuru K, Hayakawa S, Osaka A. Synthesis and cytocompatibility of porous chitosan-silicate hybrids for tissue engineering scaffold application. *Chem Eng J*. 2008;137:122–8.
- 15 Amado S, Simo~es MJ, Armada da Silva PAS, Lui’s AL, Shiroasaki Y, Lopes MA, et al. Use of hybrid chitosan membranes and N1E-115 cells for promoting nerve regeneration in an axonotmesis rat model. *Biomaterials*. 2008;29:4409–19.
- 16 Simo~es MJ, Amado S, Ga~rtner A, Armada-da-Silva PAS, Stefania Raimondo, Vieira M, et al. Use of chitosan scaffolds for repairing rat sciatic nerve defects. *Ital J Anat Embryol*. 2010;115:190–210.
- 17 Cortez PP, Shiroasaki Y, Botelho CM, Simo~es MJ, Gartner F, Gil da Costa RM, et al. Hybrid chitosan membranes tested in sheep for guided tissue regeneration. *Key Eng Mater*. 2008;361–36:1265–8.
- 18 Alkalay RN, Kim DH, Urry DW, Xu J, Parker TM, Glazer PA. Prevention of postlaminectomy epidural fibrosis using bioelastic materials. *Spine (Phila Pa 1976)*. 2003;28:1659–65.
- 19 Yu~cesoy K, Karci A, Kilic,alp A, Mertol T. The barrier effect of laminae: laminotomy versus laminectomy. *Spinal Cord*. 2000;3:442–4.

- 20 Su C, Sui T, Zhang X, Zhang H, Cao X. Effect of topical application of mitomycin-C on wound healing in a postlaminectomy rat model: an experimental study. *Eur J Pharmacol.* 2012;674:7–12.
- 21 Sangsanoh P, Suwantong O, Neamnark A, Cheepsunthorn P, Pavasant P, Supa-phol P. In vitro biocompatibility of electrospun and solvent-cast chitosan substrata towards Schwann, osteoblast, keratinocyte and fibroblast cells. *Eur Polym J.* 2010;46:428–40.
- 22 Chang JJ, Lee YH, Wu MH, Yang MC, Chien CT. Electrospun anti-adhesion barrier made of chitosan alginate for reducing peritoneal adhesions. *Carbohydr Polym.* 2012;88:1304–12.
- 23 Klopp LS, Welch WC, Tai JW, Toth JM, Cornwall GB, Turner AS. Use of polylactide resorbable film as a barrier to postoperative peridural adhesion in an ovine dorsal laminectomy model. *Neurosurg Focus.* 2004;16:E2.
- 24 Rodgers KE, Robertson JT, Espinoza T, Oppelt W, Cortese S, diZerega GS, et al. Reduction of epidural fibrosis in lumbar surgery with Oxiplex adhesion barriers of carboxymethylcellulose and polyethylene oxide. *Spine J.* 2003;3:277–83; discussion 284.
- 25 Cho Y, Borgens RB. Polymer and nano-technology applications for repair and reconstruction of the central nervous system. *Exp Neurol.* 2012;233:126–44.
- 26 Cho Y, Shi R, Borgens RB. Chitosan produces potent neuroprotection and physiological recovery following traumatic spinal cord injury. *J Exp Biol.* 2010;213:1513–20.
- 27 Zhou J, Lee JM, Jiang P, Henderson S, Lee TD. Reduction in postsurgical adhesion formation after cardiac surgery by application of N,O-carboxymethyl chitosan. *J Thorac Cardiovasc Surg.* 2010;140:801–6.
- 28 Sandoval-Sa´nchez JH, Ramos-Zu´n˜iga R, Luqui´n de Anda S, Lo´pez-Dellamary F, Gonzalez-Castan˜eda R, Ramı´rez-Jaimes JD, et al. A new bilayer chitosan scaffolding as a dural substitute: Experimental valuation. *World Neurosurg.* 2012;77:577–82.
- 29 Chuang JP, Chang CP, Shen HT, Kao J, Yan JL. Repair of the canine vertebral lamina with a combination of autologous micromorselized bone and poly-lactic acid gel after a total laminectomy. *Kaohsiung J Med Sci.* 2010;26:357–65.
- 30 Liu J, Ni B, Zhu L, Yang J, Cao X, Zhou W. Mitomycin Cpolyethylene glycol controlled-release film inhibits collagen secretion and induces apoptosis of fibroblasts in the early wound of a postlaminectomy rat model. *Spine J.* 2010;10:441–7.