

AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Ni80Fe20 nanodisks by nanosphere lithography for biomedical applications

This is a pre print version of the following article:

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/1576352> since 2022-04-01T16:24:45Z

Publisher:

20th INTERNATIONAL CONFERENCE ON MAGNETISM

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

Ni₈₀Fe₂₀ nanodisks by nanosphere lithography for biomedical applications

P. Tiberto¹, G. Barrera^{1,2}, F. Celegato¹, M. Coisson¹, G. Conta^{1,2}, F. Vinai¹, K. Martina³, M. Caporaso³, L. Serpe³, R. Canaparo³

¹INRIM, Electromagnetism Dept, Torino, Italy

²Chemistry Dept, Università di Torino, Torino, Italy

³Dipartimento di Scienza e Tecnologia del Farmaco, Università di Torino, Torino, Italy

Magnetic nanoparticles have been intensively studied for applications in data storage, contrast enhancement agents in magnetic resonance imaging, drug delivery systems and magnetic hyperthermia.

The magnetic moment is exploited for target-directed delivery, detection, separation, and manipulation. A number of recent publications describe the preparation of composite materials in which every component of a hybrid plays an equally significant role in biorecognition and targeting, multimodal imaging, and therapy.

The intrinsic difficulty of controlling nanoparticle dimension leads to not easily tunable magnetic properties. Bottom-down nanolithography process allows the production of nanodisks having different diameter and ferromagnetic properties.

In this work, the fabrication process together with room-temperature magnetic behavior of Ni₈₀Fe₂₀ nanodisk suspended in ethanol solution are presented. Arrays of nanodisks were obtained by polystyrene nanospheres nanolithography, as shown in the scheme reported in Fig. 1a together with the corresponding SEM images. Such a process is based on the self-assembling of commercially available polystyrene nanospheres (starting diameter 800 nm) on continuous thin films (thickness 30 nm) sputtered on a layer of optical resist. After depositing a monolayer of nanospheres on the film surface, spheres diameter is reduced by plasma in Ar. Subsequently, magnetic material among the nanospheres is removed by sputter-etching. The removal of the remaining spheres is performed by sonication. At this stage, the resist layer is dissolved in acetone resulting in freely nanodisks. After the complete removal of the polymer by several washings the nanodisks are dispersed in ethanol.

AFM/MFM images have been measured on all samples before the removal process. Magnetic vortex magnetisation process have been observed. Room-temperature magnetic hysteresis curves have been recorded at several stages of the process, as shown in Fig. 1b. The continuous film displays a typical soft magnetic behaviour. The patterning process leads to a hysteresis loop having the shape typical of magnetisation vortex nucleation with a higher coercive field. Free-standing nanodisks are characterised by an unsaturating magnetisation behaviour together with a non-zero coercivity that can be related to the high nanodisk diameter (around 600 nm).

To assess, in biomedical application, the suitability of the nanodisks in targeted drug delivery, chemical bioderivatization has been taken into account. Bioderivatization was aimed to the production of a nanoscaled functional material that combines multiple functionalities for enhanced therapeutic efficacy. The *in vitro* toxicity assessment of the nanodisks will be discussed.