



AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Energy and moisture losses during poplar and black locust logwood storage

This is the author's manuscript
Original Citation:
Availability:
This version is available http://hdl.handle.net/2318/1616651 since 2016-11-25T14:20:59Z
Published version:
DOI:10.1016/j.fuproc.2015.05.026
Terms of use:
Open Access
Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

Energy and moisture losses during poplar and black locust firewood logwood storage

- 3
- 4
- 5

6 Abstract

The main problem with firewood production is the same as for other wood biofuels: storage.
Usually, firewood is stored in logwood. The goal of this study was to determine the drying storage
dynamics of logwood used for firewood production under the typical work conditions forest

10 practise of southern Europe. Storage dynamics were evaluated for two different forestry tree species

11 (poplar and black locust) with logwood disposed in uncovered piles for a period of 180 days

12 (March–September). In this study, the effect of the diameter of logs and their position inside the pile

13 on wood drying was evaluated. In each treatment This evaluation was performed considering the

14 main key drying physical parameters were monitored – temperature (T), moisture content (MC),

15 heating value (HV) and dry matter (DM).

The study found that initial values of key parameters were different for both forestry species, but at the end of the storage period the values were considered to be similar (19 °C T, 19% MC, 14.30 MJ kg^{-1} LHV, no DM losses). No statistically significant differences were pointed out between logs with different diameter sizes and different positions in the pile. For this reason, drying firewood logwood in uncovered piles can be considered a good storage method irrespective of forestry species, the diameter of logs and the position of logs in the pile.

22

23

24 Keywords

25 firewood, logwood, moisture content, energy content, black locust, poplar

1. Introduction

3	Firewood is a form of energy wood that is still used today globally as an alternative to fossil fuel
4	[1]. This biofuel is used especially in developing countries [2]. In industrialised countries, in fact,
5	the widespread use of firewood is limited to only rural areas [3]. In Europe, chopped firewood is
6	still used more than any other industrial energy wood product [4], especially in northern countries
7	where its consumption covers between 20 and 25 % of the heating needs [5-6]. In southern Europe
8	(France and Italy), firewood is used, but to a lesser extent than in the rest of Europe [7].
9	
10	Firewood is preferred to other biofuel because its production process is easier and requires lower
11	investments [8]. Biofuel preparation requires only cross-cutting and splitting the logs extracted from
12	the forest [9]. This operation is even performed by individuals and small businesses or farmers that
13	carry out this activity on a part-time basis [10], not only in northern Europe [11], but also in
14	Southern Europe [12]. Irrespective of the region being considered, the production of chopped
15	firewood can play an important role in economic development where coppice forests are diffused
16	[13].
17	
18	The main problem with the commercialization of firewood is the same as for other wood biofuels:
19	the moisture content. When wood is harvested in forests its moisture content is higher and not very
20	suitable for <u>direct</u> use in small boilers and domestic stoves [14]. In fact, the quality of energy wood
21	is proportional to its calorific value, which is higher when the moisture content is lower [15].
22	Nevertheless, moisture losses can decrease significantly by storing energy wood in piles for a short
23	period of time only [16]. Until now, many works have focused on the storage dynamics of
24	woodchips. Some of these have studied the influence of the forestry species used for woodchip
25	production – poplar [17], Salix [18] or pine [19] – while others have analysed the effect of

woodchip pile weight [18], drying methods [20] and storage techniques used [21-22]. Little has
 been done regarding the storage of energy logwood.

3

4 In contrast to woodchips, drying logwood shows low dry matter losses (2% per year) [23] because during the storage period, microbial activities are lower than in comminuted wood [24]. Another 5 advantage of drying logwood is the economic benefit. In fact, drying wood for energy with this 6 method showed an increase in its market value of 14,40 $\in t^1$ after five months [16]. In recent years, 7 some experimentations were focused on logwood storage dynamics, especially in terms of moisture 8 content [16, 25-26], but all of these were carried out in northern Europe where the work conditions 9 forest practises are different to those in southern Europe. In fact, in northern Europe, firewood is 10 obtained from logs of 2–6 m in length, while in southern Europe it is obtained from logs 1–2 m 11 long, due to the different extraction methods [27-28]. 12

13

On the basis of this, the goal of this study was to determine the drying storage dynamics of logwood
used for firewood production under the typical work conditions forest practises of southern Europe.
In particular, the storage dynamics of drying logwood in piles were evaluated for two different
forestry tree species.

18

19 **2. Materials and methods**

20

This experiment was carried out at Moncalieri in Turin/Italy (45°00'31''N, 7°42'53''; 356 m above
sea level). The study was conducted during 2014 and it lasted for six months (March–September).
In Italy, <u>this period correspond to the usual firewood storage</u> because the wood is harvested until

24 March and starts being used from September.

Generally in Italy, firewood is produced by from only high-density tree species, but in this work, in
order to establish eventual differences in drying dynamics, tests were carried out using both highdensity tree species (black locust – *Robinia pseudoacacia*) and low-density tree species (poplar – *Populus x euroamericana*). Hybrid poplar and black locust are most common on North Italian
farmland and normally used for energy production, which is why they can be considered
representative of the two wood categories [29].

7

8 Storage dynamics were assessed through variations in moisture and temperature taking into account
9 different logs' diameter and position in the pile. Temperature and moisture content are reliable
10 indicators of wood storage performance used for energy production [30]. Therefore, moisture
11 content and temperature inside the logs were monitored over the whole storage period, which began
12 in March with the preparation of logs and ended in September with usage of the wood.

13

In order to maintain logs in the same position over the whole storage period, in this experiment 14 15 moisture content was not determined by gravimetric method, but was monitored by a digital hygrometer (accuracy of ‰) normally used in sawmills (GANN®Hydromette HT85T). This device, 16 designed for registering external moisture, presents a probe with two short steel electrodes (20 mm). 17 18 Since in the test the measurement point was D/2 for each diameter class, specific probes with steel electrodes of different lengths were made. In order to obtain only the moisture measurement at the 19 top of the probe (half of the log diameter), the electrodes were covered with electrical tape up to 5 20 21 mm from its top. The probes were positioned at the middle length of the logs (about 1 m from the head). All logs used in the test had a length of about 2 metres because this is a common length that 22 23 is commercialized in unprocessed energy wood in Italy [27].

The temperature was measured by thermocouples placed near the probes for determining moisturecontent.

1	The influence of log diameter on wood drying was evaluated by monitoring the moisture content of
2	logs of different diameters (50, 100, 150, 200 and 250 mm).

All logs, equipped with thermocouples and probes, were placed outdoors on two transversal logs
positioned on the soil at a distance of 300 mm apart. The logs were placed with their longitudinal
axis orientated south-north and left uncovered for the entire storage period. Data were collected

6 every three days for the first 30 days, thereafter every 15 days (Fig. 1).

For each diametric class and for each forestry tree species, measurements were carried out on three
different logs (three repetitions). Table 1 reports the experimental design.

9

11

10 The influence of the position of logs in the pile on drying wood was analysed by making two

uncovered piles (one of poplar and one of black locust) on naked soil and aligning their longer axis

12 in an east-west direction. <u>The experimentation was conducted with uncovered piles made on naked</u>

13 soil because this is the usually forest practice used for logwood storage in all European countries

14 [25-26]. A single pile had a volume of approximately 60 m^3 (12 m long, 2 m wide and 3 m high).

15 The wood moisture content was measured by a probe prototype described in a previous test. Each

16 probe was placed halfway (1 m) along the logs and was 150 mm in diameter and 2 metres in length.

17 The reading of moisture content was performed only at the mid-diameter of the logs.

18

1.5, 2.0, 2.5 and 3.0 metres). At each sampling height three logs were positioned at a distance of 1
metre apart (Fig. 2).

22

The complete experimental design consisted of 21 replicates per forestry tree species (poplar and
black locust) (Table 2).

Near the piles, a weather station was installed in order to monitor air temperature (°C), air humidity
 (%), precipitation (mm) and wind speed (ms⁻¹) at 1 h intervals. All measuring components were
 installed at a height of 1.7 m to 2.2 m.

4

Finally, in order to establish the logwood storage benefits, at the beginning and at the end of the test 5 period the heating value (lower and higher) and dry matter losses of logs were determined. Heating 6 7 value was determined according to European Standard UNI EN 14918 [31]. In detail, Higher 8 Heating Value (HHV) was tested using an oxygen bomb calorimeter. For this measurement, the wood sample taken from the logs did not show the presence of bark. Dry matter losses were 9 10 determined for each log diameter class and forestry species (10 treatments with 3 replicates). Each log was weighed at piling, and then at the end of the storage period. For this test, moisture content 11 was determined with the gravimetric method according to European standard UNI EN 14774-2 [32] 12 13 because this is more reliable and accurate than probes set up for periodic measurements (previously described) [33]. Initial moisture content was determined using a cutting an end portion of the logs 14 15 (150 mm), while the final value was determined by cutting a central portion (150 mm) of the logs. 16 Data were processed with the SPSS statistical software, adopting a significance level of a = 0.05, in 17

Data were processed with the SPSS statistical software, adopting a significance level of a = 0.05, in
order to check on the statistical significance of eventual differences between treatments. In detail,
the SSPS software was used to perform typical analysis of variance (ANOVA) in order to see how
the sum of square was divided between main effects, interactions and residuals.

21

22 **3. Results**

23

During the investigation period of 180 days, air temperature ranged from 5 to 25 °C, with a mean value of 17 °C. The mean wind speed was 0.52 ms⁻¹ during the test period. The maximum wind speed was 6.71 ms⁻¹ and the dominating wind direction was from the south-east. The relative humidity was fairly constant, with a monthly average of between 75% and 83%, and highs during
rain events (Fig. 3). In all periods considered, only liquid precipitations were felled. In all, a total of
370 mm was absorbed. Rain was distributed across a dozen main events, each contributing about 9–
27 mm precipitation.

5

6 The different forestry tree species tested showed different initial moisture content: approximately 7 60% for poplar and about 45% for black locust. Nevertheless, both species displayed a similar 8 moisture loss trend in which the higher values were observed in the first 30 days. At the end of the 9 storage period considered, irrespective of forestry investigated tree species, all logs had an average 10 moisture content of about 19% (Fig. 4).

11

In the firsts 30 days of storage, moisture losses for poplar logwood were inversely proportional to the diameter of the logs. In fact, the highest loss value (61%) was observed for the smallest diameter (50 mm), while the lowest moisture (46%) was observed for the biggest diameter (250 mm). Considering a storage period between 60 and 180 days, the moisture losses were similar for all diameters (Table 3).

17

This trend was also true for black locust logwood. However, in this case, moisture losses were
lower (from 14% to 26%) than for same-diameter poplar logs due to lower initial moisture content
(25%). After 60 days of storage, the moisture content of about 20% of the logs was tested and no
difference between logs with different diameters was observed (Table 3).

22

In the "log position" test carried out with poplar wood a significantly different moisture loss from

logs placed at different heights from the ground in the first 30 days of storage was observed.

25 Nevertheless, this difference was clearly visible only in the first 10 days where logs near the soil

were highlighted as lower drying (35%) than those positioned at a higher height (42%). Also in this

case, after a storage period of 60 days, all logs showed a similar moisture content below 20% (Table
 2).

4	Similar results were obtained using black locust logs. In fact, considering the same storage period of
5	10 days, the moisture loss variance between logs near the soil and others placed at a higher level
6	was similar (5%) to that of poplar (7%). No differences between the moisture content of logs were
7	observed after 60 days of stacking (Table 4).
8	
9	At the end of the storage period considered (180 days), data processing highlighted no statistical
10	differences between the forestry-tree species, diameter size and position in the pile of logs (Table 5).
11	
12	Similar values were also obtained after 60 days of storage, but in this case there was a significant
13	difference between the forestry tree species where the poplar wood showed a higher moisture
14	content than the black locust (Table 6).
15	
16	During the test, all logs showed similar internal temperature values to air temperature values in all
17	treatments tests. Initially, internal log temperatures were about 3 °C, while at the end of the storage
18	period the temperatures increased to about 20 °C.
19	No statistical differences between values recorded by thermocouples placed among the poplar logs
20	and values read by the weather station were observed in either test type performed ("log diameter"
21	and "log position"). The same dynamics were recorded with the black locust logs. Data processing
22	also showed no significant value differences between poplar and black locust (Tables 7 and 8).
23	Table 7: Air temperature and internal temperature of logs of 100 mm in diameter of different
24	forestry species placed at different heights in the pile during whole storage period.
25	Poplar, with an average of 18.74 MJ kg ⁻¹ , showed an initial HHV higher than black locust, which
26	obtained only an average value of 18.04 MJ kg ⁻¹ . On the other hand, initial LHV was high for black

1	locust (7.75 MJ kg ⁻¹) and low for poplar (7.05 MJ kg ⁻¹). At the end of the storage period, no
2	significant variations were obtained in HHV values, while substantial variations were observed in
3	LHV values. In detail, final LHV values were similar for all forestry tree species and treatment test
4	reaching an average value of 14.40 MJ kg ⁻¹ . This values trend highlighted an LHV increase of
5	approximately 100% for poplar and of 84% for black locust. Diameter size and log position inside
6	the pile did not influence the final LHV values (Tables 9 and 10).
7	
8	Table 11 shows the mean dry matter weight of logs with different diameters at the beginning and at
9	the end of the storage period. No differences between initial and final values were statistically
10	significant for either of the forestry tree species tested.
11	
12	4. Discussion
13	
13 14	With regard to the initial moisture content of the different forestry tree species tested, the values
13 14 15	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species
13 14 15 16	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in
13 14 15 16 17	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario.
13 14 15 16 17 18	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario.
13 14 15 16 17 18 19	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario.
13 14 15 16 17 18 19 20	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario.
13 14 15 16 17 18 19 20 21	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario. In this work, the moisture content of logs rapidly decreased in the first 30 days of storage. These results are also comparable with the findings of another study carried out in Michigan [26], but in contrast, the wood moisture content decreased for all storage period. This is probably due to the
13 14 15 16 17 18 19 20 21 22	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario. In this work, the moisture content of logs rapidly decreased in the first 30 days of storage. These results are also comparable with the findings of another study carried out in Michigan [26], but in contrast, the wood moisture content decreased for all storage period. This is probably due to the drier climate of Italy, which makes water transfer between wood and air easy and does not permit
 13 14 15 16 17 18 19 20 21 22 23 	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario. In this work, the moisture content of logs rapidly decreased in the first 30 days of storage. These results are also comparable with the findings of another study carried out in Michigan [26], but in contrast, the wood moisture content decreased for all storage period. This is probably due to the drier climate of Italy, which makes water transfer between wood and air easy and does not permit remoistening of the biomass [35-36]. A similar trend was also observed in woodchip storage where
 13 14 15 16 17 18 19 20 21 22 23 24 	With regard to the initial moisture content of the different forestry tree species tested, the values obtained in this work are in line with another study carried out with the same forestry tree species [21]. The significant difference in logwood moisture content between the poplar and black locust in the first 60 days of the storage period is similar to that found by Gautam et al [34] in Ontario. In this work, the moisture content of logs rapidly decreased in the first 30 days of storage. These results are also comparable with the findings of another study carried out in Michigan [26], but in contrast, the wood moisture content decreased for all storage period. This is probably due to the drier climate of Italy, which makes water transfer between wood and air easy and does not permit remoistening of the biomass [35-36]. A similar trend was also observed in woodchip storage where experiments carried out in Italy [17, 21] showed better results in terms of wood moisture content

than works practices performed in northern Europe [37-38].

Values obtained in <u>during</u> the first 20 days are similar to those reported by Petterson and Nordfiell
 [39] in Sweden during a storage forestry logging residues and young tree storage in summer.

3

In this study, the moisture content was uniform from top to bottom of the piles for most of the 4 storage period (30-180 days). In contrast, Gingler et al [35] found that the top of the pile has a 5 higher moisture content, while Roser et al [40] reported that the wood moisture content of a pile 6 decreases from top to bottom. This could be attributed to a wetter climate where the experiment was 7 8 carried out: rainfall can heavily affect biomass moisture content [41]. In contrast, in another study it was pointed out that the bottom layers of the pile showed a higher wood moisture content due to 9 10 lower ventilation and soil moisture [42]. On the basis of this, it is possible to assert that the environmental conditions influenced the drying of the biomass because they interact significantly 11 12 with water evaporation and wood moisture content [43].

13

Moreover, in this work it is pointed out that the diameter of logwood did not interfere with wood drying when the storage period was more than 30 days long. Also, in this case, results are similar to those found by Gautam et al [34], although in their study only branches with diameters higher and lower than 40 mm were compared. In this regard, readers must remember that the short length (2 metres) of the logs considered in this experiment may have facilitated the water evaporation from wood irrespective of diameter.

20

No treatments tests showed any difference between air temperature and temperature values inside the logs. This can be considered as an indication of the absence of biological activities inside the logs/piles, which can be the main cause of dry matter losses [37]. In fact, in this study no dry matter losses were observed in the whole storage period. Such storage dynamics were foreseeable because in previous works drying logwood showed low dry matter losses (2% per year) [23] due to low microbial activities [24].

In this study, initial HHV values are in line with those found by Carmona et al [44]. In light of the 2 absence of statistical variation between initial and final HHV values for both forestry species tested, 3 4 it is possible to assert that during the storage period the wood energy content does not change. This values trend is similar to that observed in other experiments [34, 26], but in contrast with other 5 studies [45-46] where authors assert that the HHV is maintained only during the first 4 months and 6 7 later decreases because the biodegradation process changes the chemical composition of the wood. 8 Results obtained in this work are supported by the effectively restricted microbial activity due to fast wood drying that caused a biomass moisture content of lower than 20% after only 60 days [47]. 9

10

In general, logwood storing was carried out very efficiently because of the biomass increasing its
LHV by between 83 and 100 % in six months respectively for black locust and poplar. These values
were obtained irrespective of the diameters and log positions in the pile. Similar values were found
in other works carried out with hardwood [34, 48].

15

16 **5.** Conclusions

The study found that the initial value of moisture content was different for poplar and black locust, 17 but at the end of the storage period the values were considered to be similar (approximately 19%). 18 In addition, logs placed in different layers obtained a uniform moisture content because ground soil 19 20 and rainfall did not increase the presence of water at the bottom and top of the log pile. No statistically significant differences were pointed out either between logs with different diameters. 21 22 Moreover, the study has pointed out that wood could be considered dried after only 60 days of storing because the values observed in this period are similar to those recorded after 180 days. 23 24 Similar performances were also obtained in heating value evaluation; in fact, over six months the low heating value can increase to 100%. 25

1 On the basis of these considerations, it is possible to assert that drying firewood logwood in

2 uncovered piles showed a good performance in terms of moisture content, heating values and

3 energy content irrespective of log diameter size and position in the pile. Nevertheless, the results

4 obtained in this work are valid only in a dry climate closed to southern Europe.

5

6 **References**

- 7 [1] Guo M, Song W, Buhain J. Bioenergy and biofuel: History, status and perspective. Renewable
 8 and Sustainable Energy Reviews 2015;42:712-725.
- 9 [2] Keam S, McCormick N. Implementing sustainable bioenergy production; a compilation of tools
 and approaches. IUCN, Gland, Switzerland (2008) 1-32.
- [3] Lillemo S, Halvorsen B. The impact of lifestyle and attitudes on residential firewood demand in
 Norway. Biomass and Bioenergy 2013;57:13-21.
- [4] Nybakk E, Lunnan A, Jenssen J, Crespell P. The importance of social networks in the
 Norwegian firewood industry. Biomass and Bioenergy 2013;57:48-56.
- 15 [5] Halder P, Pietarinen J, Havu-Nuutinen S, Pelkonen P. Young citizens'knowledge and
- 16 perceptions of bioenergy and future policy implications, Energy Policy 2010;38:3058-3066.
- 17 [6] Lindroos O. Residential use of firewood in Northern Sweden and its influence on forest biomass
- resources, Biomass and Bioenergy 2011;35:385-390.
- 19 [7] Elyakime B, Cabanettes A. Financial evaluation of two models for energy production in small
- 20 French farm forests, Renewable Energy 2013;57:51-56.
- 21 [8] Manzone M, Spinelli R. Efficiency of small-scale firewood processing operations in Southern
- Europe. Fuel Processing Technology 2014;122:58-63.
- 23 [9] Lindroos O. The effects of increased mechanization on time consumption in small-scale
- firewood processing. Silva Fennica 2008;42:791-805.
- 25 [10] Kärhä K, Jouhiaho A. Producing chopped firewood with firewood processors. Biomass and
- 26 Bioenergy 2009;33:1300-1309.

1	[11] Seppänen A, Kärhä K. The chopped firewood trade in Finland. TTS Institute, Forestry Bulletin
2	2003;662:1-6.

- [12] Spinelli R, Magagnotti N, Facchinetti D. Logging companies in the European mountains: an 3 example from the Italian Alps. International Journal of Forest Engineering 2013. DOI: 4 10.1080/14942119.2013. 838376. 5 [13] B. Lasserre, G. Chirici, U. Chiavetta, V. Garfi`, R. Tognetti, R. Drigo, P. DiMartino, M. 6 7 Marchetti, Assessment of potential bioenergy from coppice forests trough the integration of 8 remote sensing and field surveys, Biomass and Bioenergy 2011;35:716-724. [14] Nurmi J. The storage of logging residue for fuel. Biomass Bioenergy 1999;17:41-7. 9 10 [15] Hartmann H, Kaltschimitt M. Energie aus Biomasse: Grundlagen, Techniken und Verfahren. Springer Verlag. Berlin-Heidelberg-New York 2001. 770 p. 11 [16] Erber G, Kanzian C, Stampfer K. Predicting moisture content in a pine logwood pile for energy 12 13 purpuses. Silva Fennica 2012;46(4):555-567. [17] Barontini M, Scarfone A, Spinelli R, Gallucci F, Santagelo E, Acampora A, Jirjis R, Civitarese 14 15 V, Pari L. Storage dynamics and fuel quality of poplar chips. Biomass Bioenergy 2014;62:17-25. 16
- [18] Jirjis R. effects of particle size and pile height on storage and fuel quality of comminuted salix
 viminalis. Biomass bioenergy 2005;28:193-201.
- [19] Casal MD, Gil MV, Pevida C, Rubiera F, Pis JJ. Influence of storage time on the quality and
 combustion behaviour of pine woodchips. Energy 2010;35:3066-3071.
- [20] Le Lostec B, Galanis N, Baribeault J, MilletteJ. Wood chip drying with an adsorption heat
 pump. Energy 2008;33:500-512.
- [21] Manzone M, Balsari P, Spinelli R. Small-scale storage techniques for fuel chips from short
 rotation forestry. Fuel 2013;109:687-692.
- 25 [22] Ergul E, Ayrilmis N. Effect of outdoor storage conditions of wood chip pile on the
- technological properties of wood-based panel. Biomass Bioenergy 2014;61:66-72.

1	[23] Golser M, Pichler W, hader F. Energieholztrocknung. Holzforschung Austria 2005: 138 p.
2	[24] Petterson M, Nordfiell T. Fuel quality changes during seasonal storage of compacted logging
3	residues and young trees. Biomass Bioenergy 2007;11:782-792.
4	[25] Erber G, Routa J, Kolstrom M, Kanzian C, Sikanen L, Stampfer K. Comparing two different
5	Approaches in modelling small diameter energy wood crying in logwood piles. Croatian
6	Journal of Forestry Engineering 2014;35(1):15-22.
7	[26] Lin Y, Pan F. Effect of in-wood storage of unprocessed logging residue on biomass feedstock
8	quality. Forest products journal 2013;63:119-124.
9	[27] Magagnotti N, Pari L, Spinelli R. Re-engineering firewood extraction in traditional
10	Mediterranean coppice stands, Ecological Engineering 2012;38:45-50.
11	[28] Zimbalatti G, Proto A. Cable logging opportunities for firewood in Calabrian forests.
12	Biosystems Engineering 2009;102:63-68.
13	[29] Facciotto G, Bergante S, Lioia C, Mughini G, Rosso L, Nervo G. Come scegliere e coltivare le
14	colture da biomassa, Supplemento Forlener L'informatore Agrario 2005;34:27-30 (in italian).
15	[30] Fuller W. Chip pile storage – a review of practices to avoid deterioration and economic losses.
16	TAPPI J 1985;68:48-52.
17	[31] UNI EN 14918. Solid biofuels, determination of calorific value; 2010.
18	[32] UNI EN 14774-2. Solid biofuels, determination of moisture content – oven dry method, Part 2:
19	total moisture - simplified method 2010.
20	[33] Samuelsson R, Burvall, Jirjis R. Comparison of different methods for the determination of
21	moisture content in biomass. Biomass Bioenergy 2006;30:929-934.
22	[34] Gautam S, Pulkki R, Shahi C, Leitch M. Fuel quality changes in full tree logging residue
23	during storage in roadside slash piles in Northwestern Ontario. Biomass Bioenergy 2012;42:43-
24	50.
25	[35] Gigler JK, Van Loon WKP, Van den Berg JV, Sonneveld C, Meerdink G, 2000. Natural wind
26	drying of willow stems. Biomass Bioenergy 19;3:153-163.

[36] Steele PH, Mitchell BK, Cooper JE, Arora S. Bundled slash: a potential new biomass resource
 for fuels and chemicals. Appl. Biochem. Biotechnol 2008;148(1):1-13.

3 [37] Jirjis R. Storage and drying of wood fuel. Biomass Bioenergy 1995;9:181-190.

- 4 [38] Jirjis R, Thelander O. The effect of seasonal storage on the chemical composition of forest
 5 residue chips, Scand J For Res 1990;5:437-448.
- [39] Pettersson M, Nordfjell T. Fuel quality changes during seasonal storage of compacted logging
 residues and young trees. Biomass Bioenergy 2007;31:782-792.
- 8 [40] Roser D, Mola-Yudego B, Sikanen L, Prinz R, Gritten D, Emer B, Vaatain K, Erkkila A.
- 9 Natural drying treatments during seasonal storage of wood for bioenergy in different European
- 10 locations. Biomass Bioenergy 2011;35:4238-4247.
- [41] Pan F, Han HS, Johnson L, Elliot W. Net energy output from harvesting small-diameter trees
 using a mechanized system. Forest Prod J. 2008;58(1/2):25-30.
- [42] Filbakk T, Olav H, Nurmi J. Modeling natural drying efficiency in covered and uncovered
 piles of whole broadleaf trees for energy use. Biomass Bioenergy 2011;35:454-463.
- 15 [43] Bedane AH, Afzal MT, Sokhansanj S. Simulation of temperature and moisture changes during
- storage of woody biomass owing to weather variability. Biomass Bioenergy 2011;35:3147-

17 3151.

18 [44] Carmona R, Nuñez T, Alonso MF. Biomass yield and quality of an energy dedicated crop of

19 poplar (Populus spp.) clones in the Mediterranean zone of Chile. Biomass Bioenergy

20 2015;74:96-102.

- [45] Brand MA, Bolzon de Muniz GI, Quirino WF, Brito JO. Storage as a tool to improve wood
 fuel quality. Biomass Bioenergy 2011;35:2581-2588.
- [46] Nurmi J. The effect of whole-tree storage on the fuelwood properties of short-rotation Salix
 crops. Biomass Bioenergy 1995;8:245-249.
- 25 [47] Hudson H. Fungal Biology. Great Britain: Cambridge University Press;1992, 305 pp.

- 1 [48] Hakkila P. utilization of residual forest biomass. Berlin, Heidelberg, New York: springer;
- 2 1989.
- 3

1 Figures





4 Fig. 1: Placement of logs during the test.

5



3 Fig. 2: Position of logs with probes in the pile.



2 Fig. 3: Weather data recorded during the storage period.







1 Tables

2

Diameter	logs (n°)				
(mm)	Poplar	Black locust			
50	3	3			
100	3	3			
150	3	3			
200	3	3			
250	3	3			

3 Table 1: Experimental design for determining the influence of logs' diameter on wood drying

4

1 Table 2: Experimental design for determining the influence of logs' position in the pile on wood

2 drying

Sampling	logs (n°)					
height (m)	Poplar	Black locust				
0.0	3	3				
0.5	3	3				
1.0	3	3				
1.5	3	3				
2.0	3	3				
2.5	3	3				
3.0	3	3				

3

Caralia	Diameter					Storage	days (n°)			
Species	(mm)	-	1	5	10	20	30	60	120	180
	50	Mean	60a	42a	35a	30a	23a	20a	19a	19a
		SD	0.58	1.52	0.58	2.00	1.00	1.52	1.52	0.58
		MCR (%)	-	31	43	50	61	66	68	69
	100	Mean	60a	40ab	37b	32b	25b	19a	18a	18a
		SD	0.58	1.15	1.00	0.58	0.58	1.00	0.58	1.00
		MCR (%)	-	33	40	47	59	69	70	70
	150	Mean	61a	44b	39c	31b	28bc	20a	19a	18a
Poplar		SD	1.15	1.00	1.00	1.74	1.52	0.58	1.00	0.58
		MCR (%)	-	27	36	49	54	66	69	71
	200	Mean	61a	47c	41c	35c	31cd	21a	19a	18a
		SD	1.15	1.00	1.52	0.58	1.00	1.00	1.00	0.58
		MCR (%)	-	23	32	43	49	65	69	70
	250	Mean	61a	48c	44d	36c	33d	22a	20a	19a
		SD	0.58	0.58	0.58	0.58	1.00	1.00	1.52	0.58
		MCR (%)	-	20	27	40	46	65	68	69
	50	Mean	46a	34a	30a	25a	21a	19a	18a	18a
		SD	0.58	0.58	1.15	0.58	1.00	0.58	1.00	1.00
		MCR (%)	-	25	34	45	54	59	61	61
	100	Mean	45a	34a	31ab	27b	23b	18a	18a	18a
		SD	1.00	1.52	1.00	0.58	1.15	1.00	0.58	1.52
		MCR (%)	-	24	31	41	50	60	59	59
	150	Mean	45a	38b	34c	30c	27c	20a	19a	18a
Black		SD	1.00	1.00	0.58	1.00	0.58	0.58	0.58	0.58
locust		MCR (%)	-	16	25	33	39	56	59	59
	200	Mean	46a	42c	36d	33d	29cd	20a	19a	19a
		SD	0.58	0.58	2.08	1.00	1.52	0.58	0.58	1.00
		MCR (%)	-	9	20	28	36	53	59	59
	250	Mean	46a	43c	38e	34d	30d	21a	19a	19a
		SD	1.00	1.00	1.00	1.15	0.58	1.00	0.58	0.58
		MCR (%)	-	7	17	27	34	54	59	57

Table 3: Moisture content of logwood with different diameters during whole storage period 1

Notes: SD = Standard Deviation; MCR = Moisture Content Reduction Different letters indicate significant differences between treatments for $\alpha = 0.05$.

1 Table 4: Internal moisture of logs of 100 mm in diameter of different forestry tree species placed at

2 different heights in the pile during whole storage period

Species	Height		Storage days (n°)							
	(m)	-	1	5	10	20	30	60	120	180
	0.0	Mean	61a	50a	40a	33a	26a	20a	20a	19a
		SD	1.52	1.52	1.15	1.00	1.52	0.58	1.00	0.58
		MDR (%)	-	17	35	46	57	66	66	69
	0.5	Mean	60a	48b	37b	31b	25ab	19a	18a	18a
		SD	0.58	0.58	1.00	0.58	0.58	2.00	0.58	0.58
		MDR (%)	-	20	38	47	59	68	69	69
	1.0	Mean	60a	42c	35c	30b	23b	19a	18a	18a
		SD	0.58	1.15	1.00	0.58	0.58	1.00	0.58	1.00
		MDR (%)	-	31	42	50	61	69	70	70
	1.5	Mean	59a	41c	36bc	31b	23b	19a	18a	18a
Poplar		SD	1.15	0.58	0.58	0.58	1.00	1.52	0.58	0.58
•		MDR (%)	-	30	39	47	61	67	70	71
	2.0	Mean	60a	41c	35c	30b	24b	19a	17a	18a
		SD	0.58	1.00	1.00	0.58	0.58	1.52	0.58	0.58
		MDR (%)	-	31	41	49	60	68	71	70
	2.5	Mean	60a	41c	34c	31b	24b	20a	18a	19a
		SD	0.58	1.00	0.58	1.00	0.58	1.00	0.58	0.58
		MDR (%)	-	32	43	49	61	67	70	69
	3.0	Mean	59a	42c	34c	31b	23b	20a	19a	18a
		SD	0.58	1.00	0.58	0.58	1.15	1.15	0.58	1.00
		MDR (%)	-	29	42	47	62	67	69	70
	0.0	Mean	44a	39a	32ab	26ab	23a	20a	20a	19a
		SD	1.15	0.58	0.58	1.00	1.15	0.58	1.15	1.00
		MDR (%)	-	11	28	40	48	55	54	58
	0.5	Mean	45a	37b	31b	26ab	22a	18a	18a	19a
		SD	1.00	1.52	0.58	1.00	1.00	1.00	0.58	1.00
		MDR (%)	-	17	32	42	51	60	59	58
	1.0	Mean	45a	34c	31b	27a	23a	18a	18a	18a
		SD	1.00	1.52	1.00	0.58	1.15	1.00	0.58	1.52
		MDR (%)	-	24	31	41	50	60	59	59
Dissis	1.5	Mean	44a	39a	31b	26ab	23a	18a	18a	18a
Black		SD	1.52	1.00	1.00	1.52	1.15	1.52	1.00	1.00
locust		MDR (%)	-	21	29	40	48	60	59	59
	2.0	Mean	45a	35bc	30b	25b	21ab	18a	17a	19a
		SD	0.58	1.15	1.00	1.15	0.58	1.52	0.58	1.15
		MDR (%)	-	22	33	45	54	60	61	58
	2.5	Mean	44a	33c	31b	26ab	22a	18a	18a	19a
		SD	1.52	1.15	0.58	1.15	1.15	1.15	0.58	0.58
		MDR (%)	-	24	30	40	49	60	58	56
	3.0	Mean	45a	35c	30b	25b	20ab	18a	19a	19a
		SD	1.15	0.58	1.52	0.58	0.58	0.58	1.15	1.52
		MDR(%)	_	22	32	45	54	50	58	58

Notes: SD = Standard Deviation; MCR = Moisture Content Reduction

Different letters indicate significant differences between treatments for $\alpha = 0.05$.

		DF	SS	%	F-Value	P-Value
Log position	Species	1	2.380	6	2.43	0.129
	Position	6	7.286	19	1.24	0.314
	Interaction	6	1.285	4	0.21	0.967
	Residual	28	27.333	71		
Log diameter	Species	1	0.592	2	0.65	0.423
	Size	6	5.282	15	0.97	0.456
	Interaction	4	1.764	5	0.49	0.742
	Residual	30	27.000	78		

1 Table 5: ANOVA table for diameter and position of logs at end of storage period (180 days)

Statistically significant interval = 0.05

3

		DF	SS	%	F-Value	P-Value
Log position	Species	1	20.024	24	11.68	0.014
	Position	6	11.000	14	1.06	0.404
	Interaction	6	2.809	3	0.27	0.944
	Residual	28	48.000	59		
Log diameter	Species	1	1.333	2	0,82	0,026
	Size	6	15.750	21	1,63	0,173
	Interaction	4	8.117	11	1,25	0.307
	Residual	30	48.333	66		

1 Table 6: ANOVA table for diameter and position of logs 60 days after pile building

Statistically significant interval $\alpha = 0.05$

1 Table 7: Air temperature and internal temperature of logs of different forestry tree species placed at

2	different	heights	in the	pile	during	whole	storage perio	bc
---	-----------	---------	--------	------	--------	-------	---------------	----

						Storage (da	ys)			
	Height (m	ı)	1	5	10	20	30	60	120	180
Air		mean	3.0	8.9	8.9	12.8	13.8	15.5	19.7	19.3
	0.0	mean	2.5	8.8	8.3	12.3	13.3	15.6	20.0	19.5
		SD	0.44	0.26	0.46	0.31	0.46	0.17	0.20	0.20
	0.5	mean	2.7	8.7	8.4	12.5	13.5	15.5	19.7	19.6
		SD	0.36	0.40	0.26	0.32	0.42	0.46	0.31	0.10
	1.0	mean	2.9	8.8	8.5	12.9	13.2	15.7	19.7	19.2
		SD	0.25	0.38	0.32	0.30	0.35	0.40	0.26	0.15
Domlar	1.5	mean	3.0	9.1	8.6	9.6	13.4	15.6	19.9	19.5
Poplar		SD	0.1	0.42	0.15	5.52	0.47	0.06	0.12	0.26
	2.0	mean	2.8	8.4	8.6	12.5	13.5	15.5	19.7	19.2
		SD	0.21	0.25	0.06	0.46	0.31	0.15	0.10	0.10
	2.5	mean	2.8	8.9	8.2	12.6	13.4	15.7	19.8	19.1
		SD	0.20	0.25	0.10	0.30	0.51	0.26	0.10	0.25
	3.0	mean	2.9	8.8	8.1	12.5	13.6	15.4	19.5	19.3
		SD	0.25	0.26	0.20	0.10	0.20	0.20	0.06	0.47
	0.0	mean	2.4	8.5	8.1	12.4	13.4	15.5	19.9	19.5
		SD	0.15	0.10	0.40	0.59	0.52	0.35	0.25	0.15
	0.5	mean	2.5	8.8	8.5	12.4	13.6	15.3	19.6	19.5
		SD	0.51	0.25	0.06	0.42	0.55	0.31	0.32	0.32
	1.0	mean	2.9	8.6	8.3	12.7	13.3	15.4	19.6	19.3
		SD	0.31	0.55	0.15	0.21	0.46	0.40	0.26	0.15
Plack locust	1.5	mean	2.7	8.7	8.4	9.4	13.4	15.4	19.7	19.5
Black locust		SD	0.53	0.42	0.30	5.37	0.40	0.35	0.42	0.21
	2.0	mean	2.8	8.8	8.4	12.4	13.8	15.3	19.5	19.3
		SD	0.21	0.36	0.29	0.32	0.15	0.25	0.36	0.12
	2.5	mean	2.5	8.7	8.3	12.5	13.5	15.4	19.6	19.1
		SD	0.36	0.47	0.25	0.28	0.58	0.40	0.38	0.29
	3.0	mean	2.8	8.5	8.1	12.4	13.8	15.2	19.3	19.2
		SD	0.32	0.45	0.21	0.25	0.15	0.35	0.26	0.35

 SD
 0.32
 0.45
 0.21
 0.25
 0.15
 0.55
 0.20
 0.55

 Note: SD = Standard Deviation; statistical analysis could not detect any significant difference between readings taken inside the logs placed at different heights in the pile and by the weather station (air); values in the table represent the average of the three individual readings obtained in three different logs for each treatment.

1 Table 8: Air temperature and internal temperature of logs with different diameters and of different

2 forestry tree species during whole storage period

	Storage (days)									
diameter (mm)			1	5	10	20	30	60	120	180
Air mean		3.0	8.9	8.9	12.8	13.8	15.5	19.7	19.3	
	50	mean	2.7	8.7	8.5	12.6	13.6	15.4	19.8	19.3
		SD	0.51	0.36	0.52	0.40	0.15	0.46	0.35	0.12
	100	mean	2.9	8.6	8.3	12.8	31.3	15.6	19.5	19.4
		SD	0.32	0.25	0.23	0.40	0.46	0.52	0.31	0.32
Donlar	150	mean	2.8	8.7	8.8	12.8	13.4	15.4	19.6	19.1
ropiai		SD	0.17	0.44	0.42	0.38	0.47	0.40	0.49	0.25
	200	mean	2.9	8.8	8.7	12.8	13.5	15.7	19.6	19.3
		SD	0.38	0.57	0.15	0.52	0.36	0.06	0.53	0.40
	250	mean	2.6	8.9	8.7	12.7	13.4	15.7	19.5	19.4
		SD	0.35	0.25	0.21	0.59	0.53	0.21	0.32	0.21
	50	mean	2.9	8.6	8.2	12.5	13.7	15.4	19.8	19.3
		SD	0.30	0.15	0.46	0.45	0.35	0.38	0.36	0.15
	100	mean	2.7	8.7	8.4	12.6	13.4	15.1	19.5	19.3
		SD	0.53	0.12	0.12	0.44	0.59	0.12	0.06	0.25
D1 1 1	150	mean	2.8	08.8	8.2	12.6	13.5	15.2	19.8	19.3
Black locust		SD	0.23	0.57	0.12	0.06	0.55	0.16	0.23	0.15
	200	mean	2.8	8.7	8.5	9.5	13.7	15.5	19.5	19.4
		SD	0.58	0.25	0.32	0.54	0.12	0.46	0.44	0.31
	250	mean	2.6	9.1	8.3	12.5	13.6	15.5	19.3	19.4
		SD	0.06	0.15	0.25	0.45	0.35	0.45	0.32	0.23

Note: SD = Standard Deviation; statistical analysis could not detect any significant difference between readings taken inside the logs with different diameters and by the weather station (air); values in the table represent the average of the three individual readings obtained in three different logs for each treatment.

1 Table 9: Initial and final values of HHV and LHV of logs of different sizes and forestry tree spectrum sizes and the spectrum sizes and forestry tree spectrum sizes and the spe
--

	Diameter	Initial value	s (MJ kg ⁻¹)	Final value	es (MJ kg ⁻¹)
	(mm)	HHV	LHV	HHV	LHV
	50	18.69a	7.05a	18.65a	14.49a
	100	18.72a	7.06a	18.74a	14.21a
Poplar	150	18.83a	7.02a	18.76a	14.32a
	200	18.65a	7.07a	18.61a	14.31a
	250	18.68a	7.09a	18.51a	14.28a
	50	18.05b	7.83b	18.06b	14.48a
	100	17.98b	7.84b	18.01b	14.26a
Black locust	150	18.12b	7.89b	17.97b	14.72a
	200	18.09b	7.93b	18.04b	14.36a
	250	18.01b	7.85b	18.06b	14.44a

Notes: HHV = Higher Heating Value; LHV = Lower Heating Value Values in the table represent the average of the three individual readings obtained in three different logs for each treatment; different letters indicate significant differences between treatments for $\alpha = 0.05$. No statistical differences were obtained between initial HHV value and final HHV value referring to the same forestry tree species.

Table 10: Initial and final values of HHV and LHV of logs of different forestry tree species placed 2

in different layers in the pile 3

-	Height from ground	Initial value	es (MJ kg ⁻¹)	Final value	s (MJ kg ⁻¹)
	(m)	HHV	LHV	HHV	LHV
	0.0	18.72a	7.06a	18.72a	14.42a
	0.5	18.69a	6.99a	18.62a	14.39a
	1.0	18.82a	6.98a	18.82a	14.23a
Poplar	1.5	18.74a	7.01a	18.71a	14.24a
-	2.0	18.78a	7.08a	18.76a	14.34a
	2.5	18.83a	7.05a	18.79a	14.47a
	3.0	18.78a	7.07a	18.73a	14.33a
	0.0	18.03b	7.75b	18.08b	14.54a
	0.5	18.05b	7.54b	18.06b	14.36a
	1.0	18.10b	7.62b	18.02b	14.41a
Black locust	1.5	17.97b	7.91b	18.01b	14.39a
	2.0	18.08b	7.41b	18.06b	14.45a
	2.5	17.98b	7.65b	18.04b	14.56a
	3.0	18.05b	7.39b	18.09b	14.57a

Notes: HHV = Higher Heating Value; LHV = Lower Heating Value Values in the table represent the average of the three individual readings obtained in three different logs for each treatment; different letters indicate significant differences between treatments for $\alpha = 0.05$. No statistical differences were obtained between initial HHV value and final value HHV referring to the same forestry tree species.

	Diameter	Dry matter	(kg)	n Value
	(mm)	Beginning	End	p- v alue
	50	1.69	1.64	0.932
	100	6.79	6.83	0.901
Poplar	150	14.11	14.23	0.898
	200	27.31	27.25	0.941
	250	41.23	41.05	0.902
	50	2.42	2.26	0.889
	100	11.08	11.21	0.884
Black locust	150	22.98	22.57	0.912
	200	42.12	41.95	0.956
	250	61.51	61.41	0.945

1 Table 11: Dry matter at the beginning and at the end of the storage period