

AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Brick technology in the roman villa (I-III c. AD) of Costigliole Saluzzo (Piedmont, Italy)

This is the author's manuscript

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/1694647> since 2019-03-11T17:35:17Z

Publisher:

Università di Torino

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

Brick technology in the roman *villa* (I-III c. AD) of Costigliole Saluzzo (Piedmont, Italy)

P. Davit ^(a), F. Turco ^(a), D. Elia ^(b), V. Meirano ^(b) and L. Operti^(a)

^(a) Department of Chemistry, Università di Torino, Via Pietro Giuria 7, 10125 Torino, Italy

^(b) Department of Historical Studies, Università di Torino, via S. Ottavio 20, 10124 Torino, Italy

francesca.turco@unito.it

The excavation of the *villa rustica* of Costigliole Saluzzo – one of the largest rural settlements of north-western Italy during the Roman age – brought to light a huge quantity of building materials pertaining to the different parts of the *villa* and to other adjacent constructions.

Among the ceramic materials, tiles, curved tiles and north-Italian *sesquipedales* bricks are very common. Other artifacts are less diffused, like a specific kind of brick which is unparalleled in other sites of Roman Piedmont so far: it is usually less compact and hard in comparison with other building materials, and shows differences in color and composition (*e.g.*, a particular concentration of vegetal elements in the fabric). Moreover, the fire which caused the destruction of the *villa* was responsible for the excellent preservation of many parts of the wall structures made in perishable materials in the technique of *opus craticium* (*e.g.*, fragments bearing the traces of the original *incannucciata*, reed structure).

EDX determination revealed a non-calcareous paste for all the analyzed samples, the composition of the *incannucciata* samples show slight differences from all the other samples, quite homogeneous. The overall original firing temperatures evaluated by means of a multitechnique approach (XRPD, SEM, TGA and FTIR) could be assumed between 800 and 1100 °C for all the intentionally fired materials, on average higher than those reported by other authors. A higher temperature in the firing process of this kind of materials results in a mechanical strength increase, suggesting technological advanced knowledge and capability. Moreover, SEM examination of fresh fractures allows ascertaining relict voids of vegetal fragments burnt during the firing step in samples pertaining to the rare type of bricks described *supra*, usually occurring in the foundations and in the bases of few structures related to the *pars urbana* of the building. It seems plausible that the increasing thermal insulation and/or enhancing the freeze-thaw resistance of the final product was the final aim of this technological choice. The expedient of creating voids in the clayey structure to increase thermal insulation and resistance in archaeological building materials was never described before, to the authors' knowledge. The physical mechanism bestowing these characteristics to the bricks was evidently not known, but its effect had been certainly observed, since the procedure of adding straw to limit shrinkage and avoid cracks formation is attested in analogous materials. The adoption of this procedure would suggest good technological knowledge and skills and particular attention in the evaluation and planning of the long-term features of the buildings.

References

- Elia D., Meirano V., La villa di Costigliole Saluzzo (CN). Contributo alla conoscenza del territorio piemontese in età romana, "Orizzonti" XIII (2012), pp. 43-65.
- Elia D., V. Meirano, F. Brigadeci, Costigliole Saluzzo, località Cimitero: insediamento di età romana. Campagne 2013-2014 dell'Università degli Studi di Torino: attività di scavo e di restauro, "Quaderni della Soprintendenza Archeologica del Piemonte. Notiziario" 30 (2015), pp. 313-316.
- Cultrone, G., Sebastián, E. & De La Torre, M.J., Mineralogical and physical behaviour of solid bricks with additives. *Construction and Building Materials*, 19(1) (2005), pp.39-48.
- Bellanger, M., Homand, F. & Remy, J.M., Water behaviour in limestones as a function of pores structure: Application to frost resistance of some Lorraine limestones. *Engineering Geology*, 36(1-2) (1993), pp.99-108.