

AperTO - Archivio Istituzionale Open Access dell'Università di Torino

The study of electrochemically active planktonic microbes in microbial fuel cells in relation to different carbon-based anode materials

This is the author's manuscript

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/1593012> since 2016-09-09T13:24:40Z

Published version:

DOI:10.1016/j.energy.2016.03.004

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

1 **The study of electrochemically active planktonic microbes in microbial fuel cells in relation**
2 **to different carbon-based anode materials.**

3

4 Schilirò T^{1*}, Tommasi T², Armato C^{1,2}, Hidalgo D^{2,3}, Traversi D¹, Bocchini S², Gilli G¹, Pirri CF^{2,3}

5

6 ¹*Department of Public Health and Pediatrics, University of Torino, Piazza Polonia, 94 - 10126,*
7 *Torino, Italy; tiziana.schiliro@unito.it, caterina.armato@unito.it, deborah.traversi@unito.it;*
8 giorgio.gilli@unito.it

9

10 ²*Center for Space Human Robotics @Polito, Istituto Italiano di Tecnologia, Corso Trento 21, 10129,*
11 *Torino, Italy. tonia.tommasi@iit.it, diana.hidalgo@iit.it, sergio.bocchini@iit.it; fabrizio.pirri@iit.it*

12

13 ³*Department of Applied Science and Technology, Politecnico di Torino, Corso Duca degli Abruzzi*
14 *24, 10129 Torino, Italy*

15

16

17

18

19

20

21 ***Corresponding author:**

22 **Tiziana Schilirò**

23 *Department of Public Health and Pediatrics, University of Torino,*

24 *Piazza Polonia, 94 - 10126, Torino, Italy,*

25 *Tel: +390116705820;*

26 *fax:+390116705874,*

27 *e-mail address: tiziana.schiliro@unito.it*

28

29 **ABSTRACT**

30 Microbial Fuel Cells (MFC) are bio-electrochemical systems that convert chemical energy into
31 electrical energy from the respiratory metabolic profit of electrochemically active bacteria.

32 In order to contribute to a greater understanding regarding the MFCs performance, real-time
33 quantitative PCR was applied to determining typical planktonic bacteria in the production of electricity
34 in MFCs, evaluating their relations with different carbon-based anode materials: carbon felt (C-
35 FELT), carbon felt with polyaniline (C-PANI) and carbon-coated Berl saddles (C-SADDLES).

36 Bacteria distribution among the three different MFC anode materials was evaluated: statistically
37 significant differences were detectable for total bacteria ($p < 0.01$), Geobacter ($p < 0.05$) and
38 Shewanella ($p < 0.05$), due to a greater abundance in C-FELT anode MFC. Significant difference (p
39 < 0.001) was shown for maximum power density: C-PANI showed a maximum power density of 28.5
40 W/m³ with respect to C-FELT (4.7 W/m³) and C-SADDLES (4.6 W/m³). In general the largest
41 electrochemically active planktonic microbes was present in the C-FELT while the best carbon-based
42 anode materials results C-PANI.

43

44 **KEYWORDS:** microbial fuel cells; bacterial communities; rt-qPCR; carbon felt; polyaniline
45 deposition; carbon-coated Berl saddles.

46

47 1. INTRODUCTION

48 Microbial fuel cell (MFC) is a bio-electrochemical system that provides a new approach for electricity
49 generation [1]. A typical MFC device is formed by two compartments, one for the anode and the
50 other one for the cathode, which are separated by a cation exchange membrane (CEM). In the anode
51 compartment, organic material is oxidized by microorganisms, thus generating electrons and
52 protons. The electrons are transferred to the cathode compartment through an external electric
53 circuit, meanwhile, the protons flow to the cathode compartment through the membrane [2].

54 Currently, research on MFCs is thriving and no longer considered as a scientific peculiarity [3] but
55 as a viable future technology [4]·[5].

56 MFCs have recently attracted wide attention as green-energy processes that generate electricity
57 from a variety of organic and inorganic materials [4];[6]. In particular, MFCs are expected to be
58 applied to the recovery of energy from biomass wastes and wastewater [6]·[7]·[8], providing dual
59 benefits of wastewater treatment and the production of inexpensive and environmentally friendly
60 energy [2]; also the utilization of marine sediments in MFCs [9]·[10] and biosensors [11] are promising
61 applications [5].

62 It has been the recent discovery of a new metabolic class of electricity-producing microorganisms
63 that has, for the first time, indicated that a wide diversity of organic compounds can be effectively
64 converted to electricity in self-sustaining MFC [12]. These organisms, known as electricigens,
65 degrade (oxidize) organic matter, producing electrons that travel through a series of respiratory
66 enzymes in the cell and make energy for the cell in the form of ATP. The electrons are then released
67 to a terminal electron acceptor (TEA) which accepts the electrons and becomes reduced. Many
68 TEAs such as oxygen, nitrate, sulfate, and others readily diffuse into the cell where they accept
69 electrons forming products that can diffuse out of the cell. However, it is well known that some bacteria
70 can transfer electrons exogenously (i.e., outside the cell) to a TEA such as a metal oxide like iron
71 oxide. These bacteria called *exoelectrogens* can exogenously transfer electrons producing power in
72 an MFC [13]

73 The ability of microbes to transfer electrons in the anode can significantly affect the performance of
74 MFCs. Anodic microbial communities were reported to be significantly related with the types of

75 substrates; for example, *Acetobacterium* species (sp.), *Geobacter* sp., and *Arcobacter* sp. were
76 detected in the anodic biofilm fed with formate [14], *Enterobacter* sp. was the dominant bacterial
77 species in the MFC with glucose as substrate [15].

78 A list of microorganism together with their substrates is reported in literature and it is shown in **Table**
79 **1**. Marine and river sediment, soil, wastewater, fresh sea-water and activated sludge are all rich
80 sources for these microorganisms [16];[17];[18].

81 In MFCs, microbes also play crucial roles in energy output and organic contaminants removal [19].
82 In anodic biofilm, five genera of known exoelectrogens accounted for 23.5% in total communities,
83 including *Desulfobulbus*, *Geobacter*, *Desulfovibrio*, *Pseudomonas* and *Comamonas*. The genera
84 of exoelectrogens in planktonic culture included *Desulfobulbus*, *Desulfovibrio*, *Pseudomonas* and
85 *Comamonas*. *Geobacter*, an important genus attributing to the power generation in an MFC, was
86 only dominant in the anodic biofilm [20];[21]. Although sulfate reducing bacteria (SRB) was reported
87 to play an important role in transferring electrons on the anode, some groups of SRB that could not
88 form biofilm on the electrode may also reduce sulfate in the planktonic niche [22]. It has already been
89 reported that SRB demonstrate functional dynamics, including electron transfer, sulfate reduction,
90 and converting organic matters, such as acetic and butyric acids to alcohols and acetone via direct
91 electron transfer [23];[24].

92 The anodic reaction in mediator-less MFCs constructed with metal reducing bacteria belonging
93 primarily to the families of *Shewanella*, *Rhodospirillum rubrum*, and *Geobacter* consist in transferring electrons
94 to the anode that act as final electron acceptor. Although most of the real mediator-less MFCs are
95 operated with dissimilatory metal reducing microorganisms, an exception was reported with
96 *Clostridium butyricum* [25];[26].

97 Usually mixed culture MFCs have good performances; using complex mixed cultures (anodic
98 microcosm) allows much wider substrate utilization with respect to pure cultures. In mixed culture
99 MFCs (with anaerobic sludge) there are both electrophiles/anodophiles and groups that use natural
100 mediators together in the same chamber [18].

101 Over the last decade numerous investigations have been directed to improve performance of an
102 MFC by hanging/modifying the following components: MFC design/architecture/configuration,

103 electrolytes in solutions, organic fuels, materials and surfaces of electrodes, and electrogenic biofilm
104 on the anode [4]. In particular, the efficiency of electron transfer from electrogens to the anode has
105 been noted to be the most critical factor controlling the overall circuit of an MFC for current production
106 [27][28];[29].

107 In order to improve bacterial adhesion and electron transfer from microorganisms to the electrode
108 several strategies have been developed on carbon-based materials to improve the performances of
109 MFC anode [30][31]. To address these issues, in this work three different anode electrodes are
110 studied and compared: (1) commercial carbon felt (C-FELT), (2) polyaniline deposited carbon felt
111 (C-PANI) and (3) carbon-coated Berl saddles (C-SADDLES). PANI can be easily deposited on
112 carbon materials and its good conductivity and biocompatibility provide the necessary conditions to
113 be used effectively as surface modifier for electrode materials in the MFCs [32][33]. Furthermore,
114 the use of carbon-coated Berl saddles have been demonstrated as low-cost solution that satisfy
115 either electrical or bioreactor requirements, increasing the reliability of the MFC processes [34].

116 The present work is aimed to apply a method for determining typical bacteria in the production of
117 electricity in a MFC by real-time quantitative Polymerase Chain Reaction (rt-qPCR). In order to
118 contribute to a greater understanding regarding the MFCs performance, **the purpose of this study**
119 **was to screening bacteria abundance and to evaluate their relations with different carbon-based**
120 **anode materials, different physic conditions and time. Three different MFCs were studied with**
121 **acetate as substrate and carbon felt, carbon felt with polyaniline and carbon-coated Berl saddles as**
122 **anode materials.**

123

124 **2. MATERIALS AND METHODS**

125 **2.1 Materials**

126 Carbon felt, commercial Berl saddles, α -D-glucose (96%), Sodium phosphate dibasic dihydrate
127 ($\text{Na}_2\text{HPO}_4 \cdot 2\text{H}_2\text{O}$, 98%), Sodium phosphate monobasic monohydrate ($\text{NaH}_2\text{PO}_4 \cdot \text{H}_2\text{O}$, 98%) and
128 Potassium ferricyanide ($\text{K}_3\text{Fe}(\text{CN})_6$, 99%) were purchased from Sigma Aldrich. Seawater was used
129 as inoculum of active microorganisms. The deposition of conductive carbon layer on Berl saddles
130 was performed as reported by Hidalgo and colleagues [34].

131

132 **2.2 MFC configuration and operation**

133 MFC device consists of two circular chambers, i.e. the anode and the cathode. Both compartments
134 were made in Poly(methyl methacrylate) with internal diameter of 12 cm and 1.5 cm of thickness
135 (internal volume for each chamber ~ 170 ml) separated by a cation exchange membrane (CEM, CMI
136 7000, Membranes International Inc., Glen Rock, NJ, USA). Different conductive materials were
137 introduced in each anode chamber: commercial carbon felt (C-FELT) (Soft felt SIGRATHERM GFA5,
138 SGL Carbon, Germany) in MFC1, polyaniline deposited carbon felt (C-PANI) in MFC2 and carbon-
139 coated Berl saddles (C-SADDLES) in MFC3 as anodic materials. For the cathode, it was always
140 used carbon felt (Soft felt SIGRATHERM GFA5, SGL Carbon, Germany) as electrode material. Each
141 conductive material was connected with a graphite rod (5 mm in diameter) to ensure an effective
142 current transport. MFCs were inoculated in the anode chamber by sea water (Arma di Taggia, Italy),
143 previously enriched with following cultures (in five steps) in anaerobic conditions (V inoculum 10%
144 of synthetic substrate previously described). The first 10 days of tests have been conducted in Open
145 Circuit Voltage condition, in order to have the adaptation of bacteria at the new conditions inside the
146 MFCs. After the start-up period, MFCs were operated under external resistance of 1000 Ω .
147 All the investigations were carried out under the same operational conditions, in fed-batch mode by
148 using a multi-programmable syringe-pump (NE-1600, New Era Pump System) at room temperature
149 22 ± 2 °C. The mixing of the solutions at both anode and cathode chambers was obtained by
150 recirculating anolyte and catholyte from a 500 ml reservoir, respectively at a high flow rate (30
151 mL/min) by multichannel peristaltic pumps at both anode and cathode chambers (Peri-Star Pro 4
152 and 8 channel, USA, respectively).
153 Evaluations were performed over a period of 5 weeks feeding in the anodic solution sodium acetate
154 (1 g/L) as synthetic substrate and peptone (1.25 g/L) as nutrient sources for microorganisms growth.
155 The cathodic compartment was filled by potassiumferricyanide (6.58 g/L) used as oxidant compound.
156 To prepare anodic and cathodic solutions, a buffer of inorganic salts, i.e. $\text{Na}_2\text{HPO}_4 \cdot 2\text{H}_2\text{O}$ (8.2 g/L)
157 and $\text{NaH}_2\text{PO}_4 \cdot \text{H}_2\text{O}$ (5.2 g/L) was used.

158

159 **2.3 Electrochemical measurements and analyses**

160 The comprehension of the MFCs trend during time-course of tests required the exploration of both
161 physiological and electrochemical parameters. For this reason, every 2-3 days, pH, Redox Potential
162 (rH), conductivity and optical density (OD) at 600nm were monitored taking planktonic samples from
163 liquid samples. Moreover, electrochemical characterizations, including Open Circuit Voltage (OCV),
164 Linear Sweep Voltammetry (LSV) and Current Interrupt (CI) method, were conducted under 1000 Ω
165 external resistance from day 3 to day 35, allowed to understand the system from electrical and
166 biological point of view. Electrochemical experiments were performed on a multi-channel VSP
167 potentiostat/galvanostat produced by BioLogic. Measurements were recorded by using EC-Lab
168 software version 10.1x (BioLogic) for data acquisition. All tests were carried out using a two electrode
169 setup, where the working electrode was coupled to the anode and both counter electrode and
170 reference electrode were connected to the cathode. Polarization curves were performed at a scan
171 rate of 1mV/s when a constant OCV was achieved, from the open-circuit cell voltage V_0 (where $I =$
172 0) to the short-circuit cell voltage $V_{sc} = 0$ (where $I = I_{max}$). From the I-V curves, the power density
173 was calculated by $P = IV/v$, where I , V and v represent current, recorded voltage output and the total
174 anode compartment (TAC), respectively.

175 CI measurement was performed to determine the ohmic resistance of the MFC through the
176 interruption of the current flow and the resulting voltage transients [4]. The circuit was opened
177 causing a steep potential followed of further low rise. The resistance was evaluated as $R_{\Omega} = V_R/I_0$
178 and a mean value of different tests were computed [34].

179 Furthermore, both anode potential (versus Ag/AgCl electrode) and MFC potential, were maintained
180 in OCV conditions during the first 3 days of operation and then an external resistance of 1000 Ω was
181 connected from 3 to 35 days, which allowed continuously recorded the voltage generated every 60
182 s during the whole time-course of tests by using a Data Acquisition Unit (Agilent, 34972A). These
183 voltage data were used to calculate current and therefore power density according to the external
184 resistance applied and the internal volume of anode chamber of MFCs. Even if the tests were
185 conducted using buffer solution in both chambers, a pH adjustment by HCl 0.01M was necessary

186 because the anode pH tends to increase, probably related to the increase of conductivity of anode
187 solution due to the use of a medium containing sea-water.

188 **2.4 Biological analysis**

189 On the basis of literature were selected procedures in order to analyze the bacterial communities
190 involved in anaerobic fermentation leading to production of electricity in a MFC [5];[35];[36];[37];[38].

191 The rt-qPCR analysis were performed for the following genera of microorganisms: Total Bacteria,
192 Total Sulfate Reducing Bacteria (SRB), Acetobacter (Gram-), Clostridium (Gram+), Geobacter
193 (Gram-), Saccharomyces (Yeast), Shewanella (Gram-). Gene target primers for each strain were
194 selected by the international scientific literature (**Table 2**) and they have been tested in their
195 functionality: a specific rt-qPCR protocol was used for each primer, then a new common rt-qPCR
196 protocol was developed in order to optimize and standardize the analysis at the same time.

197 **2.5 DNA extraction and purification**

198 In order to evaluate microbial community variability of in MFC, 1.8 ml of culture media from MFC
199 were centrifuge at 10000 g for 30 sec, and supernatant was discarded. The DNA extraction was
200 performed with a commercial kit (UltraClean™ Microbial DNA Isolation Kit, MO-BIO Laboratories
201 Inc., Carlsbad, CA).

202 An electrophoresis gel on 2% agarose and 1X TBE buffer (1L, 10X TBE buffer stock: 121.1 g Trizma
203 base, 61.8 g boric acid and 7.4 g EDTA) was performed after each extraction to check genomic DNA
204 integrity. 20 µl of DNA sample (1:10) with 20 µl of loading buffer (950 µl of glycerol 30%, 50 µl of
205 bromophenol blue) and 15 µl of ethidium bromide were loaded into the gel together with a molecular
206 mass marker (M). The gel was placed in an electrophoresis chamber, which was then connected to
207 a power source. The applied electric current is 100 V for 70 min.

208 **2.6 DNA quantification**

209 The fluorimetric quantification of each DNA sample was performed using Qubit™ Fluorometer and
210 Qubit™ dsDNA HS Assay by Invitrogen (distributed by Life Technology Ltd. – Paisley, UK), taking
211 into account the manufacturer's instructions.

212 Samples with a concentration greater than 1 µg/mL and showing sufficient DNA quality as observed
213 by gel electrophoresis were used for the analysis. These restrictions were applied because of

214 difficulty in quantifying poor quality DNA or small concentration of it. Samples were stored at -20°C
215 until performing RT-qPCR analysis.

216 **2.7 RT-qPCR**

217 After DNA extraction and purification RT-qPCR was used to identify and quantify microorganisms.
218 Each RT-qPCR was performed in a 96 wells plates. All RT-qPCR were carried out in a 20 µl volume,
219 in singleplex, with specific primer; each sample was tested in triplicate.

220 The reactions used a standard super-mix (Bio-Rad SsoFast_EvaGreen SuperMix) and the RT-qPCR
221 Chromo4 (Bio-Rad) with Opticon Monitor 3 Software.

222 After that RT-qPCR protocols were tested with their specific primer
223 [39]·[40]·[41]·[42]·[43]·[44]·[45]·[46]·[47]·[48], a new common thermal protocol for RT-qPCR was drawn
224 and tested. Reaction conditions were as follow: 1° step: 95°C for 3.5 minutes, as initial denaturation
225 phase; 2° step: 95°C for 30 sec, as denaturation phase; 3° step: 55°C for 45 seconds, as annealing
226 phase; 4° step: 72°C for 30 sec, as extension phase; 5° step: Reading plate. After 40 cycles (steps
227 2°-5°) a melting curve, was run with the following thermal conditions: from 55 °C to 95 °C read every
228 0.5 °C, and read plate at 95 °C.

229 To quantify the Total Bacteria the reaction use standard power-mix (Bio-Rad IQTM Multiplex
230 PowerMix) and the RT-qPCR Chromo4 (Bio-Rad) with Opticon Monitor 3 Software. The RT-qPCR
231 thermal protocol was the same (melting curve was not performed).

232 The standard curves had six points and were calculated according to the threshold cycle method.
233 There was a 1:10 dilution factor between each standard curve point (range 10 – 10⁶). The standards
234 and samples were tested in triplicate. The triplicate value was accepted only if the coefficient of
235 variation was below 20%. The correlation coefficient was considered sufficient if above 0.980. The
236 PCR efficiency for the different strains was between 79% and 104%. We used 2 µl of a 1:10 dilution
237 factor of each DNA extract sample for the amplification. This quantity was evaluated as the best
238 among various tested quantities according to a standard curve and acceptable PCR efficiency. The
239 1:10 dilution limited the effect of inhibitory substances present in this kind of sample.

240 In order to obtain an absolute quantification of bacteria in MFC samples, a standard curve of specific
241 genomic DNA was performed, in this way, the quantification of bacteria could be expressed in terms

242 of gene copies number as a useful and necessary parameter to compare different samples (**Table**
243 **2**). After each PCR analysis, in order to confirm fragment amplification, gel electrophoresis on 2%
244 agarose was performed, with the technical procedure previously described for evaluation of DNA
245 integrity.

246 **2.8 Statistics**

247 Statistical analyses were performed with the SPSS Package version 21.0 for Windows. Student's t-
248 test and one-way analysis of variance (ANOVA) were applied to compare two or more groups of
249 independent samples, respectively, while Spearman's correlation was used to test for possible
250 associations between the variables. For ANOVA testing, the homogeneity of the variance was firstly
251 assessed through the Levene test, thus the equal variance of Tukey's test was assumed for post
252 hoc multiple comparisons. The differences and correlations were considered significant at $p < 0.05$.

253

254 **3. RESULTS AND DISCUSSION**

255 **3.1 MFCs electrochemical measurements and analyses**

256 **Figure 1** is an overview of the electrical behavior of the three MFCs. The first three days, MFCs
257 were maintained in OCV conditions, in order to reach stable voltage conditions of potential and to
258 favorite bacterial adaptation and growth and without the stress induced by external resistances.

259 **Figure 1** showed many fluctuations mainly due to the fed-batch condition. Changing from OCV to
260 1000 Ω resistances provokes a drop of voltage, more evident (about 50% of OCV) the first week
261 where the biofilm probably was not so stable. Moreover, it was possible to observe that MFC 1 which
262 operated using C-FELT showed more evident fluctuations possibly due to both external resistance
263 connection and fed-batch feeding of substrate. Furthermore, MFC 2 which operated using C-PANI
264 showed more stable electrical conditions, probably due to the PANI deposition improved the bacterial
265 adhesion on felt facilitating electron transfer from microorganisms to the electrode. Similar results
266 were also obtained in MFC 3 confirm that C-SADDLES satisfied the electrical requirements in MFC.
267 The complete comprehension of the MFCs trend during time-course of test required the exploration
268 of both physiological and electrochemical parameters, as shown in **Table 3**.

269 Initial pH was 6.65 ± 0.02 for the three cells. It sharply increases for the three cells during the first
270 15 days till 8.2, 8.3 and 8, respectively for MFC 1, 2 and 3. After that period the measured pH values
271 (referred before adjustment) were constant in the range of 7.5 - 8.3. Redox Potential (rH) rapidly
272 decreased in the first 3 days (OCV conditions) from values near to $0 \pm 3.6\text{mV}$ at time 0 to negative
273 values of $-120 \pm 30\text{ mV}$ as average values for the three cells at time 3 days. The rH data confirmed
274 that there were reducing conditions and hence the good condition of electron release in the liquid
275 medium, thanks to metabolic activity of microorganisms starting from sodium acetate, as electron
276 donor. The low rH was also a demonstration of anaerobic condition establishment, necessary to
277 recovery electrons on anode electrodes. Moreover it was in agreement with Optical Density (OD)
278 measures, because in the first three days an exponential phase of total cell were noted in the three
279 MFCs: after a lag-phase lesser than 1 day in which microorganisms reorganize their molecular
280 constituent to adapt to a new environmental conditions, the metabolism starts releasing reduced
281 compounds, such as liquid and gas metabolites beyond protons and electrons, as confirmed from
282 electrochemical analysis [49]. The anolyte conductivities shows a linear increase of about 7 units
283 (from 27 to 34 mS/cm). These highly conductivity values (bigger than those ones present in real
284 wastewater, typically in order of only 1 mS/cm [50], are essentially due to the consecutive addition
285 of phosphate buffer and sea water in the anode feeding, useful mainly for charge transfer (electrons
286 and cations, towards anode-electrode and CEM membrane, respectively), approximately neutral pH
287 maintenance, and for supply micronutrients for bacteria growth.

288 In **Figure 1** the voltage of MFCs increased from low to high values, resulting in a greater power after
289 3 days from the beginning of the experiments.

290 Moreover in the first 20 days there were a sharply decrease of voltage, these decreases were
291 probably due to an imbalanced ratio between carbon and nitrogen (C/N= 100); after day 19th it was
292 established a ratio C/N=30 adding peptone and the voltage increased.

293 Polarization curves (LSV) describes voltage as a function of current representing a powerful tool for
294 a rapid analysis and characterization of MFC during tests (**Table 3**). They were checked at initial
295 time, the 3rd day, before to put 1000 Ohm resistances, and day 32 before to stop tests. LSV curves
296 demonstrate a great increase of MFC performances from the starting point: in particular MFC 2

297 (carbon felt with PANI deposition) shows the biggest power density value of 35 W/m^3 , one order of
298 magnitude more than MFC1 and MFC2. MFC3, with 3-D granular electrode shows a curve very
299 different from both MFC1 and MFC2, showing always a constant behavior from OCV till Short Circuit
300 Current conditions (SCC). Maximum power density for MFC3 was obtained at the end of experiment,
301 reaching 4.6 W/m^3 (**Figure 2**). Similar behavior of polarization curves has been obtained in other
302 works with graphite in granules as electrode [51] [52].

303 Even if MFC2 (with PANI deposition) gave the highest power density by LSV, it does not completely
304 reflect the real behavior under load of 1000 Ohm of about 2.5 W/m^3 . MFC2 has the most stable and
305 highest value of voltage than MFC1 and MFC3, but with the same order of magnitude. On the
306 contrary, the response of the voltage slop of 1 mV/s by LSV showed MFC performances one order
307 of magnitudes higher than MFC1 and MFC3, probably disregard the affect of bacteria adaptation.
308 Author's opinion is that LSV slightly overestimated electrical parameters (I, V) and therefore power
309 density, while 1000 Ohm resistances did not fit the best resistance in order to have maximum power
310 point (MPP) that were one order less for MFC1 and MFC3 and two orders less for MFC2.

311 **Figure 3** evidences an important increase of the maximum power density of the MFC2 (28.5 W/m^3)
312 with respect to MFC1 (4.7 W/m^3) and MFC3 (4.6 W/m^3) after 35 days of operation, which can be
313 related to an important reduction of the ohmic resistance of the cell by using C-PANI. Results
314 confirmed that PANI effectively increases the conductivity of the material favoring the recovery of
315 electrons and increasing the sustainability of the process. In addition, **Figure 4** shows that despite
316 of the higher internal resistance of MFC3 with respect to MFC1, similar results were obtained for
317 both cells suggesting that microorganisms were effectively adapted to the new anode material which
318 could be advantageous for continues MFC applications.

319 **3.2 RT-qPCR and target microbial populations in MFCs**

320 The fluorimetric quantification of DNA samples ranged between 25.4 and $128.0 \text{ } \mu\text{g/mL}$ and all
321 samples had intact DNA.

322 The realization of a unitary RT-qPCR protocol proved to be valid for all microorganisms selected
323 either bacteria or yeasts. The method gives highly reliable results: standard curve R^2 is never lower
324 than 0.984 . This allowed to carry out standardized analyses and to compare different samples.

325 RT-qPCR analyses have highlighted that all the different microbial populations were present and
326 quantifiable in each MFC, with the exception of Acetobacter that resulted undetectable in all the
327 samples probably owing to maintenance of the anaerobic conditions; acetic acid bacteria are
328 characterized by aerobic metabolism with incomplete oxidation of organic substrates.

329 The detected level of various bacteria groups is displayed in **Figure 4**. Groups varied in quantity
330 during the MFC operation and were always present at all, total SRB resulted prevalent followed by
331 Shewanella. In this study were analyzed bacteria belonging to Proteobacteria (Acetobacter, α -
332 Proteobacteria; Desulfovibrio and Geobacter, δ -Proteobacteria; Shewanella, γ -Proteobacteria),
333 Firmicutes (Clostridium) and Ascomycota (Saccharomyces) phyla.

334 As described in the literature, in MFC planktonic culture are present mainly bacteria belonging to the
335 Proteobacteria phylum [1][24]; β - and γ - Proteobacteria resulted predominant among the
336 Proteobacteria phylum in the Sun et al. (2010) instead Wang et al. (2014) showed a majority of δ -
337 and β - Proteobacteria.

338 The selected typical bacteria accounted for 22% of total Bacteria and the percentage of each
339 microorganisms strain was variable (**Figure 4**); RT-qPCR analyses have identified 16 % (range:
340 5.35% – 36.65%) SRB, 3.6 % (range: 1.62% – 7.24%) Shewanella, 2.4 % (range: 0.02% - 8.76%)
341 Geobacter, 0.001 % (range: 0.000% - 0.003%) Saccharomyces, 0.001 % (range: 0.0001% -
342 0.0039%) Clostridium and Acetobacter resulted absent. SRB resulted the most abundant
343 microorganisms among total bacteria and always in higher quantity than other species; a similar
344 datum was also present in a research conducted by Logan using MFCs containing sediments [13].
345 To date more than 220 species belonging to 60 different genera of SRB have been described [53]
346 this might justify the found percentages.

347 **3.3 MFCs considerations**

348 The differences among the three anode materials were evaluated comparing the performance of the
349 three MFCs. Considering carbon felt and carbon felt with PANI (MFC1 vs MFC2), **no statistically**
350 **significant differences resulted for total bacteria (t-test, $p > 0.05$)** although in MFC1 they decreased
351 steadily by one order of magnitude (from 10^9 to 10^8), whereas in MFC2 they kept constant all trial
352 long. No statistically significant differences resulted for SRB (t-test, $p > 0.05$). Although Clostridium

353 decreased in MFC1 and keep constant in MFC2, there were no statistically significant differences (t-
354 test, $p > 0.05$). During the trial in both of the MFCs Geobacter increased, contrariwise
355 Saccharomyces decreased and Shewanella remained constant: the differences were not statistically
356 significant for all the three (t-test, $p > 0.05$).

357 The MFCs system utilized in this test provided performance in line with the scientific literature
358 [54].[55].[56]: maximum power density reached is 255.7 W/m^3 and maximum current density reached
359 is 2138.5 A/m^3 . The MFC2 configuration gave the best performance: the use of PANI increases in a
360 statistically significant manner the performance of the cell. In the future could be useful to measure
361 the substrate concentration to quantify more accurately the performance of the system.

362 Power density and maximum current showed statistically significant differences (t-test, $p < 0.001$ and
363 $p = 0.001$): MFC2, that presented the deposition of PANI, has higher value of one order of magnitude;
364 therefore it was possible to state that deposition of PANI improved the performance of the cell.

365 Correlation between amount of microorganisms and power density were not detectable because of
366 reduced availability of data.

367 Considering carbon felt and graphitized Berl saddles (MFC1 vs MFC3), the analyses highlighted that
368 the quantity of microorganism was always higher in MFC1: this could be due to sampling of
369 planktonic component rather than anode biofilm, since Berl saddles provide greater adhesion surface
370 to the microorganism. Total bacteria and SRB decreased after some day of increase in MFC1,
371 contrariwise they kept constant in MFC3: statistically significant differences resulted only for total
372 bacteria (t-test, $p = 0.011$) but not for SRB (t-test, $p > 0.05$). No statistically significant differences
373 resulted for Geobacter (t-test, $p > 0.05$), that increased in both of the cells since the twelfth day.
374 Shewanella decreased slightly in MFC1, while remained constant in MFC3 (t-test, $p = 0.014$).

375 Maximum power density is approximately equivalent in both of the MFCs, contrariwise the maximum
376 current is higher in MFC1 although in no statistically significant way (t-test, $p > 0.05$).

377 Total bacteria seemed to correlate positively with the maximum current, but this was not verifiable
378 with statistical analysis because of reduced amount of data.

379 One-way analysis of variance (ANOVA) was applied to evaluate differences in the distribution of
380 bacteria among the three different MFCs. In general statistically significant differences were

381 detectable for total bacteria ($p = 0.007$), *Geobacter* ($p = 0.050$), *Shewanella* ($p = 0.046$), current
382 density ($p < 0.001$) and power density ($p < 0.001$). Post hoc test (Tuckey) showed significant
383 differences in the anodic chambers: - for the total bacteria in relation to carbon felt with or without
384 PANI ($p = 0.047$) and carbon felt or graphitized Berl cells ($p = 0.006$) these results were due to a
385 larger number of total bacteria in the MFC1 during the tests; - for *Shewanella* in relation to carbon
386 felt or graphitized Berl cells ($p = 0.037$): in the MFC1 there was a greater presence of *Shewanella*
387 compared to MFC3, contrariwise mean presence of *Shewanella* was similar in anodic chamber with
388 or without PANI. Otherwise Post hoc test (Tuckey) showed significant difference for maximum power
389 density in relation to - carbon felt with or without PANI ($p < 0.001$), - carbon felt with PANI or
390 graphitized Berl cells ($p < 0.001$): these differences were due to a higher power density of a MFC2;
391 for maximum current density in relation to - carbon felt with or without PANI ($p < 0.001$), - carbon felt
392 with PANI or graphitized Berl cells ($p < 0.001$): also in these cases the differences were due to
393 influence of MFC2, that had a major current density.

394 **4. Conclusion**

395 RT-qPCR method proposed herein is a useful tool for quantify typical electrochemically active
396 planktonic microbes and their differences in relation to different MFC carbon-based anode materials,
397 nevertheless our results cannot yet clearly characterize the whole active populations in a MFC.

398 **In general the best carbon-based anode materials results carbon felt with PANI deposition.** PANI
399 deposition, having molecular structures that resemble electron mediators, may function as mediators
400 that improve electron transfer [57]. It has proven to enhance the MFC performance considerably and
401 to decrease output voltage fluctuation under external load. Anyway, despite the advances made by
402 electrode materials (from our study and other researchers) significant hurdles remains before render
403 MFC technology ready for the practical deployment in either wastewater treatment or power
404 generation beyond small sensors. Moreover, further studies are needed to characterize the whole
405 electrochemically active microbial community and highlight differences between the anode-attached
406 and planktonic communities, so to understand the relation within the microbial communities and
407 increase the performance of the system.

408

410 **REFERENCES**

- 411 1. Sun M, Tong ZH, Sheng GP, Chen YZ, Zhang F, et al. (2010) Microbial communities involved in electricity
412 generation from sulfide oxidation in a microbial fuel cell. *Biosens Bioelectron* 26: 470-476.
- 413 2. Canto-Canche B, Tzec-Sima M, Vazquez-Loria JI, Espadas-Alvarez H, Chi-Manzanero BH, et al. (2013) Simple
414 and inexpensive DNA extraction protocol for studying the bacterial composition of sludges used in
415 microbial fuel cells. *Genet Mol Res* 12: 282-292.
- 416 3. Potter MC (1911) Electrical Effects Accompanying the Decomposition of Organic Compounds. *Proceedings*
417 *of the Royal Society of London Series B, Containing Papers of a Biological Character* 84: 260-276.
- 418 4. Logan BE, Hamelers B, Rozendal R, Schroder U, Keller J, et al. (2006) Microbial fuel cells: methodology and
419 technology. *Environ Sci Technol* 40: 5181-5192.
- 420 5. Liu Y, Harnisch F, Fricke K, Schroder U, Climent V, et al. (2010) The study of electrochemically active
421 microbial biofilms on different carbon-based anode materials in microbial fuel cells. *Biosens*
422 *Bioelectron* 25: 2167-2171.
- 423 6. Watanabe K (2008) Recent developments in microbial fuel cell technologies for sustainable bioenergy. *J*
424 *Biosci Bioeng* 106: 528-536.
- 425 7. Lefebvre O, Uzabiaga A, Chang IS, Kim BH, Ng HY (2011) Microbial fuel cells for energy self-sufficient
426 domestic wastewater treatment-a review and discussion from energetic consideration. *Appl*
427 *Microbiol Biotechnol* 89: 259-270.
- 428 8. Miyahara M, Hashimoto K, Watanabe K (2013) Use of cassette-electrode microbial fuel cell for wastewater
429 treatment. *J Biosci Bioeng* 115: 176-181.
- 430 9. Tender LM, Reimers CE, Stecher HA, Holmes DE, Bond DR, et al. (2002) Harnessing microbially generated
431 power on the seafloor. *Nat Biotech* 20: 821-825.
- 432 10. Tender LM, Gray SA, Groveman E, Lowy DA, Kauffman P, et al. (2008) The first demonstration of a
433 microbial fuel cell as a viable power supply: Powering a meteorological buoy. *Journal of Power*
434 *Sources* 179: 571-575.
- 435 11. Moon HS, Chang IS, Jang JK, Kim KS, Lee JY, et al. (2005) On-Line Monitoring of Low Biochemical Oxygen
436 Demand Through Continuous Operation of a Mediator-Less Microbial Fuel Cell. *Journal of*
437 *Microbiology and Biotechnology* 15: 192-196.
- 438 12. Lovley DR (2006) Bug juice: harvesting electricity with microorganisms. *Nat Rev Microbiol* 4: 497-508.
- 439 13. Logan BE (2008) *Microbial fuel cells*. Hoboken, New Jersey: John Wiley & Sons, Inc.
- 440 14. Ha PT, Tae B, Chang IS (2008) Performance and Bacterial Consortium of Microbial Fuel Cell Fed with
441 Formate \dagger . *Energy & Fuels* 22: 164-168.
- 442 15. Luo Y, Zhang R, Liu G, Li J, Li M, et al. (2010) Electricity generation from indole and microbial community
443 analysis in the microbial fuel cell. *J Hazard Mater* 176: 759-764.
- 444 16. Niessen J, Harnisch F, Rosenbaum M, Schröder U, Scholz F (2006) Heat treated soil as convenient and
445 versatile source of bacterial communities for microbial electricity generation. *Electrochemistry*
446 *Communications* 8: 869-873.
- 447 17. Zhang E, Xu W, Diao G, Shuang C (2006) Electricity generation from acetate and glucose by sedimentary
448 bacterium attached to electrode in microbial-anode fuel cells. *Journal of Power Sources* 161: 820-
449 825.
- 450 18. Du Z, Li H, Gu T (2007) A state of the art review on microbial fuel cells: A promising technology for
451 wastewater treatment and bioenergy. *Biotechnol Adv* 25: 464-482.
- 452 19. Pant D, Singh A, Van Bogaert G, Irving Olsen S, Singh Nigam P, et al. (2012) Bioelectrochemical systems
453 (BES) for sustainable energy production and product recovery from organic wastes and industrial
454 wastewaters. *RSC Advances* 2: 1248-1263.
- 455 20. Bond DR, Lovley DR (2003) Electricity production by *Geobacter sulfurreducens* attached to electrodes.
456 *Appl Environ Microbiol* 69: 1548-1555.
- 457 21. Nercessian O, Parot S, Delia ML, Bergel A, Achouak W (2012) Harvesting electricity with *Geobacter*
458 *bremensis* isolated from compost. *PLoS One* 7: e34216.
- 459 22. Malvankar NS, Lovley DR (2012) Microbial nanowires: a new paradigm for biological electron transfer and
460 bioelectronics. *ChemSusChem* 5: 1039-1046.

- 461 23. Sharma M, Aryal N, Sarma PM, Vanbroekhoven K, Lal B, et al. (2013) Bioelectrocatalyzed reduction of
462 acetic and butyric acids via direct electron transfer using a mixed culture of sulfate-reducers drives
463 electrosynthesis of alcohols and acetone. *Chem Commun (Camb)* 49: 6495-6497.
- 464 24. Wang Z, Lee T, Lim B, Choi C, Park J (2014) Microbial community structures differentiated in a single-
465 chamber air-cathode microbial fuel cell fueled with rice straw hydrolysate. *Biotechnol Biofuels* 7: 9.
- 466 25. Oh SE, Logan BE (2006) Proton exchange membrane and electrode surface areas as factors that affect
467 power generation in microbial fuel cells. *Appl Microbiol Biotechnol* 70: 162-169.
- 468 26. Park HS, Kim BH, Kim HS, Kim HJ, Kim GT, et al. (2001) A Novel Electrochemically Active and Fe(III)-
469 reducing Bacterium Phylogenetically Related to *Clostridium butyricum* Isolated from a Microbial Fuel
470 Cell. *Anaerobe* 7: 297-306.
- 471 27. Crittenden SR, Sund CJ, Sumner JJ (2006) Mediating electron transfer from bacteria to a gold electrode
472 via a self-assembled monolayer. *Langmuir* 22: 9473-9476.
- 473 28. Feng Y, Yang Q, Wang X, Logan BE (2010) Treatment of carbon fiber brush anodes for improving power
474 generation in air-cathode microbial fuel cells. *Journal of Power Sources* 195: 1841-1844.
- 475 29. Kang CS, Eaktasang N, Kwon DY, Kim HS (2014) Enhanced current production by *Desulfovibrio*
476 *desulfuricans* biofilm in a mediator-less microbial fuel cell. *Bioresour Technol* 165: 27-30.
- 477 30. Rosenbaum M, Zhao F, Quaas M, Wulff H, Schröder U, et al. (2007) Evaluation of catalytic properties of
478 tungsten carbide for the anode of microbial fuel cells. *Applied Catalysis B: Environmental* 74: 261-
479 269.
- 480 31. Li C, Zhang L, Ding L, Ren H, Cui H (2011) Effect of conductive polymers coated anode on the performance
481 of microbial fuel cells (MFCs) and its biodiversity analysis. *Biosens Bioelectron* 26: 4169-4176.
- 482 32. Scott K, Rimbu GA, Katuri KP, Prasad KK, Head IM (2007) Application of Modified Carbon Anodes in
483 Microbial Fuel Cells. *Process Safety and Environmental Protection* 85: 481-488.
- 484 33. Ghasemi M, Daud WRW, Mokhtarian N, Mayahi A, Ismail M, et al. (2013) The effect of nitric acid,
485 ethylenediamine, and diethanolamine modified polyaniline nanoparticles anode electrode in a
486 microbial fuel cell. *International Journal of Hydrogen Energy* 38: 9525-9532.
- 487 34. Hidalgo D, Tommasi T, Cauda V, Porro S, Chiodoni A, et al. (2014) Streamlining of commercial Berl saddles:
488 A new material to improve the performance of microbial fuel cells. *Energy* 71: 615-623.
- 489 35. Aelterman P, Freguia S, Keller J, Rabaey K, Verstraete W (2008) The anode potential regulates the bacterial
490 activity in microbial fuel cells. *Commun Agric Appl Biol Sci* 73: 85-89.
- 491 36. Logan BE (2009) Exoelectrogenic bacteria that power microbial fuel cells. *Nat Rev Micro* 7: 375-381.
- 492 37. Shimoyama T, Yamazawa A, Ueno Y, Watanabe K (2009) Phylogenetic analyses of bacterial communities
493 developed in a cassette-electrode microbial fuel cell. *Microbes Environ* 24: 188-192.
- 494 38. Liu W, Wang A, Sun D, Ren N, Zhang Y, et al. (2012) Characterization of microbial communities during
495 anode biofilm reformation in a two-chambered microbial electrolysis cell (MEC). *J Biotechnol* 157:
496 628-632.
- 497 39. Cummings DE, Snoeyenbos-West OL, Newby DT, Niggemyer AM, Lovley DR, et al. (2003) Diversity of
498 *Geobacteraceae* species inhabiting metal-polluted freshwater lake sediments ascertained by 16S
499 rDNA analyses. *Microb Ecol* 46: 257-269.
- 500 40. Dar SA, Kuenen JG, Muyzer G (2005) Nested PCR-denaturing gradient gel electrophoresis approach to
501 determine the diversity of sulfate-reducing bacteria in complex microbial communities. *Appl Environ*
502 *Microbiol* 71: 2325-2330.
- 503 41. Dar SA, Yao L, van Dongen U, Kuenen JG, Muyzer G (2007) Analysis of diversity and activity of sulfate-
504 reducing bacterial communities in sulfidogenic bioreactors using 16S rRNA and *dsrB* genes as
505 molecular markers. *Appl Environ Microbiol* 73: 594-604.
- 506 42. Dridi B, Henry M, El Khechine A, Raoult D, Drancourt M (2009) High prevalence of *Methanobrevibacter*
507 *smithii* and *Methanosphaera stadtmanae* detected in the human gut using an improved DNA
508 detection protocol. *PLoS One* 4: e7063.
- 509 43. Friedrich MW (2002) Phylogenetic analysis reveals multiple lateral transfers of adenosine-5'-
510 phosphosulfate reductase genes among sulfate-reducing microorganisms. *J Bacteriol* 184: 278-289.
- 511 44. Himmelheber DW, Thomas SH, Löffler FE, Taillefert M, Hughes JB (2009) Microbial colonization of an in
512 situ sediment cap and correlation to stratified redox zones. *Environ Sci Technol* 43: 66-74.

- 513 45. Meyer B, Kuever J (2007) Molecular analysis of the diversity of sulfate-reducing and sulfur-oxidizing
514 prokaryotes in the environment, using *aprA* as functional marker gene. *Appl Environ Microbiol* 73:
515 7664-7679.
- 516 46. Meyer B, Kuever J (2007) Phylogeny of the alpha and beta subunits of the dissimilatory adenosine-5'-
517 phosphosulfate (APS) reductase from sulfate-reducing prokaryotes--origin and evolution of the
518 dissimilatory sulfate-reduction pathway. *Microbiology* 153: 2026-2044.
- 519 47. Xia Q, Williams T, Husted D, Price P, Morrison M, et al. (2012) Quantitative analysis of intestinal bacterial
520 populations from term infants fed formula supplemented with fructo-oligosaccharides. *J Pediatr*
521 *Gastroenterol Nutr* 55: 314-320.
- 522 48. Xu W, Huang Z, Zhang X, Li Q, Lu Z, et al. (2011) Monitoring the microbial community during solid-state
523 acetic acid fermentation of Zhenjiang aromatic vinegar. *Food Microbiol* 28: 1175-1181.
- 524 49. Tommasi T, Sassi G, Ruggeri B (2008) Acid pre-treatment of sewage anaerobic sludge to increase hydrogen
525 producing bacteria HPB: effectiveness and reproducibility. *Water Sci Technol* 58: 1623-1628.
- 526 50. Rozendal RA, Hamelers HVM, Rabaey K, Keller J, Buisman CJN (2008) Towards practical implementation
527 of bioelectrochemical wastewater treatment. *Trends in Biotechnology* 26: 450-459.
- 528 51. Liu XW, Wang YP, Huang YX, Sun XF, Sheng GP, et al. (2011) Integration of a microbial fuel cell with
529 activated sludge process for energy-saving wastewater treatment: taking a sequencing batch reactor
530 as an example. *Biotechnol Bioeng* 108: 1260-1267.
- 531 52. Aelterman P, Versichele M, Marzorati M, Boon N, Verstraete W (2008) Loading rate and external
532 resistance control the electricity generation of microbial fuel cells with different three-dimensional
533 anodes. *Bioresource Technology* 99: 8895-8902.
- 534 53. Barton LL, Fauque GD (2009) Biochemistry, physiology and biotechnology of sulfate-reducing bacteria.
535 *Adv Appl Microbiol* 68: 41-98.
- 536 54. Arends JB, Verstraete W (2012) 100 years of microbial electricity production: three concepts for the
537 future. *Microb Biotechnol* 5: 333-346.
- 538 55. Pham TH, Aelterman P, Verstraete W (2009) Bioanode performance in bioelectrochemical systems:
539 recent improvements and prospects. *Trends Biotechnol* 27: 168-178.
- 540 56. Reimers CE, Tender LM, Fertig S, Wang W (2001) Harvesting energy from the marine sediment--water
541 interface. *Environ Sci Technol* 35: 192-195.
- 542 57. Schroder U, Niessen J, Scholz F (2003) A generation of microbial fuel cells with current outputs boosted
543 by more than one order of magnitude. *Angew Chem Int Ed Engl* 42: 2880-2883.
- 544 58. Niessen J, Schröder U, Scholz F (2004) Exploiting complex carbohydrates for microbial electricity
545 generation – a bacterial fuel cell operating on starch. *Electrochemistry Communications* 6: 955-958.
- 546 59. Ieropoulos IA, Greenman J, Melhuish C, Hart J (2005) Comparative study of three types of microbial fuel
547 cell. *Enzyme and Microbial Technology* 37: 238-245.
- 548 60. Park DH, Kim BH, Moore B, Hill HAO, Song MK, et al. (1997) Electrode reaction of *Desulfovibrio*
549 *desulfuricans* modified with organic conductive compounds. *Biotechnology Techniques* 11: 145-148.
- 550 61. Min B, Cheng S, Logan BE (2005) Electricity generation using membrane and salt bridge microbial fuel
551 cells. *Water Research* 39: 1675-1686.
- 552 62. Bond DR, Holmes DE, Tender LM, Lovley DR (2002) Electrode-reducing microorganisms that harvest
553 energy from marine sediments. *Science* 295: 483-485.
- 554 63. Lee SA, Choi Y, Jung S, Kim S (2002) Effect of initial carbon sources on the electrochemical detection of
555 glucose by *Gluconobacter oxydans*. *Bioelectrochemistry* 57: 173-178.
- 556 64. Ringeisen BR, Henderson E, Wu PK, Pietron J, Ray R, et al. (2006) High power density from a miniature
557 microbial fuel cell using *Shewanella oneidensis* DSP10. *Environ Sci Technol* 40: 2629-2634.
- 558 65. Kim BH, Kim HJ, Hyun MS, Park DH (1999) Direct Electrode Reaction of Fe(3)-Reducing Bacterium,
559 *Shewanella putrefaciens*. *Journal of Microbiology and Biotechnology* 9: 127-131.
- 560 66. Kim HJ, Hyun MS, Chang IS, Kim BH (1999) A Microbial Fuel Cell Type Lactate Biosensor Using a Metal -
561 Reducing Bacterium, *Shewanella putrefaciens*. *Journal of Microbiology and Biotechnology* 9: 365-
562 367.
- 563 67. Park DH, Zeikus JG (2002) Impact of electrode composition on electricity generation in a single-
564 compartment fuel cell using *Shewanella putrefaciens*. *Appl Microbiol Biotechnol* 59: 58-61.

- 565 68. Karthikeyan R, Sathish Kumar K, Murugesan M, Berchmans S, Yegnaraman V (2009) Bioelectrocatalysis of
566 Acetobacter aceti and Gluconobacter roseus for current generation. Environ Sci Technol 43: 8684-
567 8689.
- 568 69. Mathuriya AS, Sharma VN (2010) Electricity Generation by Saccharomyces cerevisiae and Clostridium
569 acetobutylicum via Microbial Fuel Cell Technology: A Comparative Study. Advances in Biological
570 Research 4: 217-223.
- 571

572

573

574

575

576

577

578

579

580

581

582

583

584

585

586

587

588

589

590

591

592

593

594

595

596

597 **Table 1.** Microbes used in MFCs: microorganism and substrates (modified by Du et al., 2007)

598

Microbes	Substrate	Applications	Ref.
<i>Clostridium beijerinckii</i>	Starch, glucose, lactate, molasses	Fermentative bacterium	[58]
<i>Clostridium butyricum</i>	Starch, glucose, lactate, molasses	Fermentative bacterium	[26,58]
<i>Desulfovibrio desulfuricans</i>	Sucrose	Sulphate/sulphide as mediator	[59], [60]
<i>Geobacter metallireducens</i>	Acetate	Mediator-less MFC	[61]
<i>Geobacter sulfurreducens</i>	Acetate	Mediator-less MFC	[20] [62]
<i>Gluconobacter oxydans</i>	Glucose	Mediator (HNQ, resazurin or thionine) needed	[63]
<i>Shewanella oneidensis</i>	Lactate	Anthraquinone-2,6-disulfonate (AQDS) as mediator	[64]
<i>Shewanella putrefaciens</i>	Lactate, Pyruvate, Acetate, Glucose	Mediator-less MFC; but incorporating an electron mediator like Mn (IV) or NR into the anode enhanced the electricity production	[65], [66], [67]
<i>Acetobacter aceti</i>	Glucose	Mediator-less MFC	[68]
<i>Gluconobacter roseus</i>	Glucose	Mediator-less MFC	[68]
<i>Saccharomyces cerevisiae</i>	Artificial Wastewater	methylene blue (as indicator)	[69]
<i>Clostridium thermohydrosulfuricum</i>	Artificial Wastewater	methylene blue (as indicator)	[69]

599 **Table 2:** Microorganisms, Primers, Genomic Standards and total number of bases in the genomic
600 DNA (bp), genes and number of copies of gene in μL of solution, tested in MFC biological analysis.

Microorganism	Primer name (gene target) (5' --> 3')	Genomic Standard (ATCC code) N. bases (bp)	Gene bp N. gene copies/ μL	Ref.
Acetobacter	Ace F: CGCAAGGGACCTCTAACACA Ace R: ACCTGATGGCAACTAAAGATAGGG	<i>Acetobacter diazotrophicus</i> (49037D-5) 4,00E+06	110 1,52E+06	[48]
Total Bacteria	16S RNA F: AGAGTTTGATCMTGGCTCAG 16S RNA R: TTACCGCGGCKGCTGGCAC Probe: CCAKACTCCTACGGGAGGCAGCAG	<i>Desulfovibrio vulgaris</i> (29579D-5) 3,57E+06	About 600 8,52E+06	[42]
Clostridium	Clo F: ATTAGGAGGAACACCAGTTG Clo R: AGGAGATGTCATTGGGATGT	<i>Clostridium difficile</i> (9689D-5) 4,18E+06	307 1,45E+06	[47]
Geobacter	Geo F: AAGCGTTGTTGTTCCGAWTTAT Geo R: GGCACTGCAGGGGTCAATA	<i>Geobacter metallireducens</i> (53774D-5) 4,01E+06	313 2,27E+07	[39]
Saccharomyces	Sac F: GCGGTAATTCAGCTCCAATAG Sac R: GCCACAAGGACTCAAGGTTAG	<i>Saccharomyces cerevisiae</i> (9763D) 1,21E+07	151 3,77E+07	[48]
Shewanella	She F: GCCTAGGGATCTGCCAGTCG She R: CTAGGTTTCATCCAATCGCG	<i>Shewanella oneidensis</i> (700550D) 5,13E+06	108 1,19E+07	[44]
Total SRB	AprA F: GGGYCTKCCGCYATCAAYAC AprA R: ATCATGATCTGCCAGCGGCCGGA	<i>Desulfovibrio vulgaris</i> (29579D-5) 3,57E+06	About 300 8,52E+06	[41] [43] [45] [46]

601

602

603 **Table 3.** MFCs physiological and electrochemical parameters.

Parameters	MFC1	MFC2	MFC3
pH (average value)	7.8 ± 0.5	7.6 ± 0.4	7.59 ± 0.5
Conductivity (mS)	31.4 ± 2.9	30.7 ± 2.4	29.9 ± 2.7
Redox Potential (mV)	-60 ± 33	-86 ± 40	-95 ± 43
P max (W/m ³)	4.8	28.1	4.6
P max (W/m ²)	0.074	0.430	0.071
OCV (V)	0.78	0.73	0.70
I _{sc} (A/m ³)	35.5	155.5	24.3
P _{average} (W/m ³) under 1000 Ohm	1.70 ± 0.68	2.40 ± 0.19	1.61 ± 0.24

604

605

606

607

608

609

610

611

612

613

614

615

616

617

618

619

620

621

622 **FIGURE CAPTIONS**

623 **Figure 1.** Voltage vs time course of test from time 0 to 35 days a), current densities according to
624 total anode volume b) and power density c) from MFC1, MFC2 and MFC3.

625

626 **Figure 2.** Polarization curves on the left and corresponding power on the right of MFC1, MFC2 and
627 MFC3, respectively.

628

629 **Figure 3.** MFCs power density (P) and ohmic resistance (R).

630

631 **Figure 4.** Radar graph of gene copies/mL values (logarithmic scale) of samples from MFC1, MFC2,
632 MFC3 for each strain by each probe during the time (from 1st to 5th week)..

633