AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Surface reactivity and in vitro toxicity on human bronchial epithelial cells (BEAS-2B) of nanomaterials intermediates of the production of titania-based composites

This is the author's manuscript

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/1561271> since 2016-06-17T12:07:37Z

Published version:

DOI:10.1016/j.tiv.2016.04.003

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

UNIVERSITÀ DEGLI STUDI DI TORINO

This is an author version of the contribution published on: Questa è la versione dell'autore dell'opera:

Surface reactivity and in vitro toxicity on human bronchial epithelial cells (BEAS-2B) of nanomaterials intermediates of the production oftitanium-based composites

[Toxicology in Vitro 34 (2016) 171–178 DOI: 10.1016/j.tiv.2016.04.003] The definitive version is available at: La versione definitiva è disponibile alla URL: [http://www.journals.elsevier.com/toxicology-in-vitro/]

Surface reactivity and in vitro toxicity on human bronchial epithelial cells (BEAS-2B) of nanomaterials intermediates of the production oftitanium-based composites

Viviana Vergaro^{a,b}, Elisabetta Aldieri^{c,d}, Ivana Fenoglio^{d,e,*}, Arianna Marucco^{d,e}, Claudia Carlucci^f,
Giuseppe Ciccarella^{a,b,*}

^aBiological and Environmental Sciences Department, University of Salento, Via Monteroni 73100 Lecce, Italy

^bIstituto di Nanotecnologia (NANOTEC) University of Salento, Via Monteroni 73100 Lecce, Italy

^cDepartment of Oncology, University of Torino, Italy

^dDepartment of Chemistry and NIS – Nanostructured Interfaces and Surfaces, University of Torino, Italy

^e“G. Scansetti” Interdepartmental Centre for Studies on Asbestos and other Toxic Particulates, University of Torino, Italy,

^fDepartment of Chemistry, University of Bari, Via Orabona 4, 70126 Bari, Italy

Corresponding author:

IvanaFenoglio: Associate Professor of General and Inorganic Chemistry Department of Chemistry, University of Torino, via P. Giuria 7 10125-Torino Italy Tel. +39 116707506 e. mail:

ivana.fenoglio@unito.it

Giuseppe Ciccarella: Associate Professor Biological and Environmental Sciences Department, University of Salento, Via Monteroni 73100 Lecce, Italy Tel. +39 0832298233 e.mail:giuseppe.ciccarella@unisalento.it

Abstract

Titanium dioxide (TiO₂) nanoparticles (NPs) are manufactured worldwide in large quantities for use in a wide range of applications. Evaluating the hazards associated with TiO₂NPs is crucial as it enables risk assessment related to human and environmental exposure. In this study the in vitro human toxicity of a set of TiO₂ NPs modified with acetic, oleic and boric acids were studied in order to assess the hazard in view of a future scale-up of the synthesis. The surface reactivity of the powders under simulated solar illumination and in the dark has been evaluated by means of EPR spectroscopy. Human bronchial epithelial cells (BEAS-2B) have been chosen as a model for lung epithelium. Cytotoxicity has been assessed by measuring the cells membrane integrity by lactate dehydrogenase (LDH) assay, and the inflammatory response evaluated as nitric oxide (NO) and TNF- α production, and oxidative stress measured as intracellular reduced glutathione (GSH) levels, and induced lipoperoxidation. Aeroxide P25 was used for comparison. The results demonstrated a low photoreactivity and a toxic effects lower than Aeroxide P25 of the nano-TiO₂ powders, probably as a consequence of the presence of acidic moieties at the surface.

Keywords: TiO₂, Cytotoxicity, Oxidative stress, Inflammation, Lung, Hazard.

Introduction

In recent years there has been increasing evidence of the adverse effects related to the environmental exposure to nanoparticles, such as the enhancement in respiratory and cardiovascular mortality and morbidity and worsening of asthma (Soto 2005; Chen 2006; Soto 2007; Warheit 2007). On the other hand, the risk associated to the exposure to the growing number of engineered nanomaterials is poorly known. Many types of nanomaterials, such as silica, titanium dioxide (TiO₂), silver, carbon nanotubes, as well as some magnetic particles, have been investigated for their toxicity (Ray et al., 2009, Sharifi et al. 2012). Among them, TiO₂ nanoparticles (NP) has received a great deal of attention due to their widespread use in several products (sunscreens, cosmetics, toothpaste, pharmaceuticals, paints, plastics, self-cleaning devices and food additives) that leads to a high human and environmental exposure. Model systems for lungs are largely employed in toxicological studies since the respiratory tract is the main portal of entry of nanoparticles (Warheit, Borm et al. 2007; Park 2008). TiO₂ NPs have been shown to be toxic in several *in vitro* models and to induce pulmonary inflammatory response (Oberdörster 2000; Oberdörster, Elder et al. 2009). However, the results are often controversial (Shi 2013), mainly as a consequence of the large variety of nanosized TiO₂ commercial forms with different physicochemical characteristics available (Johnston 2009; Moschini 2013).

Many *in vitro* studies revealed cytotoxic, genotoxic and inflammatory effects induced by TiO₂ NPs that are mediated by oxygenated reactive species (ROS) generation, apoptosis and DNA damage (Dunford, Salinaro et al. 1997; Park 2008; Shi 2010; Jugan 2012). Differences in toxic response elicited depending upon the crystalline form (anatase, rutile or mixed phase samples) of TiO₂ or other physico-chemical properties such as particle size and shape, surface area, aggregation degree, agglomeration tendency and surface chemistry have been found (Bhattacharya 2009; Falck 2009; Johnston 2009; Xue 2010; Petkovic 2011).

Most of the nanotoxicological studies focus on commercial products or, when homemade, on the final products of syntheses. However, workers are exposed also to intermediates of the productions, which toxicity need to be therefore assessed.

Some of us previously reported the preparation of a series of nano-titania powders to be used as fillers in high-tech composites (Xu, Picca et al. 2013; Carlucci, Scremin et al. 2014; Carlucci, Xu et al. 2014; Carlucci, Xu et al. 2014; Xu, Carlucci et al. 2014). These materials were prepared via a microwave-solvothermal route using boric, acetic and oleic acid as the key additive reagents. The aim of this study was to assess the *in vitro* human and ecotoxicity of the three kind of TiO₂ nanopowders, in view of a future scale-up of the synthesis and, possibly, commercialization.

Illumination has been shown to play an important role in the ecotoxicity of TiO₂ (Ma, Brennan et al. 2011; Clemente, Castro et al. 2014). TiO₂ is in fact a photo-catalyzer, able to generate ROS that induce damage to aquatic species. Photo-activity has been here assessed by measuring the ability to produce free radicals under artificial solar light, to simulate the environmental conditions. As reference, a highly photo-reactive nano-TiO₂, the commercial mixed phase Aeroxide P25 (Gerloff 2012) has been used. Furthermore, human bronchial epithelial cells (BEAS-2B), a cell line widely used as model to evaluate the toxicity of

nanomaterials (Frohlich and Salar-Behzadi 2014), has been chosen to test the TiO₂ intermediates for their potential human lung toxicity, being inhalation the main route of exposure of powders in occupational setting. Cytotoxicity has been assessed by measuring the cell membrane integrity by lactate dehydrogenase (LDH) assay, the occurrence of oxidative stress by evaluating lipoperoxidation (Malondialdehyde- MDA - production) and the level of intracellular reduced glutathione (GSH), while the inflammatory response has been evaluated by measuring nitric oxide (NO) release and TNF- α production.

2. Experimental section

Materials and Methods

2.1 TiO₂ samples preparation

All chemicals were analytical-grade reagents without further purification. In a typical synthesis procedure, 1 mL titanium tetraisopropoxide (TTIP) (3.36 mmol) was slowly added into 10 mL of benzyl alcohol in a Teflon-line vessel. Acetic acid, oleic acid or boric acid were respectively added to the solution, without magnetic stirring.

The formed solution was then transferred into a Teflon vessel line (XP 1500) connected to a pressure transducer to monitor and control the pressure during the synthesis, under magnetic stirring. The microwave-assisted syntheses was conducted by using a microwave digestion system (Model. Mars, CEM, Matthews, NC). The system uses 2.45 GHz microwaves and it is controlled by temperature (210 °C) and pressure (300 psi).

The resulting product was collected and washed with methanol or diisopropylether at least three times in order to remove residues of the reaction and any by-products, and finally dried under vacuum at 50°C for 6 h. The different obtained samples were labelled as **AA**, **AO** and **AB** respectively. The synthetic conditions were reported in table 1.

Table 1. Synthetic conditions for the different samples.

Sample	Acetic Acid [mmol]	TTIP : AA Ratio	Oleic Acid [mmol]	TTIP : OA Ratio	Boric Acid [mmol]	TTIP : BA Ratio	Reaction Time
AA	6.72	1:2					45'
AO			26.9	1:8			45'
AB					6.72	1:2	1'30''

2.2 Morphological Characterization

Morphological characterizations of the TiO₂ nanopowders were performed using conventional transmission electron microscopy (TEM). Images were obtained by using a JeolJem 1011 microscope operating at an accelerating voltage of 100 kV. The samples were prepared by dropping diluted solutions of titania nanoparticles in ethanol onto 400-mesh carbon-coated copper grids and immediately evaporating the solvent.

Powder X-ray diffraction (XRD) for the phase analysis of the nanocrystals was performed with a Rigaku(Tokyo, Japan) RINT2500 diffractometer, using Cu K α monochromatic radiation

($\lambda = 1.5418 \text{ \AA}$). The XRD patterns were recorded in the range of $2\theta = 20^\circ\text{--}90^\circ$ by coupled $\theta/2\theta$ scanning mode, using 2θ increments of 0.03° . The XRD patterns were analyzed by using a whole-profile Rietveld-based fitting program (FULLPROF)(Wiles and Young 1981), according to the following procedure:

- (1) The instrumental resolution function (IRF) was evaluated by fitting the XRD pattern of a LaB_6 NIST (National Institute of Standards and Technology) standard recorded under the same experimental conditions used for measuring the samples. The IRF data file was provided separately to the program in order to allow subsequent refinement of the XRD patterns of the samples.
- (2) The phase composition of the samples was determined by fitting the XRD patterns with the crystal structure models of tetragonal TiO_2 nananatase (Inorganic Crystal Structure Database # 92363; space group: $I4_1/amd$; cell parameters: $a = b = 3.77 \text{ \AA}$ and $c = 9.43 \text{ \AA}$; $\alpha = \beta = \gamma = 90^\circ$). The weight percentage accuracy of the estimation was determined to be 5-7% w/w;
- (3) The inhomogeneous peak broadening of the anatase reflections was described by a phenomenological model based on a modified Scherrer formula:

$$\beta_{h,k,l} = \frac{\lambda}{D_{h,k,l} \cos \theta} = \frac{\lambda}{\cos \theta} \sum_{imp} a_{imp} Y_{imp}(\Theta_h, \Phi_h) \quad (1)$$

where $\beta_{h,k,l}$ was the size contribution to the integral width of the (h,k,l) reflection and Y_{imp} were the real spherical harmonics normalized according to a procedure described elsewhere (Jarvinen 1993). After refinement of the a_{imp} coefficients, the program calculated the coherent crystal apparent domain size along each reciprocal lattice vector (h,k,l) direction. The other refinable parameters were the unit cell parameters. The background was unrefined and linearly interpolated.

The nitrogen adsorption-desorption isotherms at 77 K by Brunauer–Emmett–Teller (BET) characterization were recorded with a ASiQwin system (Quantachrome, Boynton Beach, FL, USA).

2.3 Free Radical Generation

The ability of a particle to generate radical species was monitored by electron spin resonance (ESR) spectroscopy (Miniscope 100 ESR spectrometer, Magnetech, Berlin, Germany) using the spin trapping technique with 5,5-dimethyl-1-pyrroline-N-oxide (DMPO) as trapping agent according to a procedure previously described (Fenoglio, Ponti et al. 2013).

Briefly, a suspension of 30 mg of the TiO_2 powders was diluted in 125 μl buffered solution (0.5 M potassium phosphate buffer, pH 7.4) containing sodium formate (Sigma-Aldrich, St. Louis, MO) 2M (1 mM final concentration) and 125 μl of DMPO 0.17M (40 mM final concentration). The suspension was stirred at room temperature in the dark (black vials) or under simulated solar light (500 W mercury/xenon lamp -Oriel Instruments- equipped with an IR water to avoid the overheating of the suspensions and a 400 nm cut-off filter). The ESR spectra were recorded directly on aliquots of the suspension within one hour. All experiments were repeated at least twice.

The experiments were conducted under simulated solar illumination (500 W mercury/ xenon lamp, Oriel Instruments, equipped with an infrared water filter to avoid the overheating of the suspensions and a 400 nm cut-off filter) and in the dark (incubation in a dark vials).

2.6 Dispersion of TiO₂ samples in the Culture Media

The TiO₂ samples were suspended in the culture media described below at a concentration of 0,5 mg/ml in a eppendorf tube. The suspensions were sonicated for 1 min twice with a probe sonicator (Sonoplus, Bandelin, Berlin, Germany) with the following experimental setting: 100 W, 20 kHz, attenuation 40%, probe in titanium, diameter of the probe 13mm). The suspension was administered to the cell culture in reduced illumination conditions, i.e. by obscuring the hood to reduce illumination by indoor light thus avoiding photo-activation of the powders.

2.7 Hydrodynamic diameter and ζ -potential measurements

TiO₂-NP stability and tendency to aggregate in different aqueous media were investigated by dynamic light scattering and ζ -potential measurements. All samples (0.5 mg/ml) were suspended in aqueous solutions (either phosphate buffer saline solutions or cell culture medium) and dispersed according to the following protocol: (i) 1 min stirring, (ii), 30 sec-sonication (Elma Transsonic T460-H) (RO 5 power IKAMAH) and (iii) further 1 min stirring. The mean hydrodynamic diameter was calculated from the autocorrelation function of the intensity of light scattered from the particles. A Zetasizer apparatus (3000 HS, Malvern Instruments Ltd., UK) was employed on NP dispersions sufficiently diluted (0.5 mg/ml) to avoid multiple scattering. Experiments on all samples were repeated twice and data reported as average value $\pm$ standard deviation repeated twice, and data will be reported as average value $\pm$ standard deviation.

The electrophoretic mobility (ζ -potential measurements) of TiO₂-NP aggregates was measured at T = 298K by employing the Zetasizer apparatus described above and was automatically converted to ζ -potential values, by means of the instrument software based on the Henry's equation with the Smoluchowski approximation. Z-potential value of each investigated sample will be reported as the mean of data obtained for five subsequent measurements performed on each of two independently prepared dispersions. Data are reported as mean values $\pm$ standard deviation. The dispersion obtained by suspending 0.5 mg of TiO₂-NP per ml of aqueous solution was employed for the evaluation of isoelectric point (IEP) of the stable aggregates. Z-potential was determined in the 2.5–9.5 pH range: pH was measured by means of a Mettler Toledo Seven Easy pH-meter and adjusted to the desired value by using diluted NaOH and/or HCl aqueous solutions. Data are reported with an accuracy of less than 5% of error.

2.8 Cells and Reagents

Human bronchial epithelial (BEAS-2B) cells are immortalized cells obtained from American Type Culture Collection (ATCC, Manassas, VA). They were cultured in 35- (1.2×10^6 cells) or 100- (7.5×10^6 cells) mm-diameter petri dishes in RPMI 1640 medium (Gibco, Paisley, UK) supplemented with 10% fetal bovine serum (FBS) and 1% penicillin/streptomycin in a humidified incubator at 37°C in a 5% CO₂ atmosphere. The generic cell culture protocol consisted of growing the cells in an incubator at 37°C 5% CO₂ in 75 or 150 cm² flasks, replacing media every 2-3 days, and passaging before confluence by dislodging with trypsin,

washing and seeding new dishes or treatment wells. Prior to the commencement of the assay, TiO₂ samples (1-5-10 µg/cm² equal to 5-25-50 µg/mL) were sonicated (100 W: 30 sec; LabsonicSonicator; Sartorius Stedim Biotech S.A., Aubagne, France) to allow better suspension in the culture medium. Cells were incubated for 24, 48 or 72 h in the absence or presence of TiO₂. All biological experiments were performed in triplicate (n=3). The protein content of the monolayers and cell lysates was assessed with the BCA kit from Pierce (Rockford, IL).

2.9 Measurement of Leakage of Lactate Dehydrogenase (LDH) Activity

The cytotoxic effect of TiO₂ on cell membrane integrity was determined by measuring the activity of lactate dehydrogenase (LDH), released into the extracellular medium as a consequence of membrane damage (Polimeni, Gazzano et al. 2008). LDH assay is a marker of cell membrane integrity. After each incubation, extracellular medium was collected and centrifuged at 13,000 × g for 30 min. The cells (cultured in 35-mm-diameter petri dishes, 1.2 × 10⁶ cells) were washed with fresh medium, detached with trypsin/ethylenediaminetetracetic acid (EDTA; 0.05/0.02% v/v), washed with phosphate-buffered saline (PBS), resuspended in 1 ml TRAP (82.3 mM triethanolamine, pH 7.6), and sonicated on ice with two 10-s bursts. Aliquots of cell lysate (5 µl, 2.5 µg protein) and extracellular medium (50 µl/2 ml medium) were diluted with TRAP and supplemented with 0.5 mM sodium pyruvate and 0.25 mM NADH (final volume of the mix 300 µl) to start the reaction. The reaction was followed for 10 min, measuring the absorbance at 340 nm (37°C) with a Packard EL340 microplate reader (Bio-Tek Instruments, Winooski, VT). Each set of reaction kinetics was linear throughout the time of measurement. Both intracellular and extracellular enzyme activities were expressed as micromoles NADH oxidized per minute per dish, and then extracellular LDH activity (LDH out) was calculated as percent of total (intracellular + extracellular) LDH activity (LDH tot) in the dish.

2.10 Measurement of Lipid Peroxidation

Thiobarbituric acid-reactive substances (TBARS) assay was used to detect lipid peroxidation products according to Yano (Yano 1988). After 24 h of incubation in the absence or presence of different TiO₂ concentrations, cells (cultured in 60-mm-diameter petri dishes, 2.5 × 10⁶ cells) were washed with fresh medium, detached with trypsin/EDTA (0.05/0.02%, v/v), and resuspended in 1 ml PBS. A 500-µl aliquot of cell suspension, each containing the same amount of cell proteins (0.1 mg), was added to 5 µl Triton X-100 and 500 µl TBA solution (0.375% thiobarbituric acid and 30% trichloroacetic acid in 0.5 N HCl). Samples were boiled for 20 min at 100°C, rapidly cooled by immersion in an ice bath, and centrifuged for 30 s at 13,000 × g. The absorbance of 300 µl of the reaction mixture at 532 nm was read with a Packard EL340 microplate reader. TBARS values were expressed as picomoles per milligram cellular protein.

2.11 Measurement of Intracellular Glutathione

Intracellular reduced glutathione (GSH) was measured as previously described (Vandeputte, Guizon et al. 1994). Cells (cultured in 35-mm diameter petri dishes, 1.2×10^6 cells) were washed with PBS, and 600 μ l 0.01 N HCl was added to each cell monolayer. After scraping, the cells were frozen/thawed twice and proteins were precipitated by adding 120 μ l of 6.5% 5-sulfosalicylic acid to 480 μ l lysate. Each sample was placed in ice for 1 h and centrifuged for 15 min at $13,000 \times g$ (4°C). Total GSH was measured in 20 μ l cell lysate (15 μ g protein) with the following reaction mix: 20 μ l stock buffer (143 mM NaH_2PO_4 , 63mM EDTA, pH 7.4), 200 μ l daily reagent (10 mM 5,5 dithiobis-2-nitrobenzoic acid [DTNB], 2 mM NADPH in stock buffer), and 40 μ l glutathione reductase (8.5 U/mL). The kinetics of reaction was followed at 415 nm for 10 min (to check that it was linear) using a Packard microplate reader EL340. Each measurement was made in triplicate, and results were expressed as nanomoles GSH per milligram cellular protein.

2.12 Measurement of Nitric Oxide Synthesis

After a 24-h incubation, the extracellular medium was removed and tested for the content of nitrite, which is a stable derivative of nitric oxide (NO), using the Griess method as previously described (Ghigo, Aldieri et al. 1998). A blank was prepared in the absence of cells, and its absorbance was subtracted from the one measured in the samples; absorbance values were corrected for the content of cell proteins, and results were expressed as nmol/mg cellular proteins. Parallel cell-free controls containing different concentrations of particles were assayed to determine the potential interference of particles with the assay reagents.

2.13 Measurement of Tumor Necrosis Factor- α Production

After a 24-h incubation, the extracellular medium was collected and centrifuged at $13,000 g$ for 30 min. The concentration of the cytokine in the supernatant was determined by using the Conventional ELISA kit from Bender MedSystems (Vienna, Austria), following the manufacturer's instructions. Absorbance was measured at 450 nm with a Synergy HT microplate reader. The cytokine amount, corrected for the content of cell proteins, was expressed as pg/ml/mg cellular proteins. Parallel cell-free controls containing different concentrations of particles were assayed to determine the potential interference of particles with the assay reagents.

2.14 Statistical analysis

Statistical analysis was carried on results obtained from three fully independent experiments, while measures concerning each experiment were performed in duplicate or triplicate, according to the test used. All results were evaluated using one-way analysis of variance (ANOVA) with Dunnett's post-hoc comparison. Data shown in the graphs represent mean and standard deviations (SD), with level of significance indicated by the number of asterisks, the 95% confidence ($p < 0.05$) was considered significant. Statistical analyses were performed using GraphPad Prism 6 Software.

3.Results

3.1 TiO₂ nanoparticles characterization

TiO₂ nanocrystals in anatase phase were synthesized via a microwave-solvothermal route using TTIP as the precursor, benzyl alcohol as the solvent, and acetic, boric and oleic acid as the key additive reagents. This is a simple, economical method that produces highly replicable results and affords the opportunity to control the morphology and dimensions of nanometric, anatase-phase TiO₂ particles in a single step. The products, obtained without recourse to any subsequent treatment, have high anatase content, nanocrystalline-scale particle dimensions and a predominant shape. Moreover, the new method of preparation is carried out in the absence of surfactants, additional templates or other additives, thus reducing the possibility for the occurrence of phase precipitations or separations and presence of organic impurities (Xu, Picca et al. 2013; Carlucci, Scremin et al. 2014; Carlucci, Xu et al. 2014; Carlucci, Xu et al. 2014; Ciccarella Giuseppe 2014; Xu, Carlucci et al. 2014).

TEM images (figure 1, table 2) revealed differently-shaped nanocrystals. Aeroxide TiO₂ P25 is a commercial product made by pyrolysis, and consisting of 80% of anatase crystal phase and 20% of rutile. Its physical-chemical nature has been reported in several studies. However, small differences in morphology and crystallinity may be encountered depending upon the batch used. Figure 1 shows that the nanoparticles used in this study present an irregular faceted morphology and an average diameter size of about 30 nm. Sample AA has a nearly spherical or slightly elongated shape with the diameter of the nanoparticles increasing in the longitudinal side, with an average size between 2 nm and 7 nm (figure 1 (b)). Sample AB (figure 1 (c)) revealed an estimated average size for the short axis of about 5 - 6 nm, and of 7 - 8 nm for the long axis. Sample AO (figure 1 (d)) consisted of nanorods with an estimated average size between 3 nm (diameter) and 33 nm (length). The measured surface area (Table 1) well agrees with the different dimension of the primary particles. XRD analysis revealed that all prepared nanomaterials were anatase (Table 1).

Figure 1. TEM images acquired of different TiO₂ samples: (a) Aeroxide P25, (b) AA, (c) AB (d) AO. Scale bar 100 nm.

The organic acids used in the synthesis coordinate on the titania surface and provide a layer which has characteristic bands in the FT-IR spectrum. TiO₂ surface characterization was detected by the FT-IR spectra, as described in our previous works (Carlucci, Xu et al. 2014; Carlucci, Xu et al. 2014; Ciccarella Giuseppe 2014). In the FT-IR spectrum of the of TiO₂-TBsamples (see SM figure SM2), the absorption peak at 1397 cm⁻¹ can be ascribed to the vibration of tri-coordinated boron. Furthermore, absorption peaks at 1202 and 1096 cm⁻¹ could be attributed to pure B₂O₃ and incorporated BO₄ which reveal the increase of boron content. These results show that boron is probably introduced into the titania framework in the form of Ti-O-B bond.

Characterization of the nanomaterials in cell media is a prerequisite for accurate toxicological tests (Prasad 2013),(Jiang, Oberdörster et al. 2009). The aggregates/agglomerates size may be qualitatively assessed by measuring the hydrodynamic diameter of the particles/agglomerates by means of Dynamic Light Scattering (DLS), while the surface charge may be indirectly estimated by measuring the ζ -potential.

The stability of TiO₂ NP dispersions were monitored first in ultra-pure water, then in phosphate buffer solution (PBS) and then in culture medium (see SM figure SM1). In ultra-pure water all TiO₂ NPs exhibited ζ -potential values that vary depending upon the pH; as expected, an acidic point of zero charge (PZC) was found for the TiO₂ samples likely due to the presence of acidic species at the surface, i.e. acetic acid, boric acid and oleic acid used to synthesize them. In PBS, and especially in culture medium, the ζ -potential values decreased for all samples and the curves became similar, due to both an increase ionic strengths and to the adsorption of phosphate buffer and proteins (Marucco, Turci et al. 2013; Marucco, Catalano et al. 2015). With regard to stability and aggregation, in RPMI at physiological pH, all samples exhibited a similar mean size and dispersion degree, with poly dispersion index (PDI) relatively high but smaller than P25. These differences encountered among samples and P25 should not be attributed to a different repulsion among the nanoparticles, being the ζ -potential value in culture medium similar for all samples (Table 1), but likely a consequence of a reduced aggregation degree due to the different methods of synthesis .

Sample	Crystalline Phase ^a	Mean Size (TEM) nm	Surface area BET (m ² /g) ^b	Mean size in RPMI (nm) /PDI	ζ potential in RPMI (mV))
P25	Anatase 80%; Rutile 20%	30±4 (Anatase); 50±6 (Rutile)	53.0	344,0 ± 32,8 /0.691	-8.0
TiO ₂ -AA	Anatase 100%	7 (length); 2(diam)	140.3	188,8 ± 4,4 /0.310	-7.8
TiO ₂ -AB	Anatase 100%	7.0±0.9; 5.6±0,7	136.0	222,7 ± 9,2 /0.235	-7.9
TiO ₂ -AO	Anatase 100%	33.3±12.5; 3	60.2	232,4 ± 0,3 /0.357	-7.9

Table 1. Main Physico-chemical properties of the samples. ^aXRD measurements, ^bBET measurements

3.2 Surface reactivity

TiO₂ is a photo-catalyst able to generate high amount of free radical species. This reactivity is clearly related to its photo-toxicity (Dunford, Salinaro et al. 1997; Fenoglio, Ponti et al. 2013) or ecotoxicity (Ma, Brennan et al. 2011), while the role of such reactivity in the dark is still under debate (Sayes, Wahi et al. 2006; Carlotti, Ugazio et al. 2009; Petkovic 2011). Some of us previously proposed a series of protocols that may be used to assess the surface reactivity of TiO₂ (Corazzari, Livraghi et al. 2012; Fenoglio, Ponti et al. 2013). Among them, the generation of carboxyl radicals from sodium formate has been shown to be a reliable method to assess the overall oxidative capacity of TiO₂. Oxidative reactions are, in fact, the most involved in the degradative processes induced by TiO₂. The reactivity of the TiO₂ samples has been evaluated firstly by performing the reaction under simulated solar illumination (Figure 2A). As expected an intense EPR spectra, corresponding to CO₂^{•-} radicals trapped by the spin trap DMPO was recorded for P25 suggesting an high amount of radical species generated (Fenoglio, Ponti et al. 2013). Since the samples exhibit an high surface area, and are made of pure anatase, a high photo-reactivity was expected. Conversely, a very small signal was observed for all samples suggesting that the presence of organic compounds or borate at the surface inhibits the oxidative photo-reactivity of the samples.

Since inhaled powders elicit their biological effect in the dark, the experiments were repeated by keeping the suspension in a black vial. A small reactivity was still observed for P25 while the other samples appeared totally inert.

Figure 2. Surface reactivity of the TiO₂ nanomaterials measured by means of EPR spectroscopy as ability to generate carboxyl radicals from sodium formate under A) simulated solar illumination and B) dark. In the figure representative EPR spectra obtained in the various experiments are shown. The intensity is expressed in arbitrary units (A.U.)

3.3 Cytotoxicity

The prompt LDH release detected in the present study on BEAS-2B cells, beginning from 5 µg/ml, correlates with the viability reduction and indicates cell membrane damage induction as a first step of the cytotoxic process, presumably followed by other events such as apoptosis induction, demonstrated by Park and Shi

(Park 2008; Shi 2010). The TiO_2 powders were tested for their toxicity toward BEAS-2B cells at very low doses (1.0, 5.0 and 10 $\mu\text{g}/\text{cm}^2$ correspondent to 5 $\mu\text{g}/\text{ml}$, 25 $\mu\text{g}/\text{ml}$ and 50 $\mu\text{g}/\text{ml}$ respectively by measuring the membrane integrity by leakage of intracellular LDH into the extracellular medium. To assess the appropriate time for the incubation of BEAS-2B cells with TiO_2 samples, time dependent experiments were performed (data not shown). As a consequence of these preliminary results, we evaluated LDH leakage after 72 hours of incubation with increasing concentration of titania nanoparticles as reported in Fig. 3.

A little cytotoxic effects were observed after cellular incubation with ~~for~~ the sample AB at the concentration of 25 $\mu\text{g}/\text{ml}$: however, all the other samples exerted no significant cytotoxic effects after cellular incubation with synthesized TiO_2 nanoparticles, and did not induce significant LDH leakage after any time period of incubation. Conversely, even at the lowest tested dose, P25 induced a significant cytotoxicity.

Figure 3: Effect of titanium dioxide nanoparticles on BEAS-2B cell membrane damage measured by the LDH assay. Cells were incubated with 1.0 (gray), 5.0 (white) and 10 (black) $\mu\text{g}/\text{cm}^2$ of the different TiO_2 samples for 72 hours. Values are expressed as the mean $\pm$ standard deviation of three independent experiments ($n = 3$). The 95% confidence ($p < 0.05$) was considered significant vs control (straight line). * $p < 0.05$ was considered significant. vs respective control: * $p < 0.01$; ** $p < 0.001$; *** $p < 0.0001$.

3.4 Induction of inflammatory markers

Nanoparticles have been shown to alter the redox homeostasis of cells and to induce inflammation (Foster, Galeffi et al. 2006; Park, Yi et al. 2008). TiO_2 has been reported to lead to oxidative stress and to induce the release of inflammatory markers (Shi 2013), however the exact mechanisms are still unclear.

The inflammatory response was assessed by measuring the extracellular levels of nitrite (the stable derivative of nitric oxide, NO) and the production of tumor necrosis factor- α (TNF- α). NO is a free radical with multiple biological functions that is overproduced by different cell types after an oxidative stress and/or inflammation induction evoked by NPs exposure. It is involved in immune response but, during a chronic inflammatory reaction, elevated levels of NO are found that became toxic for host cells. The role of NO in the cytotoxic immune response was first revealed by demonstrating the induction of the inducible NO Synthase (NOS, the enzyme responsible for NO synthesis and induced by oxidative stress), in target cells by immune cytokines (e.g. TNF- α , etc.) and resulting in the apoptosis induction (Bogdan 2015).

Detection of tumor necrosis factor-alpha (TNF- α) release was performed to evaluate the inflammatory effects as this cytokine represents important mediator of pulmonary inflammation in humans.

TNF- α is a pro-inflammatory cytokine involved in systemic inflammation, stimulating the acute phase reaction.

The control sample P25 induced a strong release of NO in BEAS-2B cells (Figure 4) in concentration dependent manner, while a much less effect, albeit significant, was observed after TiO₂-AA TiO₂-AB and TiO₂-AO cellular exposure. In particular, the exposure to 5.0 and 10 $\mu\text{g}/\text{cm}^2$ of P25 lead to a 3 times higher releasing of NO than our synthesized samples.

Figure 4: Effect of titanium dioxide nanoparticles on BEAS-2B for extracellular levels of nitrite. Cells were incubated with 1.0 (gray), 5.0 (white) and 10 (black) $\mu\text{g}/\text{cm}^2$ of the different TiO_2 samples for 72 hours. Values are expressed as the mean $\pm$ standard deviation of three independent experiments ($n = 3$). The 95% confidence ($p < 0.05$) was considered significant vs control (straight line) * $p < 0.05$ was considered significant. vs respective control: * $p < 0.01$; ** $p < 0.001$; *** $p < 0.0001$.

The accumulation of $\text{TNF-}\alpha$ concentration was significantly increased in a concentration dependent manner both for synthesized samples and for commercial one (Fig.5). For the lowest concentration tested of our samples there is no significant $\text{TNF-}\alpha$ production in comparison to the same tested concentration of P25. TiO_2 -AA did not elicit any effect to cells also at the other higher concentrations. TiO_2 -AB and TiO_2 -AO led to the production of this cytokine but the measured values are lower than those measured for P25.

A trend similar to NO release was observed, being P25 the most active while TiO_2 -AA did not elicit any effect to cells.

Note that cell-free tests aimed to reveal any interference of the particles with the assay reagents were performed (data not shown).

Figure 5: Effect of titanium dioxide nanoparticles on BEAS-2B for $\text{TNF-}\alpha$ production. Cells were incubated with 1.0 (gray), 5.0 (white) and 10 (black) $\mu\text{g}/\text{cm}^2$ of the different TiO_2 samples for 72 hours. Values are expressed as the mean $\pm$ standard deviation of three independent experiments ($n = 3$). The 95% confidence ($p < 0.05$) was considered significant vs control (straight line). * $p < 0.05$ was considered significant. vs respective control: * $p < 0.01$; ** $p < 0.001$; *** $p < 0.0001$.

3.4 Oxidative stress

To elucidate the role of oxidative stress in toxic effect evoked by nanoparticles, lipoperoxidation was evaluated by measuring the intracellular levels of TBARS, which are molecules (such as malonyldialdehyde and other aldehydes) produced by oxidative degradation of fatty acids. After a 72 h incubation, the generation of TBARS was not significantly increased in cells exposed both to synthetic TiO_2 , and P25 (see

SM figure SM3) at $10 \mu\text{g}/\text{cm}^2$. The level of reduced glutathione (GSH), the most important intracellular antioxidant molecule, is a sensitive index of the efficiency of cellular antioxidant defenses and its decrease is a marker of oxidative stress. In our cellular model, GSH levels resulted decreased after incubation with TiO_2 nanoparticles. However the differences observed between treated cells and controls were not statistically significant (see SM figure SM4).

4. Discussion

Recent studies provide strong evidence that nanoparticles can not only passively interact with cells (Nel, Xia et al. 2006; Thill, Zeyons et al. 2006; Auffan, Achouak et al. 2008; Gratton, Ropp et al. 2008), but also interfere with molecular processes that are essential for regulating cell functions (Jiang, Kim Betty et al. 2008).

In the present study, we have investigated the photoactivity and the cellular toxicity of three TiO_2 nanomaterials in anatase phase synthesized via a microwave-solvothermal route, in comparison to the known toxic Aeroxide P25, in terms of cytotoxicity and induction of oxidative stress and inflammatory markers evaluation.

Characterization in cell media showed little differences among samples in term of ζ potential and dispersion state, but a smaller polydispersion index (PDI) with respect to P25. Under simulated solar illumination the samples showed a very little oxidative reactivity when compared with P25. The observed low oxidative reactivity may be relevant for ecotoxicity of the nanomaterials accidentally released in the environment during the life cycle of the composite. No reactivity was detected in dark conditions possibly thus excluding particle-derived ROS release in the body. Note however that the possible generation of superoxide radicals or singlet have not been assessed in the present study. In the case of nanoparticles doped with boron, a decrease in photoactivity was also observed. In this case, the effect should not be due to the presence of a coating, but rather to the inhibitory effect of boron. In fact, doping with boron was reported to both increase or decrease the photocatalytic activity of TiO_2 depending upon the synthetic method used (Xu, Picca et al. 2013).

P25 appears clearly cytotoxic and induces an oxidative stress and an inflammatory response in our cellular model at relatively low doses. Ekstrand-Hammarström and co-workers previously found that Aeroxide P25 did not induce cytotoxic effect on BEAS-2B cells up to $200 \mu\text{g}/\text{mL}$ (Ekstrand-Hammarström 2012). Their results were in contrast with what found by Park and coworkers that reported a significant cytotoxicity already at $5 \mu\text{g}/\text{mL}$ (Park, Yi et al. 2008). The different results were suggested to be due to the absence of serum in the cell media (Ekstrand-Hammarström 2012). Our results support the hypothesis since the experiments were performed in RPMI supplemented with 10% FBS, the same conditions used by Park and co-workers.

Albeit cytotoxic and pro-inflammatory in BEAS-2B cells, P25 did not induce lipoperoxidation in our cellular model, suggesting a ROS generation by independent mechanism. This is consistent with the previous studies since ROS generation was reported to be induced by P25 on BEAS-2B cells (Park, Yi et al. 2008; Ekstrand-

Hammarström, Akfur et al. 2011) but at higher doses. A possible mechanism involves TNF α release, that can stimulate signalling pathways associated to the inflammatory reaction, such as Jak/STAT (Rauch, Muller et al. 2013), which can increase cytokines production (IL-4, IL-6, IL-8) and oxidative stress, the latter via inducing NO and reactive nitrogen species (RNS) production. Therefore, RNS may induce redox-sensitive transcription factors such as NF- κ B (Haddad 2002), which in turn may contribute to increase the cross-talk between oxidative stress and inflammation in the lung, by promoting further cytokines and NO production. Conversely to Aeroxide P25, the modified TiO₂ samples exhibited low cytotoxicity as measured by the LDH assay toward BEAS-2B cells. However, cells exposed to powders showed release of NO and TNF α , depending upon the kind of moieties at the surface of the nanoparticles. In fact, while TiO₂-AA was inert at the tested doses, TiO₂-AB and TiO₂-AO induced the release of NO and TNF α , albeit at much less extent than P25.

The data here reported overall suggest a toxicity of the TiO₂ samples much lower than P25, TiO₂-AA being the less toxic among the synthesized samples. Based on the wide literature on this topic, this finding may be related to differences in physico-chemical properties among samples. One possible reason may be the different dispersion state of the samples by respect to P25 that, in turn, may affect the internalization in cells (Ekstrand-Hammarström, Akfur et al. 2011). Another property that modulate the toxic effects is the crystalline phase: there are several studies reporting P25 to be more toxic than the other polymorphs (Gerloff, Fenoglio et al. 2012), despite the presence of the rutile phase, generally considered less toxic (Sayes, Wahi et al. 2006). On the other hand Gurret *al.* reported that an anatase sample, having a primary particle size similar to those tested here, induced oxidative DNA damage, lipid peroxidation, and micronuclei formation, and increased hydrogen peroxide and nitric oxide production in BEAS-2B cells (Gurr, Wang et al. 2005). The role of surface area in TiO₂ toxicity is generally accepted (Oberdörster 2000; Singh, Shi et al. 2006). However, in the present case, the TiO₂ samples exhibit a surface area higher than P25, but a lower toxicity. The samples tested here are slightly different in terms of shape of the primary particles. Shape, is considered a determinant of toxicity (Fadeel, Xue et al. 2010). However previous reports did not find any correlation among shape and toxicity of TiO₂ NP (Ravenzwaay, Landsiedel et al. 2009). Finally, as suggested by the ζ -potential values recorded in water, all samples exhibit acidic species at the surface. These species may be responsible of both the reduced oxidative photo-reactivity and toxicity by forming a coating around the particles. Since coatings or adsorbed species have been previously reported to inhibit or modify the surface reactivity (Brezova, Gabcova et al. 2005; Sayes, Wahi et al. 2006; Carlotti, Ugazio et al. 2009; Tiano, Armeni et al. 2010; Shi 2013; Ghiazza, Alloa et al. 2014) and possibly the toxicity of TiO₂ a major role of surface chemistry in the encountered differences may be hypothesized.

Conclusion

In conclusion the modified TiO₂ samples appear to have a low photoreactivity and to elicit low or negligible toxic effects on human bronchial epithelial cells depending upon the kind of synthetic method used. Albeit further studies will be needed to fully assess the safety of these intermediates, the present data represent a

first indication of low toxicity, the toxic effect elicited by the powders being much lower than the reference material AeroxideP25, already known as cytotoxic.

Acknowledgements

This work was supported by the PON, prot. n. 84/Ric. Del 2 marzo 2012 NAnoMAteriali per l'edilizia SosTEnibile (NAMASTE) prot. PON04a3_00107 CUP: B35I12000100005.

References

- Auffan, M., W. Achouak, et al. (2008). "Relation between the Redox State of Iron-Based Nanoparticles and Their Cytotoxicity toward *Escherichia coli*." Environmental Science & Technology **42**(17): 6730-6735.
- Bhattacharya, K. (2009). "Titanium dioxidenanoparticles induce oxidative stress and DNA-adduct formation but not DNA-breakage in human lung cells." Part. Fibre Toxicol. **6**: 17.
- Bogdan, C. (2015). "Nitric oxide synthase in innate and adaptive immunity: an update." Trends Immunol **36**(3): 161-78.
- Brezova, V., S. Gabcova, et al. (2005). "Reactive oxygen species produced upon photoexcitation of sunscreens containing titanium dioxide (an EPR study)." J Photochem Photobiol B **79**(2): 121-34.
- Carlotti, M. E., E. Ugazio, et al. (2009). "Role of particle coating in controlling skin damage photoinduced by titania nanoparticles." Free radical research **43**(3): 312-322.
- Carlucci, C., B. Scremin, et al. (2014). "Microwave-Assisted Synthesis of Boron-Modified TiO₂ Nanocrystals." Inorganics **2**(2): 264-277.
- Carlucci, C., H. Xu, et al. (2014). "Selective synthesis of TiO₂ nanocrystals with morphology control with the microwave-solvothermal method." CrystEngComm **16**(9): 1817-1824.
- Carlucci, C., H. Xu, et al. (2014). "Controllable One-Pot Synthesis of Anatase TiO₂ Nanorods with the Microwave-Solvothermal Method." Science of Advanced Materials **6**(8): 1668-1675.
- Chen, H. W. (2006). Titanium dioxide nanoparticles induce emphysema-like lung injury in mice, The Federation. **20**.
- Ciccarella Giuseppe, C. C. (2014). "TiO₂ nanoparticles synthesis, under shape and size control by means of microwave reaction." Patent 29.10.2014, EP2796414A1.
- Clemente, Z., V. L. Castro, et al. (2014). "Toxicity assessment of TiO₂ nanoparticles in zebrafish embryos under different exposure conditions." Aquat Toxicol **147**: 129-39.
- Corazzari, I., S. Livraghi, et al. (2012). "Inactivation of TiO₂ nano-powders for the preparation of photo-stable sunscreens via carbon-based surface modification." Journal of materials chemistry **22**(36): 19105-19112.
- Dunford, R., A. Salinaro, et al. (1997). "Chemical oxidation and DNA damage catalysed by inorganic sunscreen ingredients." FEBS Letters **418**(1-2): 87-90.
- Ekstrand-Hammarström, B., C. M. Akfur, et al. (2011). "Human primary bronchial epithelial cells respond differently to titanium dioxide nanoparticles than the lung epithelial cell lines A549 and BEAS-2B." Nanotoxicology **6**(6): 623-634.
- Fadeel, B., D. Xue, et al. (2010). "Programmed cell clearance: molecular regulation of the elimination of apoptotic cell corpses and its role in the resolution of inflammation." Biochemical and biophysical research communications **396**(1): 7-10.
- Falck, G. C. (2009). "Genotoxic effects of nanosized and fine TiO₂." Human & experimental toxicology **28**: 339-352.
- Fenoglio, I., J. Ponti, et al. (2013). "Singlet oxygen plays a key role in the toxicity and DNA damage caused by nanometric TiO₂ in human keratinocytes." Nanoscale **5**(14): 6567-76.

- Foster, K. A., F. Galeffi, et al. (2006). "Optical and pharmacological tools to investigate the role of mitochondria during oxidative stress and neurodegeneration." *Prog Neurobiol* **79**(3): 136-71.
- Frohlich, E. and S. Salar-Behzadi (2014). "Toxicological assessment of inhaled nanoparticles: role of in vivo, ex vivo, in vitro, and in silico studies." *Int J Mol Sci* **15**(3): 4795-822.
- Gerloff, K., I. Fenoglio, et al. (2012). "Distinctive toxicity of TiO₂ rutile/anatase mixed phase nanoparticles on Caco-2 cells." *Chemical research in toxicology* **25**(3): 646-655.
- Ghiazza, M., E. Alloa, et al. (2014). "Inhibition of the ROS-mediated cytotoxicity and genotoxicity of nano-TiO₂ toward human keratinocyte cells by iron doping." *Journal of nanoparticle research : an interdisciplinary forum for nanoscale science and technology* **16**(2).
- Ghigo, D., E. Aldieri, et al. (1998). "Chloroquine stimulates nitric oxide synthesis in murine, porcine, and human endothelial cells." *J Clin Invest* **102**(3): 595-605.
- Gratton, S. E. A., P. A. Ropp, et al. (2008). "The effect of particle design on cellular internalization pathways." *Proceedings of the National Academy of Sciences* **105**(33): 11613-11618.
- Gurr, J. R., A. S. Wang, et al. (2005). "Ultrafine titanium dioxide particles in the absence of photoactivation can induce oxidative damage to human bronchial epithelial cells." *Toxicology* **213**(1-2): 66-73.
- Haddad, J. J. (2002). "Redox regulation of pro-inflammatory cytokines and IκB-α/NF-κB nuclear translocation and activation." *Biochemical and Biophysical Research Communications* **296**(4): 847-856.
- Jarvinen, M. (1993). "Application of symmetrized harmonics expansion to correction of the preferred orientation effect." *Journal of Applied Crystallography* **26**(4): 525-531.
- Jiang, J., G. Oberdörster, et al. (2009). "Characterization of size, surface charge, and agglomeration state of nanoparticle dispersions for toxicological studies." *Journal of Nanoparticle Research* **11**(1): 77-89.
- Jiang, W., Y. S. KimBetty, et al. (2008). "Nanoparticle-mediated cellular response is size-dependent." *Nat Nano* **3**(3): 145-150.
- Johnston, H. J. (2009). "Identification of the mechanisms that drive the toxicity of TiO₂ particulates: the contribution of physicochemical characteristics." *Part. Fibre Toxicol.* **6**: 33.
- Jugan, M. L. (2012). "Titanium dioxide nanoparticles exhibit genotoxicity and impair DNA repair activity in A549 cells." *Nanotoxicology* **6**: 501-513.
- Ma, H., A. Brennan, et al. (2011). "Phototoxicity of TiO₂ nanoparticles under solar radiation to two aquatic species: *Daphnia magna* and Japanese medaka." *Environmental toxicology and chemistry* **31**(7): 1621-1629.
- Marucco, A., F. Catalano, et al. (2015). "Possible Chemical Source of Discrepancy between in Vitro and in Vivo Tests in Nanotoxicology Caused by Strong Adsorption of Buffer Components." *Chemical research in toxicology* **28**(1): 87-91.
- Marucco, A., F. Turci, et al. (2013). "Hydroxyl density affects the interaction of fibrinogen with silica nanoparticles at physiological concentration." *Journal of colloid and interface science* **419**: 86-94.
- Moschini, E. (2013). "The modality of cell-particle interactions drives the toxicity of nanosized CuO and TiO₂ in human alveolar epithelial cells." *Toxicology Letters* **222**: 102-116.
- Nel, A., T. Xia, et al. (2006). "Toxic potential of materials at the nanolevel." *Science* **311**(5761): 622-7.
- Oberdörster, G. (2000). "Pulmonary effects of inhaled ultrafine particles." *International Archives of Occupational and Environmental Health* **74**(1): 1-8.
- Oberdörster, G., A. Elder, et al. (2009). "Nanoparticles and the Brain: Cause for Concern?" *Journal of Nanoscience and Nanotechnology* **9**(8): 4996-5007.
- Park, E.-J., J. Yi, et al. (2008). "Oxidative stress and apoptosis induced by titanium dioxide nanoparticles in cultured BEAS-2B cells." *Toxicology Letters* **180**(3): 222-229.
- Park, E. J. (2008). "Oxidative stress and apoptosis induced by titanium dioxide nanoparticles in cultured BEAS-2B cells." *Toxicology Letters* **180**: 222-229.
- Petkovic, J. (2011). "DNA damage and alterations in expression of DNA damage responsive genes induced by TiO₂ nanoparticles in human hepatoma HepG2 cells." *Nanotoxicology* **5**: 341-353.
- Polimeni, M., E. Gazzano, et al. (2008). "Quartz inhibits glucose 6-phosphate dehydrogenase in murine alveolar macrophages." *Chem Res Toxicol* **21**(4): 888-94.

- Prasad, R. Y. (2013). "Effect of treatment media on the agglomeration of titanium dioxide nanoparticles: impact on genotoxicity, cellular interaction, and cell cycle." ACS Nano **7**: 1929-1942.
- Rauch, I., M. Muller, et al. (2013). "The regulation of inflammation by interferons and their STATs." JAK-STAT **2**(1): e23820.
- Ravenzwaay, B., R. Landsiedel, et al. (2009). "Comparing fate and effects of three particles of different surface properties: nano-TiO₂, pigmentary TiO₂ and quartz." Toxicology letters **186**(3): 152-159.
- Sayes, C. M., R. Wahi, et al. (2006). "Correlating nanoscale titania structure with toxicity: a cytotoxicity and inflammatory response study with human dermal fibroblasts and human lung epithelial cells." Toxicol Sci **92**(1): 174-85.
- Shi, H. (2013). "Titanium dioxide nanoparticles: a review of current toxicological data." Part. Fibre Toxicol. **10**: 15.
- Shi, Y. (2010). "Titanium dioxide nanoparticles cause apoptosis in BEAS-2B cells through the caspase 8/t-Bid-independent mitochondrial pathway." Toxicology Letters **196**: 21-27.
- Singh, S., T. Shi, et al. (2006). "Endocytosis, oxidative stress and IL-8 expression in human lung epithelial cells upon treatment with fine and ultrafine TiO₂: role of the specific surface area and of surface methylation of the particles." Toxicology and applied pharmacology **222**(2): 141-151.
- Soto, K. (2007). "Cytotoxic effects of aggregated nanomaterials☆." Acta biomaterialia **3**(3): 351-358.
- Soto, K. F. (2005). "Comparative in vitro cytotoxicity assessment of some manufacturednanoparticulate materials characterized by transmissionelectron microscopy." Journal of nanoparticle research : an interdisciplinary forum for nanoscale science and technology **7**(2-3): 145-169.
- Thill, A., O. Zeyons, et al. (2006). "Cytotoxicity of CeO₂ Nanoparticles for Escherichia coli. Physico-Chemical Insight of the Cytotoxicity Mechanism." Environmental Science & Technology **40**(19): 6151-6156.
- Tiano, L., T. Armeni, et al. (2010). "Modified TiO₂ particles differentially affect human skin fibroblasts exposed to UVA light." Free Radic Biol Med **49**(3): 408-15.
- Vandeputte, C., I. Guizon, et al. (1994). "A microtiter plate assay for total glutathione and glutathione disulfide contents in cultured/isolated cells: performance study of a new miniaturized protocol." Cell Biology and Toxicology **10**(5-6): 415-421.
- Warheit, D. B. (2007). "Pulmonary toxicity study in rats with three forms of ultrafine-TiO₂ particles: Differential responses related to surface properties." Toxicology (Amsterdam) **230**(1): 90-104.
- Warheit, D. B., P. J. A. Borm, et al. (2007). "Testing Strategies to Establish the Safety of Nanomaterials: Conclusions of an ECETOC Workshop." Inhalation Toxicology **19**(8): 631-643.
- Wiles, D. B. and R. A. Young (1981). "A new computer program for Rietveld analysis of X-ray powder diffraction patterns." Journal of Applied Crystallography **14**(2): 149-151.
- Xu, H., C. Carlucci, et al. (2014). "Synthesis of Ultrafine Anatase Titanium Dioxide (TiO₂) Nanocrystals by the Microwave-Solvothermal Method." Journal of Nanoengineering and Nanomanufacturing **4**(1): 28-32.
- Xu, H., R. A. Picca, et al. (2013). "Nonhydrolytic Route to Boron-Doped TiO₂ Nanocrystals." European Journal of Inorganic Chemistry **2013**(3): 364-374.
- Xue, C. (2010). "Nano titanium dioxide induces the generation of ROS and potential damage in HaCaT cells under UVA irradiation." J. Nanosci. Nanotechnol. **10**: 8500-8507.
- Yano, E. (1988). "Mineral fiber-induced malondialdehyde formation and effects of oxidant scavengers in phagocytic cells." International Archives of Occupational and Environmental Health **61**(1-2): 19-23.

Surface reactivity and in vitro toxicity on human bronchial epithelial cells (BEAS-2B) of nanomaterials intermediates of the production of titania-based composites

Viviana Vergaro^{a,b}, Elisabetta Aldieri^{c,d}, Ivana Fenoglio^{d,e*}, Arianna Marucco^{d,e}, Claudia Carlucci^f,
Giuseppe Ciccarella^{a,b*}

^a Biological and Environmental Sciences Department, University of Salento, Via Monteroni 73100 Lecce, Italy

^b Istituto di Nanotecnologia (NANOTEC) University of Salento, Via Monteroni 73100 Lecce, Italy

^c Department of Oncology, University of Torino, Italy

^d Department of Chemistry and NIS – Nanostructured Interfaces and Surfaces, University of Torino, Italy

^e “G. Scansetti” Interdepartmental Centre for Studies on Asbestos and other Toxic Particulates, University of Torino, Italy,

^f Department of Chemistry, University of Bari, Via Orabona 4, 70126 Bari, Italy

Contents:

- 1. ζ - potential measurements**
- 2. FT-IR Spectra**
- 3. TBARS**
- 4. GSH**

SM1: ζ -Potential Variation of TiO₂ samples measured in different dispersant: (a) ultra-pure water, (b) PBS buffer and (c) RPMI culture media. The curves are measured after the suspension of samples nanoparticles, TA (circle), TO (rhombus), TB (star) and P25 (square) in the different solutions after 2 min of sonication. The acquisition of these curves is repeated for three times.

SM2: FT-IR Spectra of TA (black) TO (red) and TB (blue)

SM3: Effect of TiO₂ NPs on the production of thiobarbituric acid reactive substances (TBARS) in BEAS-2B cells. Cells were incubated for 72 h in the absence (ctrl) or presence of 10 µg/cm² of commercial Aeroxide P25 or synthetic TiO₂ NPs (Ta, TB and TO). Values are expressed as the mean and standard deviation, n = 3. The 95% confidence (p < 0.05) was considered significant vs control. There are no differences statistically significant.

SM4: Effect of TiO_2 NPs on the intracellular levels of reduced (GSH) in BEAS-2B cells. Cells were incubated for 72 h in the absence (ctrl) or presence of 1 (grey), 5 (white) or 10 (black) $\mu\text{g}/\text{cm}^2$ of Aeroxide P25 or synthetic TiO_2 NPs (AA, AB and AO). Values are expressed as the mean and standard deviation, $n = 3$. The 95% confidence ($p < 0.05$) was considered significant vs control. There are no differences statistically significant.