

AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Photoinduced Ethylene Polymerization on the CrVI/SiO₂ Phillips Catalyst

This is the author's manuscript

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/1724411> since 2020-01-22T12:37:49Z

Published version:

DOI:10.1021/acs.jpcc.8b08118

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

Photo-Induced Ethylene Polymerization on the Cr^{VI}/SiO₂ Phillips Catalyst

Lorenzo Mino,^{a,*} Caterina Barzan,^a Giorgia A. Martino,^a Alessandro Piovano,^a Giuseppe Spoto,^a Adriano Zecchina,^{a,*} and Elena Groppo^a

Department of Chemistry, NIS Centre and INSTM, University of Torino, via Pietro Giuria 7, Torino, Italy

*Corresponding authors e-mail addresses: lorenzo.mino@unito.it, adriano.zecchina@unito.it

Abstract

Herein we report on two photo-induced reactions occurring at the surface of the Cr^{VI}/SiO₂ Phillips catalyst. The first is the photo-reduction of Cr^{VI}/SiO₂ in CO at room temperature, that leads to the reduction of a fraction of the Cr^{VI} sites to Cr^{IV}(=O) intermediates and then to Cr^{II}. With respect to the thermal reduction of Cr^{VI}/SiO₂ in CO, the relative amount of highly uncoordinated Cr^{II} sites is larger, suggesting that the relaxation of the Cr^{II} sites at the silica surface strongly depends on the temperature at which they are formed. The second is the photo-induced ethylene polymerization on Cr^{VI}/SiO₂ at room temperature that is reported here for the first time. We demonstrate that UV-Vis light has the potential to trigger the reduction of chromates by ethylene and the successive ethylene polymerization. DR UV-Vis and FT-IR spectroscopies allowed us to identify the nature of the Cr sites involved in the polymerization (i.e. 6-fold coordinated Cr^{II}) and of the oxidized by-products remaining in their coordination sphere, which are methylformate and ethylene oxide. While the former was previously observed during the thermally-induced ethylene polymerization on Cr^{VI}/SiO₂, the latter was never observed.

1. Introduction

Chromium(VI) supported on amorphous silica is one of the most used catalyst in the petrochemical industry, affording more than one third of all the High Density Polyethylene (HDPE) produced worldwide and also a large fraction of Linear Low Density Polyethylene (LLDPE).¹⁻³ Due to its apparent simplicity, it has been the object of fundamental studies since more than half a century. Since the beginning, most of the efforts have been devoted to correlate the structural and electronic properties of the chromium sites to the peculiar performances of this catalyst in ethylene polymerization,⁴⁻¹⁰ such as its ability to polymerize ethylene without any activator or the very broad molecular weight distribution of the produced HDPE. These properties place the Phillips catalyst in an unique position in the polyethylene market when compared to its competitors.¹ Direct spectroscopic methods applied on model versions of the catalyst – such as the CO-reduced form ($\text{Cr}^{\text{II}}/\text{SiO}_2$),^{6,8,11-17} or systems obtained from well-defined $\text{Cr}^{\text{VI-n}}$ organometallic precursors,¹⁸⁻²⁴ or even planar models suitable for surface science investigation²⁵⁻³³ – have played the major role in the characterization of the active sites at a molecular level, while the mechanism of ethylene polymerization has been mainly investigated by means of theoretical calculation.^{23,34-43}

A crucial feature that distinguishes the Phillips catalyst from most of its competitors in olefin polymerization is its capability to start the polymerization reaction in the absence of any Al-alkyl activator, a fact that simplifies its handling in the polymerization reactor, but also opens some question on the polymerization mechanism and on the nature of the active sites. The Phillips catalyst enters the polymerization reactor after being activated in oxidizing conditions at a temperature higher than 600 °C. This procedure mainly gives isolated hexavalent chromates^{6,8,11,44-48} (hereafter Cr^{VI}), and possibly also a small amount of mono-oxo CrO_5 ,^{40,49-54} grafted on the surface of a highly dehydroxylated silica. Hence, the catalyst is not alkylated when it goes into the reactor, that is, it has no Cr–alkyl bond into which ethylene may be inserted. The Cr^{VI} sites are slowly reduced by ethylene at the reaction temperature (ca. 100 °C) during a variable induction time that can last also some hours, and successively transformed into the (alkylated) active sites. Although the two steps (reduction and alkylation) cannot be separated in the industrial reactor, many experimental evidences have been accumulated in the academic laboratories indicating that, during the reduction step, the Cr^{VI} sites are reduced to Cr^{II} precursors.^{1,4,6,9,10,55-58} For a long time it was considered that the oxidized by-products deriving from ethylene oxidation left the surface of the catalyst at the reaction temperature and that therefore the precursors of the active sites were low-coordinated Cr^{II} species, similar to those obtained by reducing the $\text{Cr}^{\text{VI}}/\text{SiO}_2$ in CO at 350 °C.⁵⁹⁻⁶² Only recently this concept has been revolutionized, due to the observation that the oxidized by-

products (ketones, aldehydes, carboxylates or esters) do not desorb into the gas phase at temperatures below 250 °C, which suggests that under commercial polymerization conditions oxygenates may remain attached to the chromium sites.^{63,64}

On the whole, it is clear that the reducing ability of ethylene towards the chromates is quite poor. This is one of the reason why often, in the industrial practice, specific reducing agents are added in the reactor before or together with the ethylene injection, aimed at shortening (or even eliminating) the induction time, and/or at performing ethylene polymerization at lower temperature.^{1,65-69} In this work we explore, for the first time, the use of UV-Vis light to trigger the ethylene polymerization on the Cr^{VI}/SiO₂ catalyst at room temperature, without the addition of any activator. The idea had the inception from the documented knowledge that highly dispersed and isolated Cr^{VI} sites in the form of monochromates supported on silica can operate as efficient photocatalysts for a wide range of reactions under visible light irradiation, such as for the decomposition of NO, for the partial oxidation of propane with molecular oxygen and for the selective oxidation of CO in the presence of H₂.⁷⁰⁻⁷⁴ In particular, it has been demonstrated that visible-light irradiation of tetrahedrally coordinated Cr^{VI}(=O)₂ species produces the excited triplet state Cr^V(=O)(O^{•-})*, which behaves as an active site for oxidation. Moreover, more than 20 years ago, Kohler and Ekerdt demonstrated the possibility to photoreduce the Cr^{VI}/SiO₂ catalyst in CO.⁷⁵ These examples prompted us to develop an experimental set-up to monitor the Cr^{VI}/SiO₂ catalyst *during* the UV-Vis light irradiation in the presence of ethylene at room temperature, by means of FT-IR and DR UV-Vis spectroscopies. By combining these two sensitive methods, we have been able to: 1) observe the gradual reduction of the chromates; 2) investigate the properties of the reduced chromium sites; 3) detect the by-products of ethylene oxidation, and 4) demonstrate the occurrence of ethylene polymerization at room temperature.

2. Experimental

The Cr^{VI}/SiO₂ sample (Cr loading 1 wt%) was prepared by wet-impregnation of a pyrogenic silica (Aerosil, surface area *ca.* 380 m²g⁻¹) employing CrO₃ as chromium precursor. The catalyst was activated directly inside the measurement cells, to avoid any type of contamination. The activation procedure consisted in two main steps: i) activation at 650 °C in dynamic vacuum (residual pressure < 10⁻⁴ mbar) in order to dehydroxylate the silica surface, and ii) subsequent oxidation in O₂ (equilibrium pressure *ca.* 100 mbar, twice) at the same temperature to graft the Cr species in the form of monochromates.^{6,8,11,44-46} The Cr^{III}/SiO₂ reference sample was obtained from Cr^{VI}/SiO₂ after further reduction in CO (equilibrium pressure *ca.* 100 mbar, twice) at 350 °C, followed by degassing at the same temperature.⁶ For both FT-IR and DR UV-Vis-NIR measurements the sample was prepared in the form of a self-supporting pellet, having a surface density of *ca.* 10 mg cm⁻² and 60 mg cm⁻², respectively.

The FT-IR spectra were recorded on a Bruker IFS 28 FTIR spectrometer, equipped with a MCT cryogenic detector, averaging 64 interferograms recorded at 2 cm⁻¹ resolution. Diffuse reflectance (DR) UV-Vis-NIR spectra were recorded on a Cary 5000 Varian spectrophotometer equipped with a reflectance sphere. In both cases, UV-Vis irradiation was performed using a Newport 500 W Hg(Xe) arc lamp, equipped with a water filter to eliminate the infrared portion of the spectrum. For *in situ* UV-Vis irradiation during the FT-IR experiments, the radiation was focused on the sample using an aspherical fiber bundle focusing assembly and a large core liquid light guide.⁷⁶⁻⁷⁸ This experimental set-up reduces the amount of photons reaching the sample, but allows collecting FT-IR spectra during continuous UV-Vis irradiation. In contrast, for UV-Vis irradiation during the DR UV-Vis-NIR experiments, the radiation was not focused. This experimental set-up maximizes the number of photons reaching the sample, but does not allow collecting DR UV-Vis-NIR spectra simultaneously to the irradiation.

3. Results and discussion

3.1 Photo-reduction of Cr^{VI}/SiO₂ in CO at room temperature

Initially, we followed by *in situ* FT-IR spectroscopy the photo-reduction of Cr^{VI}/SiO₂ under UV-Vis irradiation in the presence of CO (P_{CO} = 100 mbar) at room temperature, aimed at validating our experimental set-up. Figure 1a shows the FT-IR spectrum of Cr^{VI}/SiO₂ before (spectrum 1) and after 60 minutes of irradiation in CO (spectrum 2), while Figure 1a' shows all the spectra collected at intermediate irradiation time, in the ν(CO) region and after subtraction of spectrum 1. The spectrum of Cr^{VI}/SiO₂ is characterized by a narrow band at 3745 cm⁻¹ ascribed to the ν(OH) vibration of isolated silanols, and three broad bands at *ca.* 1980, 1870 and 1635 cm⁻¹ which are due to the overtones and combinations

of the fundamental vibrational modes of silica, contributing below 1300 cm^{-1} . The only spectroscopic manifestation of the Cr^{VI} sites is a weak absorption band at 1980 cm^{-1} (Figure 1a''), assigned to the first overtone of the $\nu(\text{Cr}=\text{O})$ modes,^{8,47,48,63,79,80} which are obscured in the IR by the intense absorption due to the silica framework vibrations, but were detected at $982 - 990\text{ cm}^{-1}$ by Raman spectroscopy.^{5,12,49,81-85}

During UV-Vis irradiation in CO a series of bands slowly appear in the $\nu(\text{CO})$ region (Figure 1a'), concurrently to the disappearing of the band at 1980 cm^{-1} (Figure 1a''), which indicates the slow reduction of the Cr^{VI} sites and the formation of Cr-carbonyls on the reduced Cr sites. The first band to appear is centered at 2201 cm^{-1} , and reaches the maximum intensity after about 10 minutes of irradiation. A similar absorption band was previously observed by Kohler and Ekerdt during the photo-reduction of a 2 wt% $\text{Cr}^{\text{VI}}/\text{SiO}_2$ in CO,⁷⁵ and by some of us upon adsorption of CO on a $\text{Cr}^{\text{II}}/\text{SiO}_2$ sample selectively modified by N_2O .⁷⁹ In both cases it was ascribed to mono-carbonyl species formed on $\text{Cr}^{\text{IV}}=\text{O}$ (chromyl) sites. After a few minutes of UV-Vis irradiation, also a triplet of bands at 2189, 2183 and 2177 cm^{-1} starts growing, which is known to arise from the vibrational modes of mono-carbonyls and di-carbonyls (symmetric and asymmetric modes) formed on two types of coordinatively unsaturated Cr^{II} sites ($\text{Cr}^{\text{II}}_{\text{B}}$ and $\text{Cr}^{\text{II}}_{\text{A}}$, respectively).^{6-8,58} A weak band is also visible at 2096 cm^{-1} , and assigned to multi-carbonyls formed on a small fraction of even more uncoordinated Cr^{II} sites.^{6,8,86}

The experiment reported in Figure 1a demonstrates that when $\text{Cr}^{\text{VI}}/\text{SiO}_2$ is irradiated by UV-Vis light in presence of CO at room temperature the Cr^{VI} sites are gradually reduced, initially to Cr^{IV} and successively to Cr^{II} , in well agreement with the pioneering work of Kohler and Ekerdt.⁷⁵ The photo-reduction in CO is less efficient than the thermal reduction in CO at $350\text{ }^\circ\text{C}$. This is evident by looking at Figure 1b, that compares the FT-IR spectrum of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ photo-reduced in presence of CO (spectrum 2), to that of CO adsorbed at room temperature on a $\text{Cr}^{\text{II}}/\text{SiO}_2$ sample (i.e. obtained upon thermal reduction of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ in CO at $350\text{ }^\circ\text{C}$, spectrum 3). The spectra have been normalized to the optical thickness of the pellets, hence their total intensity can be quantitatively compared. Spectrum 2 is ca. 4 times less intense than spectrum 3. Since it has been demonstrated that the thermal reduction of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ in CO at $350\text{ }^\circ\text{C}$ leads to the stoichiometric conversion of all the Cr^{VI} sites to Cr^{II} ,¹ Figure 1b indicates that only ca. $\frac{1}{4}$ of the total Cr^{VI} sites are reduced after 60 minutes of UV-Vis irradiation in the presence of CO, partially to Cr^{IV} and partially to Cr^{II} .

It is also of interest the observation that the intensity of the weak band at 2096 cm^{-1} with respect to the triplet centered at 2180 cm^{-1} is higher for spectrum 2 than for spectrum 3. This means that the relative amount of highly uncoordinated Cr^{II} sites capable of forming multi-carbonyls in presence of CO

at room temperature is much higher when the Cr^{II} sites are obtained by photo-reduction of Cr^{VI}. This is probably a consequence of a different strain at the silica surface.⁸⁷ When the reduction of Cr^{VI}/SiO₂ is accomplished at high temperature (350 °C) the obtained Cr^{II} sites have the possibility to relax. Reduction of Cr^{VI}/SiO₂ in milder conditions does not permit the relaxation of the Cr^{II} sites, that remain more accessible to the incoming molecules. This might have important consequences in terms of catalytic performances. Indeed, it has been recently demonstrated that the Cr coordination environment influences both the ethylene insertion and the chain transfer energies, with immediate consequences on the molecular weight distribution of the obtained polyethylene.^{43,88}




Figure 1. Part a): FT-IR spectra of Cr^{VI}/SiO₂ before (spectrum 1), and after 60 minutes of in situ UV irradiation in CO (spectrum 2) at room temperature (P_{CO} = 100 mbar). Inset a' shows the whole sequence of FT-IR spectra collected at intermediate irradiation time after subtraction of spectrum 1. Inset a'' shows a magnification of the spectral region where the only spectroscopic fingerprint of the Cr^{VI} sites appears. Part b): The same spectrum 2 as in part a), compared to the FT-IR spectrum, in the ν(CO) region, of CO adsorbed on a Cr^{II}/SiO₂ sample obtained upon thermal reduction in CO at 350 °C (spectrum 3).

3.2 Photo-induced ethylene polymerization on Cr^{VI}/SiO₂

Also ethylene (i.e. the monomer of the polymerization reaction) may act as reducing agent for Cr^{VI}/SiO₂. However, as for CO, the reaction does not occur at room temperature but needs ca. 100 °C, and also at that temperature it requires a certain induction time that can vary from minutes to hours, depending on the experimental conditions.¹ Ethylene polymerization starts on these reduced Cr sites and the steady state is reached only after several hours. Inspired by the results discussed above for the photo-induced CO-reduction of Cr^{VI}/SiO₂, we decided to investigate whether UV-Vis light irradiation can be exploited for performing ethylene polymerization on Cr^{VI}/SiO₂ at room temperature. The experiments were

performed in static conditions, at room temperature and low ethylene pressure ($P_{C_2H_4} = 100$ mbar), and were followed by means of both DR UV-Vis-NIR and FT-IR spectroscopies.




Figure 2. DR UV-Vis spectra of Cr^{VI}/SiO_2 before (spectrum 0, black) and after UV irradiation in presence of ethylene ($P_{C_2H_4} = 100$ mbar) at room temperature for increasing times (1 = 20 s, 2 = 40 s, 3 = 50 s, 4 = 1 min, 5 = 2 min, 6 = 5 min). The inset shows a magnification of the NIR region, where polyethylene contributes with a series of bands due to the overtones and combinations of the $\nu(CH_2)$ and $\delta(CH_2)$ vibrational modes.

Figure 2 shows the DR UV-Vis-NIR spectra of the Cr^{VI}/SiO_2 sample before (spectrum 0) and after (spectra 1 – 6) UV-Vis irradiation in presence of ethylene at room temperature for increasing times. The spectrum of Cr^{VI}/SiO_2 (spectrum 0) is dominated by two intense bands at ca. 28000 and 21500 cm^{-1} , due to the $O \rightarrow Cr^{VI}$ charge-transfer transitions characteristic of monochromates.^{5,8,11,44,45} The spectra rapidly change upon UV-Vis irradiation in presence of ethylene, and two subsequent events can be distinguished. After less than 50 seconds of irradiation (spectra 1 and 2), the spectroscopic fingerprints of the monochromates decrease in intensity, concurrently to the appearance of two bands at ca. 16500 and 9500 cm^{-1} , which indicate the reduction of the Cr^{VI} sites (d^0 species) to low-valent Cr sites (d^n species). The same bands were observed during the thermal reduction of Cr^{VI}/SiO_2 in ethylene, and ascribed to d-d transitions of Cr^{II} sites having a 6-fold coordination geometry, determined by the presence of oxidized by-products in their coordination sphere.⁶³ The assignment was corroborated by the observation of very similar spectra for Cr^{VI}/SiO_2 reduced by cyclohexene, a cyclic olefin that mimics the reactivity of ethylene without polymerizing.⁶⁹ During this step no ethylene polymerization occurs, as testified by the absence of any absorption band in the 4400 – 4050 cm^{-1} range (inset in Figure 2), that is where polyethylene contributes with a series of bands due to the overtones and combinations of the

$\nu(\text{CH}_2)$ and $\delta(\text{CH}_2)$ vibrational modes. Ethylene polymerization is observed after only 50 seconds of UV-Vis irradiation (spectrum 3), and efficiently proceeds for longer irradiation time. The global effect is the decrease in intensity of the d-d bands at 16500 and 9500 cm^{-1} , and in general of the whole spectrum. The same phenomenon was observed during the thermally induced ethylene polymerization on $\text{Cr}^{\text{VI}}/\text{SiO}_2$ and explained in terms of formation of a layer of polymer on the surface of the catalyst particles, which diffuses the incident light preventing the observation of the active Cr sites.⁶³




Figure 3. Part a): FT-IR spectra of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ (spectrum 0, black) and of the same sample during continuous UV irradiation in presence of ethylene ($P_{\text{C}_2\text{H}_4} = 100$ mbar) at room temperature for increasing times (1 = 30 s, 3 = 1 min, 30 = 90 min). Part b): magnification of the same spectra reported in part a), after subtraction of spectrum 0 and of the contribution due to gaseous ethylene, in the $\nu(\text{CH}_x)$ region. Part c): as part b) in the 1730- 1330 cm^{-1} . Part d): Time evolution of the intensity of the absorption bands at 3030 cm^{-1} (ethylene oxide), 1650 cm^{-1} (methylformate ligated through the C=O moiety) and 1585 cm^{-1} (methylformate ligated in a bidentate fashion).

The DR UV-Vis-NIR experiment discussed above clearly indicates that ethylene has the potential to reduce the Cr^{VI} sites at room temperature under UV-Vis irradiation, and is then polymerized in mild conditions. Figure 3a shows the complementary experiment performed by FT-IR spectroscopy, aimed at monitoring the formation of polyethylene and of the oxidized by-products to identify their nature. The FT-IR spectrum of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ before reaction with ethylene (Figure 3, spectrum 0) has been commented above. During the first minute of UV-Vis irradiation, a series of well-defined IR absorption bands appear in the $\nu(\text{CH}_x)$ stretching region (Figure 3b, spectra 1-3) and in the 1750-1300 cm^{-1} range (Figure 3c, spectra 1-3). In particular, the most evident bands are observed at ca. 3030, 2955 and 2877 cm^{-1} (Figure 3b) and at 1677, 1650 and 1585 cm^{-1} (Figure 3c). These bands are clearly not attributable to polyethylene and reveal the formation of surface by-products resulting from the oxidation of ethylene by

monochromates. According to the UV-Vis-NIR spectra (Figure 2) these by-products remain in the coordination sphere of the reduced Cr^{II} sites. The onset of ethylene polymerization occurs after ca. 2 minutes of continuous UV-Vis irradiation in presence of ethylene, as testified by the constant growth of two bands at 2922 and 2853 cm^{-1} (Figure 3b, spectra 4-30), which are due to the $\nu_{\text{asymm}}(\text{CH}_2)$ and $\nu_{\text{symm}}(\text{CH}_2)$ modes of polyethylene, and of the corresponding $\delta(\text{CH}_2)$ band at ca. 1470 cm^{-1} (Figure 3c, spectra 4-30).

A closer inspection to the spectra collected prior the onset of ethylene polymerization (spectra 1-3) might give indication on the nature of the by-products, and hence on the mechanism of initiation of ethylene polymerization under UV-Vis irradiation. In this respect, it is useful to recall here that methylformate (formed through the Tischenko reaction of two formaldehyde molecules at the same Cr^{II} site) has been identified as the main by-product of ethylene oxidation during the thermally induced ethylene polymerization on $\text{Cr}^{\text{VI}}/\text{SiO}_2$.⁶³ For this reason, in Figure 4 we have compared the spectrum collected after 1 minute of UV-Vis irradiation of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ in presence of ethylene (spectrum 3, the same as in Figure 3) with two reference spectra collected with independent experiments. Spectrum 1 corresponds to methylformate adsorbed on $\text{Cr}^{\text{II}}/\text{SiO}_2$ (after removal of the physisorbed molecules). The spectrum is characterized by very weak bands in the $\nu(\text{CH}_x)$ region (Figure 4a), whereas it is dominated by two intense bands at ca. 1660 cm^{-1} (with a pronounced tail at high wavenumbers) and 1597 cm^{-1} (Figure 4b). Based on the literature of methylformate adsorbed on other systems,^{89,90} both bands are assigned to the $\nu(\text{C}=\text{O})$ vibration of methylformate adsorbed on Cr^{II} sites differing in their adsorption geometry: the former is ascribed to methylformate ligated through the $\text{C}=\text{O}$ moiety, whereas the latter is due to methylformate ligated in a bidentate fashion. The similarity of spectrum 3 to spectrum 1 in this spectral region suggests that also in this case methylformate is one of the by-products of chromate reduction. As already discussed for the thermally induced ethylene polymerization, methylformate originates from the disproportionation of two formaldehyde molecules formed at the same Cr site.⁶³ On the other hand, spectrum 2 was obtained by dosing a limited amount of O_2 on a $\text{Cr}^{\text{II}}/\text{SiO}_2$ catalyst at the very beginning of the ethylene polymerization. This spectrum, which is characterized by quite intense absorption bands in the 3050 – 2800 cm^{-1} region (Figure 4a) but shows negligible features at lower wavenumbers (Figure 4b), was assigned to ethylene oxide adsorbed on partially oxidized $\text{Cr}^{\text{IV}}(=\text{O})/\text{SiO}_2$.⁹¹ The close similarity of spectrum 1 to spectrum 3 in the $\nu(\text{CH}_x)$ region indicates that a second reaction is taking place during the UV-Vis irradiation of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ in ethylene, involving the formation of ethylene oxide.




Figure 4. FT-IR spectra of methylformate adsorbed on Cr^{II}/SiO₂ (spectrum 1), the product of reacting a limited amount of O₂ on a Cr^{II}/SiO₂ catalyst at the very beginning of the ethylene polymerization, previously ascribed to ethylene oxide on Cr^{II}/SiO₂ (spectrum 2), compared to the spectrum collected after 1 minute of UV-Vis irradiation of Cr^{VI}/SiO₂ in presence of ethylene (spectrum 3, the same as in Figure 3). Parts a) and b) show the $\nu(\text{CH}_x)$ and $\nu(\text{C}=\text{O})$ regions, respectively.

In summary, the FT-IR data shown in Figure 3 and Figure 4 indicate the formation of two different oxidized by-products during the initial steps of photo-induced ethylene polymerization on Cr^{VI}/SiO₂ at room temperature: ethylene oxide and methylformate. Interestingly, the absorption bands associated with methylformate keep on growing also during ethylene polymerization (Figure 3d, orange and green circles), although with a different relative intensity. In particular, the band at ca. 1585 cm⁻¹ (green circles) grows faster than that at ca. 1650 cm⁻¹ (orange circles) and becomes the dominant one at longer irradiation/reaction time. This behavior suggests a slow conversion of the methylformate species ligated to the Cr^{II} sites through the C=O moiety into the most stable bidentate species. In contrast, the absorption bands associated to ethylene oxide apparently do not increase in intensity during ethylene polymerization. This is evident by looking to the band at ca. 3030 cm⁻¹ (Figure 3d, grey diamond), which does not overlap with any bands due to the growing polyethylene. As a final comment, the evolution of the FT-IR spectra reported in Figure 3 clearly indicates that: 1) ethylene polymerization is photo-initiated on Cr^{VI}/SiO₂ in the presence of a substantial amount of Cr^{VI} sites which are slower to be reduced, as already reported for the thermally induced ethylene polymerization;⁶³ and 2) ethylene polymerization starts and proceeds in the presence of both types of oxidized by-products, that evidently remain adsorbed at the catalyst surface during the initiation of the reaction, contributing to define the ligands sphere around the active Cr sites.

4. Conclusions

In this work we have presented two examples of photo-induced reactions on the $\text{Cr}^{\text{VI}}/\text{SiO}_2$ Phillips catalyst. At first, we found that irradiation of $\text{Cr}^{\text{VI}}/\text{SiO}_2$ with UV-Vis light in the presence of CO leads to its partial reduction already at room temperature, first to a $\text{Cr}^{\text{IV}}(=\text{O})$ intermediate, and then further to Cr^{II} , in well agreement with the pioneering work of Kohler and Ekerdt.⁷⁵ Although the photo-reduction is less efficient than the thermal one (i.e. a lower fraction of Cr^{VI} sites is reduced), notably it brings about the formation of a larger amount of highly uncoordinated Cr^{II} sites able to form multi-carbonyls in presence of CO. This finding highlights the role of the strain at the silica surface in affecting the properties of the Cr sites, and might have important consequences in terms of catalytic performances.

Second, and novel, we demonstrated that UV-Vis light efficiently triggers the ethylene polymerization on the $\text{Cr}^{\text{VI}}/\text{SiO}_2$ catalyst already at room temperature. By means of DR UV-Vis-NIR and FT-IR spectroscopies we have been able to discriminate between the two fundamental steps involved in the initiation of the reaction, namely the Cr^{VI} reduction by ethylene and the successive polymerization. With respect to the thermally induced ethylene polymerization, the induction time is drastically reduced. Moreover, two types of oxidized by-products deriving from the oxidation of ethylene by chromates have been detected: methylformate and ethylene oxide. While the former was found also during the thermally induced ethylene polymerization, the latter was never observed. The reason might be due to the specific photo-activation mechanism for Cr^{VI} that, according to the literature, involves a single oxygen per time passing through the formation of a $\text{Cr}^{\text{V}}(=\text{O})(\text{O}^-)^*$ excited state. Alternatively, we might consider the possibility that ethylene oxide is formed also during the thermally-induced ethylene polymerization but not detected because it desorbs from the Cr sites at the reaction temperature. This different polymerization mechanism with respect to the thermally induced process could also result in a polymer with peculiar characteristics. However, the limited amount of polyethylene produced in our setup prevented at the moment a more thorough *ex situ* characterization of the products by differential scanning calorimetry or size exclusion chromatography, which will be the object of a future work.

References

- (1) McDaniel, M. P. A Review of the Phillips Supported Chromium Catalyst and Its Commercial Use for Ethylene Polymerization, *Adv. Catal.* **2010**, *53*, 123-606.
- (2) McDaniel, M. P., *Organic Reactions*, in: Handbook of Heterogeneous Catalysis; Ertl, G.; Knözinger, H.; Weitkamp, J., Ed.; VHC: Weinheim, **1997**; Vol. 5, p. 2400.
- (3) Nowlin, T. E., *Business and Technology of the Global Polyethylene Industry*, in; Scrivener Publishing LLC: New York, **2014**.
- (4) McDaniel, M. P. Supported Chromium Catalysts for Ethylene Polymerization, *Adv. Catal.* **1985**, *33*, 47-98.
- (5) Weckhuysen, B. M.; Wachs, I. E.; Shoonheydt, R. A. Surface Chemistry and Spectroscopy of Chromium in Inorganic Oxides, *Chem. Rev.* **1996**, *96*, 3327-3349.
- (6) Groppo, E.; Lamberti, C.; Bordiga, S.; Spoto, G.; Zecchina, A. The Structure of Active Centers and the Ethylene Polymerization Mechanism on the Cr/SiO₂ Catalyst: A Frontier for the Characterization Methods, *Chem. Rev.* **2005**, *105*, 115-183.
- (7) Zecchina, A.; Groppo, E. Surface Chromium Single Sites: Open Problems and Recent Advances, *Proc. R. Soc. A-Math. Phys. Eng. Sci.* **2012**, *468*, 2087-2098.
- (8) Groppo, E.; Seenivasan, K.; Barzan, C. The Potential of Spectroscopic Methods Applied to Heterogeneous Catalysts for Olefin Ppolymerization, *Catal. Sci. Technol.* **2013**, *3*, 858-878.
- (9) Cheng, R.; Liu, Z.; Zhong, L.; He, X.; Qiu, P.; Terano, M.; Eisen, M. S.; Scott, S. L.; Liu, B. Phillips Cr/Silica Catalyst for Ethylene Polymerization, *Adv. Polym. Sci.* **2013**, *257*, 135-202.
- (10) Liu, Z.; He, X.; Cheng, R.; Eisen, M. S.; Terano, M.; Scott, S. L.; Liu, B. Chromium Catalysts for Ethylene Polymerization and Oligomerization, *Adv. Chem. Eng.* **2014**, *44*, 126-191.
- (11) Weckhuysen, B. M.; Schoonheydt, R. A.; Jehng, J. M.; Wachs, I. E.; Cho, S. J.; Ryoo, R.; Kijlstra, S.; Poels, E. Combined DRS-RS-EXAFS-XANES-TPR Study of Supported Chromium Catalysts, *J. Chem. Soc. Faraday Trans.* **1995**, *91*, 3245-3253.
- (12) Groppo, E.; Damin, A.; Bonino, F.; Zecchina, A.; Bordiga, S.; Lamberti, C. New Strategies in the Raman Study of the Cr/SiO₂ Phillips Catalyst: Observation of Molecular Adducts on Cr(II) Sites, *Chem. Mater.* **2005**, *17*, 2019-2027.
- (13) Groppo, E.; Lamberti, C.; Bordiga, S.; Spoto, G.; Zecchina, A. FTIR Investigation of the H₂, N₂ and C₂H₄ Molecular Complexes Formed on the Cr(II) Sites in the Phillips Catalyst: a Preliminary Step in the Understanding of a Complex System, *J. Phys. Chem. B* **2005**, *109*, 15024-15031.
- (14) Groppo, E.; Lamberti, C.; Spoto, G.; Bordiga, S.; Magnacca, G.; Zecchina, A. Tuning the Structure, Distribution and Reactivity of Polymerization Centres of Cr(II)/SiO₂ Phillips Catalyst by Controlled Annealing, *J. Catal.* **2005**, *236*, 233-244.
- (15) Zhong, L.; Lee, M.-Y.; Liu, Z.; Wanglee, Y.-J.; Liu, B.; Scott, S. L. Spectroscopic and Structural Characterization of Cr(II)/SiO₂ Active Site Precursors in Model Phillips Polymerization Catalysts, *J. Catal.* **2012**, *293*, 1-12.
- (16) Brown, C.; Krzystek, J.; Achey, R.; Lita, A.; Fu, R.; Meulenberg, R. W.; Polinski, M.; Peek, N.; Wang, Y.; Van De Burgt, L. J. et al. Mechanism of Initiation in the Phillips Ethylene Polymerization Catalyst: Redox Processes Leading to the Active Site, *ACS Catal.* **2015**, *5*, 5574-5583.
- (17) Brown, C.; Lita, A.; Tao, Y.; Peek, N.; Crosswhite, M.; Mileham, M.; Krzystek, J.; Achey, R.; Fu, R.; Bindra, J. K. et al. Mechanism of Initiation in the Phillips Ethylene Polymerization Catalyst: Ethylene Activation by Cr(II) and the Structure of the Resulting Active Site, *ACS Catal.* **2017**, *7*, 7442-7455.
- (18) Amor Nait Ajjou, J.; Scott, S. L. Reactions of Tetraalkylchromium(IV) with Silica: Mechanism of Grafting and Characterization of Surface Organometallic Complexes, *Organometallics* **1997**, *16*, 86-92.
- (19) Amor Nait Ajjou, J.; Scott, S. L. A Kinetic Study of Ethylene and 1-Hexene Homo- and Copolymerization Catalyzed by a Silica-Supported Cr(IV) Complex: Evidence for Propagation by a Migratory Insertion Mechanism, *J Am Chem Soc* **2000**, *122*, 8968-8976.
- (20) Amor Nait Ajjou, J.; Scott, S. L.; Paquet, V. Synthesis and Characterization of Silica-Stabilized Chromium(IV) Alkylidene Complexes, *J Am Chem Soc* **1998**, *120*, 415-416.
- (21) Delley, M. F.; Núñez-Zarur, F.; Conley, M. P.; Comas-Vives, A.; Siddiqi, G.; Norsic, S.; Monteil, V.; Safonova, O. V.; Copéret, C. Proton Transfers Are Key Elementary Steps in Ethylene Polymerization on Isolated Chromium(III) Silicates, *Proc. Nat. Acad. Sci.* **2014**, *111*, 11624-11629.

- (22) Conley, M. P.; Delley, M. F.; Siddiqi, G.; Lapadula, G.; Norsic, S.; Monteil, V.; Safonova, O. V.; Copéret, C. Polymerization of Ethylene by Silica-Supported Dinuclear Cr^{III} Sites Through an Initiation Step Involving C-H Bond Activation, *Angew. Chem. Int. Ed.* **2014**, *53*, 1872-1876.
- (23) Conley, M. P.; Delley, M. F.; Núñez-Zarur, F.; Comas-Vives, A.; Copéret, C. Heterolytic Activation of C-H Bonds on Cr^{III}-O Surface Sites Is a Key Step in Catalytic Polymerization of Ethylene and Dehydrogenation of Propane, *Inorg. Chem.* **2015**, *54*, 5065-5078.
- (24) Delley, M. F.; Praveen, C. S.; Borosy, A. P.; Núñez-Zarur, F.; Comas-Vives, A.; Copéret, C. Olefin Polymerization on Cr(III)/SiO₂: Mechanistic Insights from the Differences in Reactivity Between Ethene and Propene, *J. Catal.* **2017**, *354*, 223-230.
- (25) Thune, P. C.; Verhagen, C. P. J.; van den Boer, M. J. G.; Niemantsverdriet, J. W. Working Surface Science Model for the Phillips Ethylene Polymerization Catalyst: Preparation and Testing, *J Phys Chem B* **1997**, *101*, 8559-8563.
- (26) Thune, P. C.; Loos, J.; Lemstra, P. J.; Niemantsverdriet, J. W. Polyethylene Formation on a Planar Surface Science Model of a Chromium Oxide Polymerization Catalyst, *J Catal* **1999**, *183*, 1-5.
- (27) Thune, P. C.; Loos, J.; de Jong, A. M.; Lemstra, P. J.; Niemantsverdriet, J. W. Planar Model System for Olefin Polymerization: the Phillips CrO_x/SiO₂ Catalyst, *Top Catal* **2000**, *13*, 67-74.
- (28) Thune, P. C.; Linke, R.; van Gennip, W. J. H.; de Jong, A. M.; Niemantsverdriet, J. W. Bonding of Supported Chromium During Thermal Activation of the CrO_x/SiO₂ (Phillips) Ethylene Polymerization Catalyst, *J Phys Chem B* **2001**, *105*, 3073-3078.
- (29) Thune, P. C.; Loos, J.; Wouters, D.; Lemstra, P. J.; Niemantsverdriet, J. W. The CrO_x/SiO₂/Si(100) catalyst - A surface science approach to supported olefin polymerization catalysis, *Macromol. Symp.* **2001**, *173*, 37-52.
- (30) Thune, P. C.; Loos, J.; Chen, X. H.; van Kimmenade, E. M. E.; Kong, B.; Niemantsverdriet, J. W. H. Visualization of Local Ethylene Polymerization Activity on a Flat CrO_x/SiO₂/Si(100) Model Catalyst, *Topics in Catalysis* **2007**, *46*, 239-245.
- (31) van Kimmenade, E. M. E.; Kuiper, A. E. T.; Tamminga, Y.; Thune, P. C.; Niemantsverdriet, J. W. A Surface Science Model for the Phillips Ethylene Polymerization Catalyst: Thermal Activation and Polymerization Activity, *J. Catal.* **2004**, *223*, 134-141.
- (32) van Kimmenade, E. M. E.; Loos, J.; Niemantsverdriet, J. W.; Thune, P. C. The Effect of Temperature on Ethylene Polymerization Over Flat Phillips Model Catalysts, *J. Catal.* **2006**, *240*, 39-46.
- (33) Pan, Q.; Li, L.; Shaikhutdinov, S.; Freund, H. J. Planar Model System of the Phillips (Cr/SiO₂) Catalyst Based on a Well-Defined Thin Silicate Film, *J. Catal.* **2018**, *357*, 12-19.
- (34) Fong, A.; Yuan, Y.; Ivry, S. L.; Scott, S. L.; Peters, B. Computational Kinetic Discrimination of Ethylene Polymerization Mechanisms for the Phillips (Cr/SiO₂) Catalyst, *ACS Catal.* **2015**, *5*, 3360-3374.
- (35) Fong, A.; Peters, B.; Scott, S. L. One-Electron-Redox Activation of the Reduced Phillips Polymerization Catalyst, via Alkylchromium(IV) Homolysis: A Computational Assessment, *ACS Catal.* **2016**, *6*, 6073-6085.
- (36) Fong, A.; Vandervelden, C.; Scott, S. L.; Peters, B. Computational Support for Phillips Catalyst Initiation via Cr-C Bond Homolysis in a Chromacyclopentane Site, *ACS Catal.* **2018**, *8*, 1728-1733.
- (37) Gierada, M.; Handzlik, J. Active Sites Formation and Their Transformations During Ethylene Polymerization by the Phillips CrO_x/SiO₂ Catalyst, *J. Catal.* **2017**, *352*, 314-328.
- (38) Gierada, M.; Handzlik, J. Computational Insights Into Reduction of the Phillips CrO_x/SiO₂ Catalyst by Ethylene and CO, *J. Catal.* **2018**, *359*, 261-271.
- (39) Chakrabarti, A.; Gierada, M.; Handzlik, J.; Wachs, I. E. Operando Molecular Spectroscopy During Ethylene Polymerization by Supported CrO_x/SiO₂ Catalysts: Active Sites, Reaction Intermediates, and Structure-Activity Relationship, *Top. Catal.* **2016**, *59*, 725-739.
- (40) Gao, J.; Zheng, Y.; Tang, Y.; Jehng, J. M.; Grybos, R.; Handzlik, J.; Wachs, I. E.; Podkolzin, S. G. Spectroscopic and Computational Study of Cr Oxide Structures and Their Anchoring Sites on ZSM-5 Zeolites, *ACS Catal.* **2015**, *5*, 3078-3092.
- (41) Handzlik, J.; Grybos, R.; Tielens, F. Structure of Monomeric Chromium(VI) Oxide Species Supported on Silica: Periodic and Cluster DFT Studies, *J. Phys. Chem. C* **2013**, *117*, 8138-8149.
- (42) Handzlik, J.; Grybos, R.; Tielens, F. Isolated Chromium(VI) Oxide Species Supported on Al-Modified Silica: A Molecular Description, *J. Phys. Chem. C* **2016**, *120*, 17594-17603.

- (43) Floryan, L.; Borosy, A. P.; Núñez-Zarur, F.; Comas-Vives, A.; Copéret, C. Strain Effect and Dual Initiation Pathway in CrIII/SiO₂ Polymerization Catalysts From Amorphous Periodic Models, *J. Catal.* **2017**, *346*, 50-56.
- (44) Weckhuysen, B. M.; Deridder, L. M.; Schoonheydt, R. A. A Quantitative Diffuse Reflectance Spectroscopy Study of Supported Chromium Catalysts, *J. Phys. Chem.* **1993**, *97*, 4756-4763.
- (45) Weckhuysen, B. M.; Verberckmoes, A. A.; Buttiens, A. L.; Schoonheydt, R. A. Diffuse-Reflectance Spectroscopy Study of the Thermal Genesis and Molecular Structure of Chromium Supported Catalysts, *J. Phys. Chem.* **1994**, *98*, 579-584.
- (46) Groppo, E.; Prestipino, C.; Cesano, F.; Bonino, F.; Bordiga, S.; Lamberti, C.; Thüne, P. C.; Niemantsverdriet, J. W.; Zecchina, A. In Situ, Cr K-Edge XAS Study on the Phillips Catalyst: Activation and Ethylene Polymerization, *J. Catal.* **2005**, *230*, 98-108.
- (47) Demmelmaier, C. A.; White, R. E.; van Bokhoven, J. A.; Scott, S. L. Evidence for a Chromasiloxane Ring Size Effect in Phillips (Cr/SiO₂) Polymerization Catalysts, *J. Catal.* **2009**, *262*, 44-56.
- (48) Demmelmaier, C. A.; White, R. E.; van Bokhoven, J. A.; Scott, S. L. Nature of SiOCrO₂Cl and (SiO)₂CrO₂ Sites Prepared by Grafting CrO₂Cl₂ Onto Silica, *J. Phys. Chem. C* **2008**, *112*, 6439-6449.
- (49) Wachs, I. E.; Roberts, C. A. Monitoring Surface Metal Oxide Catalytic Active Sites with Raman Spectroscopy, *Chem. Soc. Rev.* **2010**, *39*, 5002-5017.
- (50) Chakrabarti, A.; Gierada, M.; Handzlik, J.; Wachs, I. E. Operando Molecular Spectroscopy During Ethylene Polymerization by Supported CrO_x/SiO₂ Catalysts: Active Sites, Reaction Intermediates, and Structure-Activity Relationship, *Top. Catal.* **2016**, *59*, 725-739.
- (51) Chakrabarti, A.; Wachs, I. E. The Nature of Surface CrO_x Sites on SiO₂ in Different Environments, *Catal. Lett.* **2015**, *145*, 985-994.
- (52) Guesmi, H.; Tielens, F. Chromium Oxide Species Supported on Silica: A Representative Periodic DFT Model, *J. Phys. Chem. C* **2012**, *116*, 994-1001.
- (53) Gierada, M.; Michorczyk, P.; Tielens, F.; Handzlik, J. Reduction of Chromia-Silica Catalysts: A Molecular Picture, *J. Catal.* **2016**, *340*, 122-135.
- (54) Handzlik, J.; Grybos, R.; Tielens, F. Isolated Chromium(VI) Oxide Species Supported on Al-Modified Silica: A Molecular Description., *J. Phys. Chem. C* **2016**, *120*, 17594-17603.
- (55) Krauss, H. L.; Stach, H., *Z. Anorg. Über Oberflächenverbindungen von Übergangsmetallen. IV*. Polymerisationsreaktionen an Oberflächen-Chrom(II)-Verbindungen Allg. Chem.* **1969**, *366*, 34-42.
- (56) Krauss, v. H. L.; Stach, H. Chrom(II) als wirksamer bestandteil des Phillips Katalysators zur Äthylenpolymerisation, *Inorg. Nucl. Chem. Lett.* **1968**, *4*, 393-397.
- (57) Finch, J. N., Reduction Studies on Supported Chromic Anhydride Catalysts *J. Catal.* **1976**, *43*, 111.
- (58) Zecchina, A.; Garrone, E.; Ghiotti, G.; Coluccia, S. On the Chemistry of Silica Supported Chromium Ions. II. One-Ligand Complexes. Adsorption of Carbon Monoxide, Carbon Dioxide and Pyridine., *J. Phys. Chem.* **1975**, *79*, 972-978.
- (59) Liu, B.; Nakatani, H.; Terano, M. New Aspects of the Induction Period of Ethene Polymerization Using Phillips CrO_x/SiO₂ Catalyst Probed by XPS, TPD and EPMA, *J Mol Catal a-Chem* **2002**, *184*, 387-398.
- (60) Liu, B. P.; Nakatani, H.; Terano, M. Mechanistic implications of the Unprecedented Transformations of Ethene Into Propene and Butene over Phillips CrO_x/SiO₂ Catalyst During Induction Period, *J Mol Catal a-Chem* **2003**, *201*, 189-197.
- (61) Xia, W.; Liu, B.; Fang, Y.; Hasebe, K.; Terano, M. Unique Polymerization Kinetics Obtained from Simultaneous Interaction of Phillips Cr(VI)O_x/SiO₂ Catalyst With Al-Alkyl Cocatalyst and Ethylene Monomer, *J. Mol. Cat.* **2006**, *256*, 301-308.
- (62) Zhong, L.; Liu, Z.; Cheng, R.; Tang, S.; Qiu, P.; He, X.; Terano, M.; Liu, B. Active Site Transformation During the Induction Period of Ethylene Polymerization over the Phillips CrO_x/SiO₂ Catalyst, *Chemcatchem* **2012**, *4*.
- (63) Barzan, C.; Piovano, A.; Braglia, L.; Martino, G. A.; Lamberti, C.; Bordiga, S.; Groppo, E. Ligands Make the Difference! Molecular Insights into Cr-VI/SiO₂ Phillips Catalyst during Ethylene Polymerization, *J. Am. Chem. Soc.* **2017**, *139*, 17064-17073.
- (64) Potter, K. C.; Beckerle, C. W.; Jentoft, F. C.; Schwerdtfeger, E.; McDaniel, M. P. Reduction of the Phillips Catalyst by Various Olefins: Stoichiometry, Thermochemistry, Reaction Products and Polymerization Activity, *J. Catal.* **2016**, *344*, 657-668.

- (65) Cicmil, D.; Meeuwissen, J.; Vantomme, A.; Wang, J.; van Ravenhorst, I. K.; van der Bij, H. E.; Munoz-Murillo, A.; Weckhuysen, B. M. Polyethylene with Reverse Co-monomer Incorporation: From an Industrial Serendipitous Discovery to Fundamental Understanding, *Angew. Chem. Int. Ed.* **2015**, *54*, 13073-13079.
- (66) Cicmil, D.; Meeuwissen, J.; Vantomme, A.; Weckhuysen, B. M. Real-time Analysis of a Working Triethylaluminium-Modified Cr/Ti/SiO₂ Ethylene Polymerization Catalyst with In Situ Infrared Spectroscopy, *ChemCatChem* **2016**, *8*, 1937-1944.
- (67) Cicmil, D.; van Ravenhorst, I. K.; Meeuwissen, J.; Vantomme, A.; Weckhuysen, B. M. Structure-Performance Relationships of Cr/Ti/SiO₂ Catalysts Modified with TEAL for Oligomerisation of Ethylene: Tuning the Selectivity towards 1-Hexene, *Catal Sci Technol* **2016**, *6*, 731-743.
- (68) Schwerdtfeger, E.; Buck, R.; McDaniel, M. Reduction of Cr(VI) Polymerization Catalysts by Non-Olefinic Hydrocarbons, *Appl. Catal. A* **2012**, *423-424*, 91-99.
- (69) Barzan, C.; Damin, A. A.; Budnyk, A.; Zecchina, A.; Bordiga, S.; Groppo, E. Pre-Reduction of the Phillips Cr^{VI}/SiO₂ Catalyst by Cyclohexene: A Model for the Induction Period of Ethylene Polymerization, *J. Catal.* **2016**, *337*, 45-51.
- (70) Anpo, M.; Thomas, J. M. Single-Site Photocatalytic Solids for the Decomposition of Undesirable Molecules, *Chem. Commun.* **2006** 3273-3278.
- (71) Anpo, M.; Kim, T. H.; Matsuoka, M. The Design of Ti-, V-, Cr-Oxide Single-Site Catalysts within Zeolite Frameworks and Their Photocatalytic Reactivity for the Decomposition of Undesirable Molecules-The Role of Their Excited States and Reaction Mechanisms, *Catal. Today* **2009**, *142*, 114-124.
- (72) Kamegawa, T.; Morishima, J.; Matsuoka, M.; Thomas, J. M.; Anpo, M. Eliminating Traces of Carbon Monoxide Photocatalytically from Hydrogen with a Single-Site, Non-Noble Metal Catalyst, *J. Phys. Chem. C* **2007**, *111*, 1076-1078.
- (73) Berg, O.; Hamdy, M. S.; Maschmeyer, T.; Moulijn, J. A.; Bonn, M.; Mul, G. On the Wavelength-Dependent Performance of Cr-Doped Silica in Selective Photo-Oxidation, *J. Phys. Chem. C* **2008**, *112*, 5471-5475.
- (74) Tsukamoto, D.; Shiro, A.; Shiraishi, Y.; Hirai, T. Visible-Light-Induced Partial Oxidation of Cyclohexane by Cr/Ti/Si Ternary Mixed Oxides with Molecular Oxygen, *J. Phys. Chem. C* **2011**, *115*, 19782-19788.
- (75) Kohler, S. D.; Ekerdt, J. G. Infrared Spectroscopic Characterization of Chromium Carbonyl Species Formed by Ultraviolet Photoreduction of Silica-Supported Chromium(vi) in Carbon-Monoxide, *J. Phys. Chem.* **1994**, *98*, 4336-4342.
- (76) Mino, L.; Zecchina, A.; Martra, G.; Rossi, A. M.; Spoto, G. A Surface Science Approach to TiO₂ P25 Photocatalysis: An in Situ FTIR Study of Phenol Photodegradation at Controlled Water Coverages from Sub-Monolayer to Multilayer, *Appl. Catal. B-Environ.* **2016**, *196*, 135-141.
- (77) Mino, L.; Negri, C.; Zecchina, A.; Spoto, G. Photodegradation of Organic Pollutants on TiO₂ P25 Surfaces Investigated by Transmission FTIR Spectroscopy Under in Situ UV-Vis Irradiation, *Z. Phys. Chem.* **2016**, *230*, 1441-1451.
- (78) Barzan, C.; Mino, L.; Morra, E.; Groppo, E.; Chiesa, M.; Spoto, G. Photoinduced Ethylene Polymerization on Titania Nanoparticles, *ChemCatChem* **2017**, *9*, 4324-4327.
- (79) Groppo, E.; Damin, A.; Otero Arean, C.; Zecchina, A. Enhancing the Initial Rate of Polymerisation of the Reduced Phillips Catalyst by One Order of Magnitude, *Chem. Eur. J.* **2011**, *17*, 11110 – 11114.
- (80) Cieslak-Golonka, M. Spectroscopy of chromium(VI) species, *Coordin. Chem. Rev.* **1991**, *109*, 223-249.
- (81) Weckhuysen, B. M.; Wachs, I. E. Raman Spectroscopy of Supported Chromium Oxide Catalysts - Determination of Chromium-Oxygen Bond Distances and Bond Orders, *J. Chem. Soc. Faraday Trans.* **1996**, *92*, 1969-1973.
- (82) Weckhuysen, B. M.; Wachs, I. E. In Situ Raman Spectroscopy of Supported Chromium Oxide Catalysts: ¹⁸O₂-¹⁶O₂ Isotopic Labeling Studies, *J. Phys. Chem. B* **1997**, *101*, 2793-2796.
- (83) Vuurman, M. A.; Wachs, I. E.; Stufkens, D. J.; Oskam, A. Characterization of Chromium-Oxide Supported on Al₂O₃, ZrO₂, TiO₂, and SiO₂ under Dehydrated Conditions, *J Mol Catal* **1993**, *80*, 209-227.
- (84) Wachs, I. E. Raman and IR Studies of Surface Metal Oxide Species on Oxide Supports: Supported Metal Oxide Catalysts, *Catal. Today* **1996**, *27*, 437-455.
- (85) Lee, E. L.; Wachs, I. E. In Situ Raman Spectroscopy of SiO₂-Supported Transition Metal Oxide Catalysts: An Isotopic O-18-O-16 Exchange Study, *J. Phys. Chem. C* **2008**, *112*, 6487-6498.

- (86) Spoto, G.; Bordiga, S.; Garrone, E.; Ghiotti, G.; Zecchina, A.; Petrini, G.; Leofanti, G. Cr(II) and Cr(III) Ions Grafted at Internal Nests of a Pentasilic Zeolite (Silicalite) - Characterization and Formation of Polycarbonylic, Polynitrosylic, and Mixed Species by Interaction with CO and NO, *J Mol Catal* **1992**, *74*, 175-184.
- (87) Amakawa, K.; Sun, L.; Guo, C.; Hävecker, M.; Kube, P.; Wachs, I. E.; Lwin, S.; Frenkel, A. I.; Patlolla, A.; Hermann, K.; Schlögl, R.; Trunschke, A. How Strain Affects the Reactivity of Surface Metal Oxide Catalysts, *Angew. Chem. Int. Ed.* **2013**, *52*, 13553-13557.
- (88) Tonosaki, K.; Taniike, T.; Terano, M. Origin of Broad Molecular Weight Distribution of Polyethylene Produced by Phillips-Type Silica-Supported Chromium Catalyst, *J. Mol. Catal. A-Chem.* **2011**, *340*, 33-38.
- (89) Millar, G. J.; Rochester, C. H.; Waugh, K. C. Infrared Study of Methyl Formate and Formaldehyde Adsorption on reduced and Oxidised Silica-Supported Copper Catalysts, *J. Chem. Soc. Faraday Trans.* **1991**, *87*, 2785-2793.
- (90) Millar, G. J.; Rochester, C. H.; Waugh, K. C. Evidence for the Adsorption of Molecules at Special Sites Located at Copper/Zinc Oxide Interfaces. Part 3.—Fourier-Transform Infrared Study of Methyl Formate Adsorption on Reduced and Oxidised Cu/ZnO/SiO₂ Catalysts, *J. Chem. Soc. Faraday Trans.* **1992**, *88*, 3497-3503.
- (91) Groppo, E.; Lamberti, C.; Bordiga, S.; Spoto, G.; Zecchina, A. In-Situ FTIR Spectroscopy of Key Intermediates in the First Stages of Ethylene Polymerization on the Cr/SiO₂ Phillips Catalyst: Solved the Puzzle of the Initiation Mechanism?, *J. Catal.* **2006**, *240*, 172-181.

TOC Graphic

