



ELSEVIER

Contents lists available at ScienceDirect

Data in brief

journal homepage: www.elsevier.com/locate/dib

Data Article

Operando X-ray absorption spectra and mass spectrometry data during hydrogenation of ethylene over palladium nanoparticles

Aram L. Bugaev^{a,*}, Alexander A. Guda^a, Ilia A. Pankin^{a,b}, Elena Groppo^b, Riccardo Pellegrini^c, Alessandro Longo^{d,e}, Alexander V. Soldatov^a, Carlo Lamberti^{a,f}^a The Smart Materials Research Institute, Southern Federal University, Sladkova 178/24, 344090 Rostov-on-Don, Russia^b Department of Chemistry, INSTM and NIS Centre, University of Turin, Via Quarellio 15, 10125 Turin, Italy^c Chimet SpA - Catalyst Division, Via di Pescaiola 74, Vicinomagno Arezzo, 52041 Italy^d Netherlands Organization for Scientific Research at ESRF, BP 220, F-38043 Grenoble Cedex 9, France^e Istituto per Lo Studio Dei Materiali Nanostrutturati (ISMN)-CNR, UOS Via Ugo La Malfa, 153, 90146 Palermo, Italy^f Department of Physics and CrisDi Interdepartmental Centre, University of Turin, Via P. Giuria 1, 10125 Turin, Italy

ARTICLE INFO

Article history:

Received 14 March 2019

Received in revised form 2 April 2019

Accepted 18 April 2019

Available online 26 April 2019

ABSTRACT

We report the series of Pd *K*-edge X-ray absorption spectra collected during hydrogenation of ethylene with variable ethylene/hydrogen ratio over carbon supported palladium nanoparticles. The data presented in this article includes normalized X-ray absorption spectra, k^2 -weighted oscillatory $\chi(k)$ functions extracted from the extended X-ray absorption fine structure (EXAFS) and k^2 -weighted Fourier-transformed EXAFS data, $\chi(R)$. Each spectrum is reported together with the hydrogen, ethylene and helium flow rates, adjusted during its collection. In addition, time evolution of the ratio of m/Z signals of 30 and 28 registered by online mass spectrometer is presented. The data analysis is reported in Bugaev et al., *Catal. Today*, 2019 [1].

© 2019 The Author(s). Published by Elsevier Inc. This is an open access article under the CC BY license (<http://creativecommons.org/licenses/by/4.0/>).

DOI of original article: <https://doi.org/10.1016/j.cattod.2019.02.068>.

* Corresponding author.

E-mail address: abugaev@sfedu.ru (A.L. Bugaev).

<https://doi.org/10.1016/j.dib.2019.103954>

2352-3409/© 2019 The Author(s). Published by Elsevier Inc. This is an open access article under the CC BY license (<http://creativecommons.org/licenses/by/4.0/>).

Specifications table

Subject area	Catalysis, spectroscopy, nanomaterials
More specific subject area	Operando spectroscopy of palladium nanocatalyst
Type of data	Table, text file, figure
How data was acquired	X-ray absorption spectra were collected in transmission mode at BM26A beamline of ESRF synchrotron. Mass spectrometry data were collected by online mass spectrometer manufactured by Pfeiffer.
Data format	Processed, Analyzed
Experimental factors	X-ray absorption spectra in transmission mode
Experimental features	Carbon supported palladium nanoparticles pre-reduced in hydrogen exposed to the reaction mixture with variable ethylene/hydrogen ratio
Data source location	Grenoble, France (45.209749, 5.688410)
Data accessibility	Data is provided with this article
Related research article	Companion paper to: A. Bugaev et al. The Role of Palladium Carbides in the Catalytic Hydrogenation of Ethylene over Supported Palladium Nanoparticles. <i>Catal. Today</i> , in press, https://doi.org/10.1016/j.cattod.2019.02.068 .

Value of the data

- The dataset of X-ray absorption spectra is measured on well-defined Pd nanocatalyst during ethylene hydrogenation.
- The EXAFS data can be re-used within single- and multiple-shell Fourier analysis.
- The XANES data of well-defined 2.6 nm palladium nanoparticles can be exploited for extension of a machine learning databases.
- Deep analysis of X-ray absorption spectra may provide an insight on catalyst degradation under working conditions.

1. Data

The dataset consists of 37 different Pd *K*-edge X-ray absorption spectra collected during ethylene hydrogenation reaction under variable ethylene-to-hydrogen ratio [1]. The spectra are presented in the three forms. First, the initial EXAFS spectra after normalization are presented in Fig. 1. The background subtracted k^2 -weighted oscillatory EXAFS functions $\chi(k)$ are reported in Fig. 2. The k^2 -weighted Fourier-transformed $\chi(R)$ functions are shown in Fig. 3. Normalized EXAFS spectra, $\chi(k)$ functions, and $\chi(R)$ Fourier-transforms are listed in the files “muE.dat”, “chiK.dat”, and “chiR.dat”, respectively. The correspondence between the spectrum number and the adopted helium, hydrogen and ethylene flows is given in the Table 1. The time evolution of the ratio of m/Z signals of 30 and 28, registered by online mass spectrometer, is reported in Fig. 4, the corresponding data are listed in the file MS.dat.

2. Experimental design, materials, and methods

Sample. The sample for which all the data were collected is an industrial 5 wt% Pd/C catalyst provided by Chimet S.p.A. The catalyst consists of the palladium nanoparticles supported on the activated wood-based carbon. The average nanoparticle size is 2.6 nm with narrow particle size distribution. Detailed characterization of both the catalyst and the support itself have been reported in a number of works [2–13].

EXAFS data collection. Experimental Pd *K*-edge EXAFS spectra were measured at BM26A beamline [14,15] of European Synchrotron Radiation Facility (ESRF, Grenoble, France). The X-ray beam was monochromatized by Si(111) double-crystal monochromator and harmonic rejection was performed by Pt coated mirrors. The catalyst was loaded into an *in situ* cell with build-in heater [16]. Two additional stainless steel washers were inserted to increase the thickness of the sample, which resulted in the absorption step $\Delta\mu x = 0.35$. The spectra were collected in transmission mode using ionization chambers. Palladium foil was used to calibrate the energy. The energy range for the spectra was set




Fig. 1. Normalized EXAFS spectra collected during the first (a), second (b) and third (c) ethylene hydrogenation cycles.




Fig. 2. k^2 -weighted oscillatory EXAFS functions $\chi(k)$ of the spectra collected during the first (a), second (b) and third (c) ethylene hydrogenation cycles.

from 24.15 to 25.15 eV, which corresponds to k_{max} around 14.4 \AA^{-1} (see Fig. 2). The energy step in the pre-edge region was set to 5 eV with acquisition time of 1.5 s, step in the XANES region was 1 eV with 1.5 s acquisition, and the step in the EXAFS region was defined to obtain a uniform 0.04 \AA^{-1} step in the k -space. The time per point in the EXAFS region was increasing quadratically from 1.5 to 2.5 s.

Catalytic reaction. The cell with the sample was connected to the gas line of BM26A [17]. To avoid overpressure when flowing the gas mixture, the sample was sieved to 100–150 μm before being loaded into the cell. During the catalytic reaction, the pressure was monitored by Bourdon tube pressure gauge. The gas line was equipped with remotely controlled Bronkhorst mass flow controllers (MFCs) and electrovalves. All MFCs were calibrated using Agilent flow meter. Before starting the catalytic reaction, the sample was reduced in hydrogen at $125 \text{ }^\circ\text{C}$ for 30 minutes. The catalytic hydrogenation of ethylene to ethane was tested by stepwise increasing of the ethylene-to-hydrogen ratio. Helium was used as the carrier gas. The exact flow rates of the three gases are reported in Table 1. Because of the fact that the ethylene-to-hydrogen ratio was changed three times from 0 to 10/15, we virtually divided the whole set of data into three respective parts, which are referred to as 1st cycle, 2nd cycle and 3rd cycle.




Fig. 3. Amplitudes of the k^2 -weighted Fourier-transformed EXAFS data, $\chi(R)$, of the spectra collected during the first (a), second (b) and third (c) ethylene hydrogenation cycles.

Table 1

The correspondence between the spectrum number and the adopted helium, hydrogen and ethylene flows.

1st cycle				2 nd cycle				3 rd cycle			
#	Flow rate (mL/min)			#	Flow rate (mL/min)			#	Flow rate (mL/min)		
	He	H ₂	C ₂ H ₄		He	H ₂	C ₂ H ₄		He	H ₂	C ₂ H ₄
1	35	15	0	13	35	15	0	26	35	15	0
2	34	15	1	14	35	15	0	27	35	15	0
3	33	15	2	15	34	15	1	28	34	15	1
4	32	15	3	16	33	15	2	29	33	15	2
5	31	15	4	17	32	15	3	30	32	15	3
6	30	15	5	18	31	15	4	31	31	15	4
7	29	15	6	19	30	15	5	32	30	15	5
8	29	15	6	20	29	15	6	33	29	15	6
9	28	15	7	21	28	15	7	34	28	15	7
10	27	15	8	22	27	15	8	35	27	15	8
11	26	15	9	23	27	15	8	36	26	15	9
12	25	15	10	24	26	15	9	37	25	15	10
				25	25	15	10				

The products in the gas phase after the sample were monitored by online mass spectrometer manufactured by Pfeiffer. To quantitatively determine the ratio between ethylene and ethane in the output gas mixture, we used the ratio of m/Z signals 30 and 28. This ratio is changing from 0 for pure ethylene to ca. 0.22 for pure ethane.

EXAFS data processing. EXAFS data was processed in a standard way using Demeter package [18]. At the first step, a linear extrapolation of the pre-edge region was used to construct the pre-edge lines. After subtraction of the pre-edge lines the spectra were normalized by post-edge lines, representing second order polynomials. In this form, the spectra are presented in the Fig. 1, and are listed in the Supplementary materials. Then, the smooth background lines were subtracted from the spectra to extract the oscillatory part of EXAFS spectra [19]. To recalculate the incident photon energy E to the photoelectron wavenumber k , the energy of the edge E_0 was determined as the maximum of the first derivative for each spectrum. To enhance the oscillation at higher k -values, the oscillatory functions were multiplied by k^2 . These k^2 -weighted $\chi(k)$ -functions are reported in Fig. 2 and are listed in the Supplementary materials. Finally, the k^2 -weighted $\chi(k)$ -functions were Fourier-transformed applying the k -window from 3 to 14 \AA^{-1} . The amplitudes of $\chi(k)$ are shown in Fig. 3 and are listed in the




Fig. 4. The relative fraction of the MS-detected signals for $m/Z = 30$ and $m/Z = 28$ as a function of time. The defined ethylene flow rate at different time points are specified in the graph.

Supplementary materials. For the analysis presented in the paper [1], the lower boundary of the k -window was increased to 4 \AA^{-1} to reduce the contribution of the backscattering from carbon atoms of the support [8,20] and of the palladium carbide phase [21]. The upper boundary was lowered to 12 \AA^{-1} to avoid possible effect of the noise at high k -values.

Acknowledgments

Authors acknowledge the Russian Ministry of Education and Science for financial support (Project RFMEFI58417X0029, Agreement 14.584.21.0029).

Transparency document

Transparency document associated with this article can be found in the online version at <https://doi.org/10.1016/j.dib.2019.103954>.

Appendix A. Supplementary data

Supplementary data to this article can be found online at <https://doi.org/10.1016/j.dib.2019.103954>.

References

- [1] A.L. Bugaev, A.A. Guda, I.A. Pankin, E. Groppo, R. Pellegrini, A. Longo, A.V. Soldatov, C. Lamberti, The role of palladium carbides in the catalytic hydrogenation of ethylene over supported palladium nanoparticles, *Catal. Today*, in press, <https://doi.org/10.1016/j.cattod.2019.02.068>.
- [2] A. Piovano, A. Lazzarini, R. Pellegrini, G. Leofanti, G. Agostini, S. Rudić, A.L. Bugaev, C. Lamberti, E. Groppo, Progress in the characterization of the surface species in activated carbons by means of INS spectroscopy coupled with detailed DFT calculations, *Adv. Condens. Matter Phys.* 2015 (2015). Art. n. 803267.
- [3] G. Agostini, C. Lamberti, R. Pellegrini, G. Leofanti, F. Giannici, A. Longo, E. Groppo, Effect of pre-reduction on the properties and the catalytic activity of Pd/carbon catalysts: a comparison with Pd/Al₂O₃, *ACS Catal.* 4 (2014) 187–194.
- [4] A.L. Bugaev, A.A. Guda, A. Lazzarini, K.A. Lomachenko, E. Groppo, R. Pellegrini, A. Piovano, H. Emerich, A.V. Soldatov, I.A. Bugaev, V.P. Dmitriev, J.A. van Bokhoven, C. Lamberti, In situ formation of hydrides and carbides in palladium catalyst: when XANES is better than EXAFS and XRD, *Catal. Today* 283 (2017) 119–126.
- [5] A.L. Bugaev, O.A. Usoltsev, A.A. Guda, K.A. Lomachenko, I.A. Pankin, Y.V. Rusalev, H. Emerich, E. Groppo, R. Pellegrini, A.V. Soldatov, J.A. van Bokhoven, C. Lamberti, Palladium carbide and hydride formation in the bulk and at the surface of palladium nanoparticles, *J. Phys. Chem. C* 122 (2018) 12029–12037.
- [6] A.L. Bugaev, O.A. Usoltsev, A. Lazzarini, K.A. Lomachenko, A.A. Guda, R. Pellegrini, M. Carosso, J.G. Vitillo, E. Groppo, J. van Bokhoven, A.V. Soldatov, C. Lamberti, Time-resolved operando studies of carbon supported Pd nanoparticles under hydrogenation reactions by X-ray diffraction and absorption, *Faraday Discuss* 208 (2018) 187–205.

- [7] A.L. Bugaev, A.A. Guda, K.A. Lomachenko, A. Lazzarini, V.V. Srabionyan, J.G. Vitillo, A. Piovano, E. Groppo, L.A. Bugaev, A.V. Soldatov, V.P. Dmitriev, R. Pellegrini, J.A. van Bokhoven, C. Lamberti, Hydride phase formation in carbon supported palladium hydride nanoparticles by in situ EXAFS and XRD, *J. Phys. Conf. Ser.* 712 (2016), 012032.
- [8] A.L. Bugaev, A.A. Guda, K.A. Lomachenko, V.V. Shapovalov, A. Lazzarini, J.G. Vitillo, L.A. Bugaev, E. Groppo, R. Pellegrini, A.V. Soldatov, J.A. van Bokhoven, C. Lamberti, Core-shell structure of palladium hydride nanoparticles revealed by combined X-ray absorption spectroscopy and X-ray diffraction, *J. Phys. Chem. C* 121 (2017) 18202–18213.
- [9] G. Agostini, E. Groppo, A. Piovano, R. Pellegrini, G. Leofanti, C. Lamberti, Preparation of supported Pd catalysts: from the Pd precursor solution to the deposited Pd²⁺ phase, *Langmuir* 26 (2010) 11204–11211.
- [10] A. Lazzarini, R. Pellegrini, A. Piovano, S. Rudić, C. Castan-Guerrero, P. Torelli, M.R. Chierotti, R. Gobetto, C. Lamberti, E. Groppo, The effect of surface chemistry on the performances of Pd-based catalysts supported on activated carbons, *Catal. Sci. Technol.* 7 (2017) 4162–4172.
- [11] A. Lazzarini, A. Piovano, R. Pellegrini, G. Leofanti, G. Agostini, S. Rudić, M.R. Chierotti, R. Gobetto, A. Battiato, G. Spoto, A. Zecchina, C. Lamberti, E. Groppo, A comprehensive approach to investigate the structural and surface properties of activated carbons and related Pd-based catalysts, *Catal. Sci. Technol.* 6 (2016) 4910–4922.
- [12] R. Pellegrini, G. Leofanti, G. Agostini, E. Groppo, M. Rivallan, C. Lamberti, Pd-supported catalysts: evolution of support porous texture along Pd deposition and alkali-metal doping, *Langmuir* 25 (2009) 6476–6485.
- [13] A.L. Bugaev, A.A. Guda, K.A. Lomachenko, E.G. Kamyshova, M.A. Soldatov, G. Kaur, S. Øien-Ødegaard, L. Braglia, A. Lazzarini, M. Manzoli, S. Bordiga, U. Olsbye, K.P. Lillerud, A.V. Soldatov, C. Lamberti, Operando study of palladium nanoparticles inside UiO-67 MOF for catalytic hydrogenation of hydrocarbons, *Faraday Discuss* 208 (2018) 287–306.
- [14] S. Nikitenko, A.M. Beale, A.M. van der Eerden, S.D. Jacques, O. Leynaud, M.G. O'Brien, D. Detollenaere, R. Kaptein, B.M. Weckhuysen, W. Bras, Implementation of a combined SAXS/WAXS/QEXAFS set-up for time-resolved in situ experiments, *J. Synchrotron Radiat.* 15 (2008) 632–640.
- [15] E. Groppo, A. Lazzarini, M. Carosso, A. Bugaev, M. Manzoli, R. Pellegrini, C. Lamberti, D. Banerjee, A. Longo, Dynamic behavior of Pd/P4VP catalyst during the aerobic oxidation of 2-propanol: a simultaneous SAXS/XAS/MS operando study, *ACS Catal.* 8 (2018) 6870–6881.
- [16] G.L. Chiarello, M. Nachtegaal, V. Marchionni, L. Quaroni, D. Ferri, Adding diffuse reflectance infrared Fourier transform spectroscopy capability to extended x-ray-absorption fine structure in a new cell to study solid catalysts in combination with a modulation approach, *Rev. Sci. Instrum.* 85 (2014), 074102.
- [17] V. Martis, A.M. Beale, D. Detollenaere, D. Banerjee, M. Moroni, F. Gosselin, W. Bras, A high-pressure and controlled-flow gas system for catalysis research, *J. Synchrotron Radiat.* 21 (2014) 462–463.
- [18] B. Ravel, M. Newville, ATHENA, ARTEMIS, HEPHAESTUS: data analysis for X-ray absorption spectroscopy using IFEFFIT, *J. Synchrotron Radiat.* 12 (2005) 537–541.
- [19] L.A. Bugaev, L.A. Avakyan, V.V. Srabionyan, A.L. Bugaev, Resolution of interatomic distances in the study of local atomic structure distortions by energy-restricted x-ray absorption spectra, *Phys. Rev. B* 82 (2010), 064204.
- [20] A.L. Bugaev, A.A. Guda, K.A. Lomachenko, V.V. Srabionyan, L.A. Bugaev, A.V. Soldatov, C. Lamberti, V.P. Dmitriev, J.A. van Bokhoven, Temperature- and pressure-dependent hydrogen concentration in supported PdH_x nanoparticles by Pd K-edge X-ray absorption spectroscopy, *J. Phys. Chem. C* 118 (2014) 10416–10423.
- [21] A.A. Skorynina, A.A. Tereshchenko, O.A. Usoltsev, A.L. Bugaev, K.A. Lomachenko, A.A. Guda, E. Groppo, R. Pellegrini, C. Lamberti, A. Soldatov, Time-dependent carbide phase formation in palladium nanoparticles, *Radiat. Phys. Chem.*, in press, <https://doi.org/10.1016/j.radphyschem.2018.11.033>.